Optical nonlinearity in silicon at mid-infrared wavelengths

Wang, Ting; Venkatram, Nalla; Chen, George; Ji, Wei; Tan, Dawn T. H.

2014

Wang, T., Venkatram, N., Chen, G., Ji, W., & Tan, D. T. H. (2014). Optical nonlinearity in silicon at mid-infrared wavelengths. In CLEO: 2014, OSA Technical Digest (online) (Optical Society of America, 2014), paper STu1I.1.

<https://hdl.handle.net/10356/101856>

© 2014 OSA. This paper was published in CLEO: Science and Innovations and is made available as an electronic reprint (preprint) with permission of OSA. The paper can be found at the following official URL:

http://www.opticsinfobase.org/abstract.cfm?URI=CLEO_SI-2014-STu1I.1&origin=search.

One print or electronic copy may be made for personal use only. Systematic or multiple reproduction, distribution to multiple locations via electronic or other means, duplication of any material in this paper for a fee or for commercial purposes, or modification of the content of the paper is prohibited and is subject to penalties under law.

Downloaded on 26 Apr 2023 11:22:25 SGT

Optical nonlinearity in silicon at mid-infrared wavelengths

Ting Wang^{1*}, Nalla Venkatram^{2,3}, George Chen¹, Wei Ji², and Dawn T. H. Tan¹

¹Engineering Product Development, Singapore University of Technology and Design, 20 Dover Drive, Singapore, 138682

²Department of Physics, National University of Singapore, 2 Science Drive 3, Singapore, 117551

³Centre for Disruptive Photonic Technologies, Nanyang Technological University, Singapore, 637371

*wang_ting@sutd.edu.sg

Abstract: We report the wavelength dependency of third-order nonlinearity and multi-photon absorption of silicon in the spectral range from 1.6 μm to 6 μm , including the nonlinear figure of merit [1].

OCIS codes: (190.0190) Nonlinear optics; (190.7110) Ultrafast nonlinear optics.

I. Introduction

The interest in the development of high Kerr nonlinearity with weak multi-photon absorption (MPA) processes has increased over the past decade, because of their importance for ultra-fast all-optical signal processing [2]. However, in the mid-infrared (mid-IR), its nonlinearity has not been well characterized. The multi-photon absorption places a fundamental limitation on the usefulness of any high $\chi^{(3)}$ material in all-optical switching schemes [3] based on an intensity-dependent refractive index [4], especially strong two-photon absorption (TPA) in silicon. At telecom wavelengths, relatively high peak intensity is normally required to trigger the third-order Kerr nonlinearity, but also leads to a strong TPA [4]. Therefore, the combination of high Kerr nonlinearity (n_2) and relatively weaker MPA (α_n) beyond the TPA region makes silicon highly promising for nonlinear applications at mid-IR wavelengths.

The third-order nonlinear coefficients (n_2) and multi-photon absorption processes have been previously reported up to 2.75 μm [5], which shows a decrement of n_2 towards longer wavelength from the peak value at 1.9 μm [6]. Here, we extend the measurements further to 6 μm in the mid-IR range.

II. Mid-IR Z-scan Experiments

We explore the measurements of degenerated MPA coefficients and nonlinear refractive index n_2 in silicon, in this broad mid-IR range, using the Z-scan technique [5].

FIG. 2. Variation of n_2 in silicon at mid-IR wavelengths from 1.6-6 μm : crosses (data from ref. [6]) and diamonds (data measured by SUTD).

The dispersion of n_2 from 1.6-6 μm is measured and shown in Fig. 1. A sharp increment of n_2 from telecom wavelength towards mid-IR range is observed with a peak at 2.1 μm , following by a dip at longer wavelength, which matches with the reference data in the literature (red crosses in Fig. 1) [7]. In order to further explore the dispersion of n_2 at mid-IR wavelengths, the Z-scan measurements are extended to longer wavelength beyond 2PA region up to 6 μm . According to Kramers-Kronig (KK) relations [8], two-photon resonance leads to the peak of n_2 at the edge of transition wavelength (2.2 μm), which is in line with measured results in Fig. 1. The value of n_2 appears to decay

rapidly after entering 3PA region, and saturates at a relatively constant value of $5.2 \times 10^{-14} \text{ cm}^2/\text{GW}$. The variation of n_2 appears to be consistent with KK transform [9] as shown in Fig. 1. These results are a strong indication of consistent strength of Kerr nonlinearity at mid-IR wavelength.

III. Calculation of nonlinear figure of merit and discussion

In Fig. 2, we use normalized FOM data at the 2PA region from F. Gholami et al. [5] to bridge up with our FOM results beyond $2.2 \text{ } \mu\text{m}$. It can be clearly observed in Fig. 2 that the FOM is lower at short wave-IR region, and increases sharply with increasing wavelengths, due to decaying MPA in the mid-IR region. In the region of 3PA, in contrast to that for 2PA, 3PA coefficient exhibits an increment for the red-shift of the wavelengths, resulting in a drop in FOM. In addition, the value of n_2 is observed to decay beyond 2PA region, thus, the calculated FOM rolls over until it reaches the 3PA-4PA transition wavelength at $3.3 \text{ } \mu\text{m}$. Due to the dramatic decrement of MPA in 4PA dominant region, the nonlinear FOM exhibits a steady rise beyond 3PA region, which is almost identical to the magnitudes in the 2PA dominant short wave-IR region [10].

FIG. 2. Nonlinear figure of merit (FOM) with presence of MPA: crosses (data from ref. [7]) and stars (data measured by SUTD).

IV. Conclusion

In summary, we report the measurements of degenerated MPA and Kerr nonlinear coefficients covering the near-IR and mid-IR spectral region up to $6 \text{ } \mu\text{m}$. The results indicate a good strength of Kerr nonlinearity and significant enhancement in nonlinear FOM at longer mid-IR wavelengths ($3\text{--}6 \text{ } \mu\text{m}$), which appears to be a promising candidate for on-chip all-optical signal processing.

V. References

- [1] T. Wang, N. Venkatram, J. Gosciniaik, Y. Cui, G. Qian, J. Wei and D. T. H. Tan, "Multi-photon absorption and third-order nonlinearity in silicon and mid-infrared wavelengths," *Opt. Exp.* **21**, No. 26, 32192 (2013)
- [2] M. Dinu, F. Quochi, and H. Garcia, "Third-order nonlinearities in silicon at telecom wavelengths," *Appl. Phys. Lett.* **82**, 2954-2956 (2003).
- [3] Q. Lin, J. Zhang, G. Piredda, R.W. Boyd, P. M. Fauchet, and G. P. Agrawal, "Dispersion of silicon nonlinearities in the near infrared region," *Appl. Phys. Lett.* **91**, 021111 (2007).
- [4] V. Mizrahi, K. W. DeLong, G. I. Stegeman, M. A. Saifi, and M. J. Andrejco, "Two-photon absorption as a limitation to all-optical switching," *Opt. Lett.* **14**, 1140 (1989)
- [5] F. Gholami, S. Zlatanovic, A. Simic, L. Liu, and D. Borlaug, N. Alic, M. Nezhad, Y. Fainman, and S. Radic, "Third-order nonlinearity in silicon beyond 2350 nm," *Appl. Phys. Lett.* **99**, 091102 (2011)
- [6] N. Hon, R. Soref, and B. Jalali, "The third-order nonlinear optical coefficients of Si, Ge, and $\text{Si}_{1-x}\text{Ge}_x$ in the midwave and longwave infrared," *Appl. Phys. Lett.* **110**, 011301 (2001)
- [7] A. D. Bristow, N. Rotenberg, and H. M. van Driel, "Two-photon absorption and Kerr coefficients of silicon for 850-2200 nm," *Appl. Phys. Lett.* **90**, 191104 (2007)
- [8] M. Sheik-Bahae, A. A. Said, T. H. Wei, D. J. Hagan, and E. W. Stryland, "Sensitive measurement of optical nonlinearities using a single beam," *IEEE J. Quantum Electron.* **26**, 760 (1990)
- [9] C. Bree, A. Demircan, and G. Steinmeyer, "Kramers-Kronig relations and high-order nonlinear susceptibilities," *Phys. Rev. A* **85**, 033806 (2012)
- [10] M. Sheik-Bahae, D. J. Hagan, and E. W. Van Stryland, "Dispersion and band-gap scaling of the electronic Kerr effect in solids associated with two-photon absorption," *Phys. Rev. Lett.* **65**, 96 (1990)