Room-temperature visible electroluminescence from aluminum nitride thin film embedded with aluminum nanocrystals

Yang, Ming; Liu, Yang; Ding, Liang; Wong, Jen It; Liu, Zhen; Zhang, Sam; Zhang, Wali; Zhu, Fu Rong; Chen, Tupei

2008

Yang, M., Liu, Y., Ding, L., Wong, J. I., Liu, Z., & Zhang, S., et al. (2008). Room-temperature visible electroluminescence from aluminum nitride thin film embedded with aluminum nanocrystals. *IEEE Transactions on Electron Devices*, 55(12), 3605-3609.

<https://hdl.handle.net/10356/101982>

<https://doi.org/10.1109/TED.2008.2006531>

© 2008 IEEE. Personal use of this material is permitted. However, permission to reprint/republish this material for advertising or promotional purposes or for creating new collective works for resale or redistribution to servers or lists, or to reuse any copyrighted component of this work in other works must be obtained from the IEEE. This material is presented to ensure timely dissemination of scholarly and technical work. Copyright and all rights therein are retained by authors or by other copyright holders. All persons copying this information are expected to adhere to the terms and constraints invoked by each author's copyright. In most cases, these works may not be reposted without the explicit permission of the copyright holder. <http://www.ieee.org/portal/site..>

Room-Temperature Visible Electroluminescence From Aluminum Nitride Thin Film Embedded With Aluminum Nanocrystals

Ming Yang, *Student Member, IEEE*, T. P. Chen, Yang Liu, Liang Ding, Jen It Wong, *Student Member, IEEE*, Zhen Liu, Sam Zhang, Wali Zhang, and Furong Zhu

Abstract—In this brief, room-temperature visible electroluminescence (EL) from aluminum nitride (AlN) thin films containing aluminum nanocrystals (nc-Al) prepared by a radio-frequency magnetron sputtering technique is reported. The EL shows a broad spectrum peaked at 565 nm (2.19 eV) when a negative gate voltage is applied. A linear relationship between the EL and the current transport in the nc-Al/AlN thin film system is observed, and both the current transport and the EL intensity exhibit a power-law dependence on the gate voltage. These results are explained in terms of the formation of percolation networks of tunneling paths by the nc-Al arrays and the radiative recombination of the injected electrons and holes via the deep-level defects at the locations of nc-Al along the tunneling paths.

Index Terms—Aluminum nanocrystal, aluminum nitride, electroluminescence, light emitting device.

I. INTRODUCTION

ALUMINUM nitride (AlN) has promising applications in surface acoustic wave [1], [2], memory [3], [4], and optoelectronic devices [5]–[8]. AlN exhibits outstanding physical properties, such as a wide bandgap (6.2 eV) [9], high thermal conductivity (320 W/mK) [10], and good match of both thermal expansion coefficient and lattice constant to those of Si substrates [10], [11]. A number of techniques can be used to fabricate AlN films, including reactive evaporation [12], chemical vapor deposition [13], molecular beam epitaxy [14], pulsed laser deposition [15], and reactive magnetron sputtering [1], [2], [7]. Among them, the sputtering technique is widely used due to its advantages of fast growth rate and low

cost. Recently, amorphous AlN thin film containing aluminum nanocrystals (nc-Al) has been successfully deposited on Si substrates by a radio-frequency (RF) magnetron sputtering technique to form a nanocomposite thin film. It has been demonstrated that such nc-Al/AlN nanocomposite thin film possesses memory effect [4] and interesting current conduction behaviors [16]. The conduction modulation caused by the charge trapping and detrapping in such nc-Al/AlN thin film under ultraviolet (UV) illumination has also been observed [17]. In this brief, we report visible electroluminescence (EL) from the nc-Al/AlN thin films at room temperature.

II. EXPERIMENTAL DETAILS

The nc-Al/AlN thin film was deposited on p-type $\langle 100 \rangle$ -oriented Si substrate by the technique of RF magnetron sputtering. The purity of the Al target used in the sputtering is 99.999%. The sputtering was performed in a gaseous mixture of Ar and N₂. Prior to the deposition, both the Al target and the Si substrate were cleaned by the sputtering. The base pressure of the chamber was lower than 1.0×10^{-7} torr. During the deposition, the flow rates for Ar and N₂ were 15 and 45 sccm, respectively. The RF power during deposition was 500 W, and the substrate temperature was 400 °C. The thickness of the thin film deposited on the Si substrate is ~ 34 nm. An identical thin film deposition was also carried out on a fused silica substrate for the absorption study. To form the metal–insulator–semiconductor (MIS) light-emitting structure, the wafer backside was coated with an aluminum layer with the thickness of 200 nm to form the backside contact. Subsequently, the array of indium tin oxide (ITO) gate electrodes, with a diameter of 2.5 mm for each electrode, was formed on the sample surface.

X-ray photoemission spectroscopy (XPS) and cross-sectional transmission electron microscopy (TEM) were used to investigate the chemical and structural properties of the nc-Al/AlN thin films, respectively. Ar ion etching of the film surface (about 5 nm in depth) was performed prior to the XPS measurement to remove the Al oxide present in the surface region [4]. A Keithley 2400 semiconductor characterization system was used for both the current–voltage (I – V) and EL measurements. The light-emission measurement was carried out with a Dongwoo Optron PDS-1 photomultiplier tube (PMT) detector (in current-sensing mode) and a Dongwoo Optron DM150i monochromator (the wavelength range is 185–1600 nm; the resolution is 0.2 nm). To obtain the

Manuscript received June 4, 2008; revised September 5, 2008. Current version published November 26, 2008. This work was supported in part by the Academic Research Fund from the Ministry of Education Singapore under Project ARC 1/04, in part by the National Research Foundation of Singapore under Project NRF-G-CRP 2007-01, and in part by the National Natural Science Foundation of China under project 60806040. The review of this brief was arranged by Editor L. Lunardi.

M. Yang, L. Ding, J. I. Wong, Z. Liu, and W. Zhang are with Nanyang Technological University, Singapore 639798 (e-mail: yangming@pmail.ntu.edu.sg).

T. P. Chen is with the Division of Microelectronics, School of Electrical and Electronic Engineering, Nanyang Technological University, Singapore 639798 (e-mail: echentp@ntu.edu.sg).

Y. Liu is with the School of Microelectronics, University of Electronic Science and Technology of China, Chengdu 610054, China.

S. Zhang is with the School of Mechanical and Aerospace Engineering, Nanyang Technological University, Singapore 639798.

F. Zhu is with the Institute of Materials Research and Engineering, Singapore 117602.

Color versions of one or more of the figures in this brief are available online at <http://ieeexplore.ieee.org>.

Digital Object Identifier 10.1109/TED.2008.2006531

Fig. 1. Gaussian peak deconvolution of the Al 2p core level from the XPS measurement of the nc-Al/AlN thin film.

Fig. 2. Cross-sectional TEM image of the nc-Al/AlN thin film. The inset shows the existence of nc-Al embedded in the AlN matrix.

absorption coefficient of the thin films, transmission and reflection measurements were carried out with a Shimadzu UV-2450 spectrometer in the wavelength range of 190–850 nm. All the measurements were conducted in a dark environment at room temperature.

III. RESULTS AND DISCUSSIONS

Fig. 1 shows the peak deconvolution of the Al 2p core level obtained from the XPS measurement. As shown in the figure, the XPS Al 2p core level can be decomposed into three Gaussian peaks, namely the AlN, Al 2p_{1/2}, and Al 2p_{3/2} peaks. As an Ar ion etching of the film surface (about 5 nm in depth) was performed prior to the XPS measurement to remove the Al oxide present in the surface region [4], no significant Al₂O₃ signal was detected in this brief. The area ratio of the AlN peak to the Al peaks confirms that the deposited thin film is Al-rich. The cross-sectional TEM image for the nc-Al/AlN thin film is shown in Fig. 2. The nc-Al with lattice fringes embedded in the amorphous AlN matrix can be observed from the high-resolution TEM image shown in the inset of Fig. 2.

The nc-Al/AlN thin film exhibits a visible EL with yellow color when a negative gate voltage (V_{GATE}) is applied to the

Fig. 3. EL spectra obtained from the nc-Al/AlN thin film under different V_{GATE} .

Fig. 4. Power-law dependence of the gate current density (J_{GATE}) and the integrated EL intensity on the V_{GATE} .

ITO gate electrode. Fig. 3 shows the typical EL spectra for different V_{GATE} 's. A broad but prominent EL band extending from 350 to 850 nm can be clearly observed, and the EL intensity becomes stronger as the magnitude of the negative V_{GATE} increases. The EL peak is located at ~ 565 nm (2.19 eV). When the polarity of V_{GATE} is positive, no EL can be induced regardless of the magnitude of the V_{GATE} . The EL cannot be due to the ITO gate electrode itself, considering that the light emission from the gate electrode usually happens as a result of the impact of hot electrons to the gate electrode biased with a positive gate voltage [18]. In our case, the ITO electrode is negatively biased to supply electrons during the EL measurement. Therefore, the nc-Al/AlN thin film is responsible for the visible EL.

The current transport behavior in the nc-Al/AlN thin film is studied with the I - V measurement in order to understand the EL behaviors. Fig. 4 shows the gate current density (J_{GATE}) as a function of the magnitude of the V_{GATE} . The curve fitting suggests that the J_{GATE} and the V_{GATE} have a power-law relationship

$$J_{\text{GATE}} = \alpha_0 V_{\text{GATE}}^{\zeta} \quad (1)$$

where α_0 is a coefficient and ζ is the scaling exponent. From the curve fitting, it is found that the scaling exponent $\zeta \approx 2$.

Note that ζ is affected by the concentration and distribution of nanocrystals, as well as the charge trapping in the nanocrystals [16], [17]. In particular, ζ could be changed by the application of a voltage or even an I - V measurement itself due to the change in the charging state [16]. The power-law behavior of current transport has been reported for arrays of small metallic dots [19] and metal nanocrystal arrays [20]. The current transport in the nc-Al/AlN thin film can be explained by the percolation concept [16]. Tunneling paths are formed in the thin film by the nc-Al arrays, where the nanocrystals act as tunneling sites for the injected electrons. Due to the existence of many nanocrystals randomly distributed in the thin film, percolation networks of the tunneling paths, which electrically connect the ITO gate to the Si substrate, are formed. This greatly enhances the current conduction in the thin film, which plays an important role in the EL process.

The integrated EL intensity as a function of the magnitude of the V_{GATE} is also shown in Fig. 4. As can be observed from the figure, the dependence of the EL intensity on the V_{GATE} also follows a power law which has the same trend as that of the current transport, showing a linear relationship between the current transport and the EL intensity. This indicates that the light emission is directly related to the carrier transport in the thin film rather in the ITO gate or at the interface between the ITO gate (or the p-Si substrate) and the thin film. It also implies that the radiative recombination of the injected electrons and holes could occur along the tunneling paths formed by the nc-Al, regardless of the actual recombination processes.

The radiative recombination of the electrons and holes could be associated with defects in the nc-Al/AlN thin film. Various defects, including Al vacancy (V_{Al}), N vacancy (V_{N}), and Al and N antisite defects (Al_{N} and N_{Al}), exist in the AlN system [21], [22]. The material system in this brief is actually an Al-rich AlN thin film with the existence of a large amount of nc-Al. As revealed by the TEM images, the interfaces between the nc-Al and the AlN are imperfect. Due to the imperfection of the AlN matrix with the embedded nc-Al, it is reasonable to assume that there are large amounts of defects at the interfacial regions between the embedded nc-Al and the AlN matrix. Aside from the aforementioned defects, the oxygen impurity may also contribute to the luminescence due to the deep-level defects created by the substitution of nitrogen in the AlN with oxygen [23], [24]. However, the oxygen-related defects are unlikely to be the major contributors to the EL in this brief, as no significant signal of oxygen impurity was detected in the XPS measurement on our samples. Nevertheless, the absorption spectrum of the nc-Al/AlN thin film shown in Fig. 5 suggests the existence of defects in the thin film. As can be seen in the figure, the nc-Al/AlN thin film shows a band-to-band absorption edge (~ 6.2 eV) similar to that of the pure AlN [25] and a very broad band tail. The broad band tail is indicative of a number of possible electronic defect structures present in the thin film [23].

As pointed out earlier, both the EL intensity and the current transport follow a similar power-law dependence on the gate voltage, which suggests that the radiative recombination of the transported electrons and holes occurs at the locations of nc-Al along the tunneling paths. Therefore, if the defects are respon-

Fig. 5. Room-temperature absorption spectrum of the nc-Al/AlN thin film. The corresponding spectrum of pure AlN (from [25]) is also presented for comparison.

Fig. 6. Schematic energy band diagram of the light-emitting structure and a possible radiative recombination process of the injected electrons and holes via the deep-level defects at the location of nc-Al along the nc-Al tunneling paths.

sible for the EL, then the defects at the interfaces between nc-Al and AlN, rather than those in the amorphous AlN matrix, play the major role. It is worth mentioning that the existence of embedded nc-Al in the AlN matrix has two roles; one is to enhance the current transport by forming a large number of conductive tunneling paths, and the other is to introduce the interfacial luminescence defects along the tunneling paths. The radiative recombination of the injected electrons and holes in the nc-Al/AlN thin film is thus associated with these defects at the locations of nc-Al. Fig. 6 shows a possible defect-related radiative recombination process for the observed EL in the nc-Al/AlN thin film. The defects involved in the process are those deep-level defects with energy levels ~ 3.4 – 4.5 eV below the conduction band edge of AlN [21]. As mentioned previously, under a negative V_{GATE} , electrons and holes are injected from the ITO gate and the p-type Si substrate, respectively. When the injected electrons are transported along the tunneling paths formed by nc-Al, some of the electrons are trapped by the deep-level defects. The radiative recombination of the trapped electrons with the holes in the valence band of AlN injected from the p-Si substrate produces light emission with energies of ~ 1.7 – 2.8 eV (note that the AlN bandgap is ~ 6.2 eV). This

explains the observed EL peak centered at 2.19 eV. It also explains why the current transport and the EL intensity exhibit a similar power-law dependence on the V_{GATE} .

IV. CONCLUSION

In summary, room-temperature visible EL with a broad spectrum peaked at 565 nm (2.19 eV) from AlN thin film containing nc-Al fabricated by RF magnetron sputtering technique has been observed. It is found that the EL intensity is linearly related to the current transport in the nanocomposite system, and both the current transport and the EL intensity exhibit a power-law dependence on the applied voltage. The current conduction is explained in terms of the formation of percolation networks of the tunneling paths by nc-Al in the AlN matrix. The light emission is attributed to the radiative recombination of the injected electrons and holes via the deep-level defects at the locations of nc-Al along the tunneling paths.

REFERENCES

- [1] M. Benetti, D. Cannata, F. Di Pietrantonio, E. Verona, A. Generosi, B. Paci, and V. Rossi Albertini, "Growth and characterization of piezoelectric AlN thin films for diamond-based surface acoustic wave devices," *Thin Solid Films*, vol. 497, no. 1/2, pp. 304–308, Feb. 2006.
- [2] P. Kirsch, M. B. Assouar, O. Elmazria, V. Mortet, and P. Alnot, "5 GHz surface acoustic wave devices based on aluminum nitride/diamond layered structure realized using electron beam lithography," *Appl. Phys. Lett.*, vol. 88, no. 22, p. 223 504, May 2006.
- [3] C. H. Lai, A. Chin, B. F. Hung, C. F. Cheng, W. J. Yoo, M. F. Li, C. Zhu, S. P. McAlister, and D.-L. Kwong, "A novel program-erasable high- κ AlN Si MIS capacitor," *IEEE Electron Device Lett.*, vol. 26, no. 3, pp. 148–150, Mar. 2005.
- [4] Y. Liu, T. P. Chen, P. Zhao, S. Zhang, S. Fung, and Y. Q. Fu, "Memory effect of Al-rich AlN films synthesized with rf magnetron sputtering," *Appl. Phys. Lett.*, vol. 87, no. 3, p. 033 112, Jul. 2005.
- [5] A. Watanabe, T. Takeuchi, K. Hirose, H. Amano, K. Hiramatsu, and I. Akasaki, "The growth of single crystalline GaN on a Si substrate using AlN as an intermediate layer," *J. Cryst. Growth*, vol. 128, no. 1–4, pp. 391–396, Mar. 1993.
- [6] H. Lu, W. J. Schaff, J. Hwang, H. Wu, G. Koley, and L. F. Eastman, "Effect of an AlN buffer layer on the epitaxial growth of InN by molecular-beam epitaxy," *Appl. Phys. Lett.*, vol. 79, no. 10, pp. 1489–1491, Sep. 2001.
- [7] V. Ligatchev, T. K. S. Wong, S. F. Yoon, J. Ahn, and Rusli, "Steady-state and transient room-temperature photoluminescence of AlN films, prepared by RF magnetron sputtering," *Diamond Related Mater.*, vol. 12, no. 10/11, pp. 1897–1902, Oct./Nov. 2003.
- [8] Y. Taniyasu, M. Kasu, and T. Makimoto, "An aluminium nitride light-emitting diode with a wavelength of 210 nanometres," *Nature*, vol. 441, no. 7091, pp. 325–328, May 2006.
- [9] H. Yamashita, K. Fukui, S. Misawa, and S. Yoshida, "Optical properties of AlN epitaxial thin films in the vacuum ultraviolet region," *J. Appl. Phys.*, vol. 50, no. 2, pp. 896–898, Feb. 1979.
- [10] E. S. Dettmer, B. M. Romenesko, H. K. Charles, Jr., B. Carkhuff, and D. J. Merrill, "Steady-state thermal conductivity measurements of AlN and SiC substrate materials," *IEEE Trans. Compon., Hybrids, Manuf. Technol.*, vol. 12, no. 4, pp. 543–547, Dec. 1989.
- [11] C. Oliveiraa, K. G. Grigorovb, H. S. Maciela, M. Massia, and C. Otani, "High textured AlN thin films grown by RF magnetron sputtering: Composition, structure, morphology and hardness," *Vacuum*, vol. 75, no. 4, pp. 331–338, Aug. 2004.
- [12] R. Bensalem, A. Abid, and B. J. Sealy, "Evaporated aluminium nitride encapsulating films," *Thin Solid Films*, vol. 143, no. 2, pp. 141–153, Oct. 1986.
- [13] K. Dovidenko, S. Oktyabrysky, and J. Narayan, "Characteristics of stacking faults in AlN thin films," *J. Appl. Phys.*, vol. 82, no. 9, pp. 4296–4299, Nov. 1997.
- [14] S. Stevens, A. Ohtani, M. Kinniburgh, and R. Beresford, "Microstructure of AlN on Si (111) grown by plasma-assisted molecular beam epitaxy," *Appl. Phys. Lett.*, vol. 65, no. 3, pp. 321–323, Jul. 1994.
- [15] L. Lv, Q.-S. Li, L. Li, L.-C. Zhang, C.-F. Wang, and H.-X. Qi, "Effects of substrate temperature and nitrogen pressure on growth of AlN films by pulsed laser deposition," *Chin. Phys. Lett.*, vol. 24, no. 2, pp. 552–554, Feb. 2007.
- [16] Y. Liu, T. P. Chen, H. W. Lau, J. I. Wong, L. Ding, S. Zhang, and S. Fung, "Charging effect on current conduction in aluminum nitride thin films containing Al nanocrystals," *Appl. Phys. Lett.*, vol. 89, no. 12, p. 123 101, Sep. 2006.
- [17] Z. Liu, T. P. Chen, Y. Liu, L. Ding, M. Yang, J. I. Wong, Z. H. Cen, Y. B. Li, S. Zhang, and S. Fung, "Light-induced instability in current conduction of aluminum nitride thin films embedded with Al nanocrystals," *Appl. Phys. Lett.*, vol. 92, no. 1, p. 013 102, Jan. 2008.
- [18] D. J. DiMaria, J. R. Kirtley, E. J. Pakulis, D. W. Dong, T. S. Kuan, F. L. Pesavento, T. N. Theis, J. A. Cutro, and S. D. Brorson, "Electroluminescence studies in silicon dioxide films containing tiny silicon islands," *J. Appl. Phys.*, vol. 56, no. 2, pp. 401–416, Jul. 1984.
- [19] A. A. Middleton and N. S. Wingreen, "Collective transport in arrays of small metallic dots," *Phys. Rev. Lett.*, vol. 71, no. 19, pp. 3198–3201, Nov. 1993.
- [20] R. Parthasarathy, X.-M. Lin, and H. M. Jaeger, "Electronic transport in metal nanocrystal arrays: The effect of structural disorder on scaling behavior," *Phys. Rev. Lett.*, vol. 87, no. 18, p. 186 807, Oct. 2001.
- [21] T. L. Tansley and R. J. Egan, "Point-defect energies in the nitrides of aluminum, gallium, and indium," *Phys. Rev. B, Condens. Matter*, vol. 45, no. 19, pp. 10942–10950, May 1992.
- [22] C. Stampfl and C. G. Van de Walle, "Theoretical investigation of native defects, impurities, and complexes in aluminum nitride," *Phys. Rev. B, Condens. Matter*, vol. 65, no. 15, p. 155 212, Apr. 2002.
- [23] R. A. Youngman and J. H. Harris, "Luminescence studies of oxygen-related defects in aluminum nitride," *J. Amer. Ceram. Soc.*, vol. 63, no. 11, pp. 3238–3246, 1990.
- [24] G. A. Slack, L. J. Schowaltera, D. Morellic, and J. A. Freitas, Jr., "Some effects of oxygen impurities on AlN and GaN," *J. Cryst. Growth*, vol. 246, no. 3/4, pp. 287–298, Dec. 2002.
- [25] J. F. Muth, J. D. Brown, M. A. L. Johnson, Z. Yu, R. M. Kolbas, J. W. Cook, Jr., and J. F. Schetzina, "Absorption coefficient and refractive index of GaN, AlN, and AlGaIn alloys," *MRS Internet J. Nitride Semicond. Res.*, vol. 4S1, p. G5.2, 1999.

Ming Yang (S'06) was born in Xiamen, China, in 1982. He received the B.Eng. degree (first-class honors) in microelectronics from Nanyang Technological University (NTU), Singapore, in 2005. He is currently working toward the Ph.D. degree at NTU.

His research interest includes the electrical and optoelectronic properties of nanoscale materials and their device applications.

T. P. Chen from February 1990 to October 1991, he was a Visiting Scientist at Fritz-Haber Institute of Max-Planck Society, Berlin, Germany. From 1994 to 1997, he was a Postdoctoral Fellow with The University of Hong Kong, Pokfulam, Hong Kong, and the National University of Singapore, Singapore. From June to December 1996, he was with Chartered Semiconductor Manufacturing Ltd. He was with PSB Singapore for two and a half years, as a Senior Scientist, before he joined Nanyang Technological University, Singapore, in February 2000.

He is currently an Associate Professor with the Division of Microelectronics, School of Electrical and Electronic Engineering, Nanyang Technological University. He is the author or coauthor of more than 150 peer-reviewed journal papers (as of July 2008), about 70 conference proceeding papers, and one book chapter. He is the holder of one granted and two pending U.S. patents. His current research interests include nanoscale CMOS devices and reliability physics, nanocrystals and applications in nanoelectronic devices (memories and single/few-electron devices, etc.) and photonic/optoelectronic devices (light emitters, optoelectronic memories, photodetectors, solar cells, etc.), Si optoelectronic integrated circuits for chip-to-chip and system-to-system communication, and flexible/printing electronics.

Yang Liu received the B.Sc. degree in microelectronics from Jilin University, Changchun, China, in 1998 and the Ph.D. degree from Nanyang Technological University, Singapore, in 2005.

From May 2005 to July 2006, he was a Research Fellow with Nanyang Technological University, Singapore. In 2006, he was awarded the prestigious two-year Singapore Millennium Foundation Fellowship. In 2008, he joined the School of Microelectronics, University of Electronic Science and Technology, Chengdu, China, as a Full Professor.

He is the author or coauthor of more than 50 journal papers and more than 16 conference proceeding papers. His current research includes nanoscale CMOS device physics and reliability physics (reliability of CMOS device and memory devices, etc.), nanocrystals and their applications in electronic devices (nanocrystal-based Flash memory, resistive memory, few-electron devices, etc.) and photonic/optoelectronic devices (Si-based light emitters and optoelectronic memory), and Si-based optical ICs.

Liang Ding was born in China in 1982. He received the B.Sc. degree in physics (optical and optoelectronic physics) from Huazhong University of Science and Technology, Huazhong, China, in 2004. He is currently working toward the Ph.D. degree at the Nanyang Technological University, Singapore.

His current research interests include the optical and optoelectronic properties and applications of semiconductor nanocrystals.

Jen It Wong (S'03) was born in Johor Baru, Malaysia, in 1982. He received the B.Eng. degree in microelectronics from Nanyang Technological University (NTU), Singapore, in 2005. He is currently working toward the Ph.D. degree at NTU.

His research interests include semiconductor nanocrystals, with particular interest on their application to memory and optoelectronic devices.

Zhen Liu was born in Changsha, China, in November 1983. He received the B.Eng. degree in microelectronics from Nanyang Technological University (NTU), Singapore, in 2006. He is currently working toward the Ph.D. degree at NTU.

His research interests include the synthesis and characterizations of metal nanoparticles, targeting electrical, optical, and optoelectronic applications.

Sam Zhang received the Ph.D. degree in ceramics from The University of Wisconsin, Madison, in 1991.

He is currently a Full Professor with the School of Mechanical and Aerospace Engineering, Nanyang Technological University, Singapore. He serves as Editor-in-chief for *Nanoscience and Nanotechnology Letters* and Principal Editor for the *Journal of Materials Research (USA)*. He has authored and coauthored more than 180 research papers, with more than 1000 nonself-citation. Some of his research

papers frequently entered the Elsevier TOP25 Hottest Articles list. His research interests include the processing and characterization of nanocomposite thin films and coatings, biological coatings, bioMEMS, and electronic thin films.

Prof. Zhang is the Vice President of The Institute of Materials (East Asia).

Wali Zhang was born in Kaifeng, China, in 1980. He received the B.Eng. degree from Dalian Jiaotong University, Dalian, China, in 2003 and the M.Eng. degree from Shanghai Jiaotong University, Shanghai, China, in 2006, both in material science. He is currently working toward the Ph.D. degree at Nanyang Technological University, Singapore.

His research interests include the optoelectronic properties of Si nanostructures.

Furong Zhu received the Ph.D. degree from Charles Darwin University, Darwin, Australia, in 1993.

From 1993 to 1995, he did his postdoctoral work in the Department of Electrical and Electronic Engineering, Kyoto University, Kyoto, Japan. From 1995 to 1997, he was a Research Fellow with Murdoch University, Perth, Australia. He is currently a Senior Scientist and a Manager of the OPV/OLED Program with the Institute of Materials Research and Engineering, Singapore. His current research interests include OLEDs, organic photovoltaics, and thin-film

material-oriented research.