Electrochemical performance of cobalt free, $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ cathodes for lithium batteries

Kim, H.; Kang, K. S.; Kim, W. S.; Karthikeyan, K.; Lee, G. W.; Lee, Y. S.; Aravindan,
Vanchiappan; Amaresh, Samuthirapandian

2012

Karthikeyan, K., Amaresh, S., Lee, G. W., Aravindan, V., Kim, H., Kang, K. S., et al. (2012).
Electrochemical performance of cobalt free, $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ cathodes for
lithium batteries. *Electrochimica Acta*, 68, 246–253.

<https://hdl.handle.net/10356/106078>

<https://doi.org/10.1016/j.electacta.2012.02.076>

© 2012 Elsevier. This is the author created version of a work that has been peer reviewed
and accepted for publication by *Electrochimica Acta*, Elsevier. It incorporates referee's
comments but changes resulting from the publishing process, such as copyediting,
structural formatting, may not be reflected in this document. The published version is
available at: [DOI: <http://dx.doi.org/10.1016/j.electacta.2012.02.076>]

Downloaded on 26 Apr 2023 18:08:17 SGT

Electrochemical performance of cobalt free, $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ cathodes for lithium batteries

K. Karthikeyan^a, S. Amaresh^a, G.W. Lee^a, V. Aravindan^{a,b}, H. Kim^c, K.S. Kang^c, W.s. Kim^d, and
Y.S. Lee^{a,*}

^a Faculty of Applied Chemical Engineering, Chonnam National University, Gwang-ju 500-757, Republic
of Korea

^b Energy Research Institute (ERI@N), Nanyang Technological University, Research Techno Plaza, 50
Nanyang Drive, Singapore 637553, Singapore

^c Department of Materials Science and Engineering, Seoul National University, Seoul 151-742, Republic
of Korea

^d Daejung EM Co. Ltd, Incheon 405-820, Republic of Korea

Abstract

Cobalt free, eco-friendly layered $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ compounds are synthesized using adipic acid assisted sol-gel method. The structure and morphology of the prepared materials are examined by X-ray diffraction (XRD) and scanning electron microscopy (SEM) and transmission electron microscopy (TEM), respectively. The XRD results revealed that all

* Corresponding author

materials possess layered α -NaFeO₂ structure with $R\bar{3}m$ space group. TEM images confirmed the presence of carbon on the surface of the synthesized material. Galvanostatic charge/discharge studies demonstrated that cyclic performance and rate capability of the materials were improved by the presence of carbon and crystalline nature of the material as well. Among the synthesized materials, the sample with 1 M adipic acid exhibited not only a high discharge capacity of 160 mAh g⁻¹, but also showed an excellent cycling performance with a capacity retention of over 92 % after 25 cycles. In addition, electrochemical impedance spectroscopy (EIS) was used to confirm the improvement in electronic conductivity and the results are discussed in detail.

Key words: *Layered materials; Li_{1.2}(Mn_{0.32}Ni_{0.32}Fe_{0.16})O₂; Cobalt free cathodes; Li₂MnO₃; Solid solution*

1. Introduction

Lithium ion batteries (LIBs) had become predominant power sources for consumer electronic devices such as cellular phones, and laptops, due to their high energy density, long cycle life and light weight. The limitation of high rate capability restricted their use in electric vehicle applications, which are being considered to solve issues such as air pollution combined with the foreseen oil shortage. Although, LiCoO₂ has been commercialized as cathode in practical LIBs, numerous attempts had been made to find an appropriate alternative candidate, due to the high cost, toxicity and instability of cobalt at high potential windows greater than 4.3 V [1,2]. Layered materials, LiNiO₂ and LiMnO₂, had been extensively studied as an alternate for LiCoO₂, but they still possess various practical limitations, such as the difficulty to synthesize

phase pure materials, structural changes during cycling, thermal instability of LiNiO_2 and structural degradation of LiMnO_2 , leading to poor electrochemical performance [3-5]. Meanwhile, candidates such as LiMn_2O_4 and LiFePO_4 were also proposed and widely investigated. However, the former suffers from problems during operation at elevated temperature, because of possible Mn^{3+} dissolution and subsequent attack on the counter electrode which deteriorates the performance of the cell. The latter is affected by its inherent conductivity issue, which restricts the rate performance of the cell and also limits the operating voltage (3.4 V vs. Li) of the electrode [6]. Hence, the search is still on for high performance cathodes, preferably with a layered structure, which can exceed the combined advantages of the existing cathodes with superior electrochemical performance, low cost and eco-friendly material.

Ohzuku et al. [7,8] proposed new layered materials, $\text{LiNi}_{1/2}\text{Mn}_{1/2}\text{O}_2$ and $\text{LiNi}_{1/3}\text{Co}_{1/3}\text{Mn}_{1/3}\text{O}_2$, which were synthesized by the co-precipitation method. Dahn et al. [9] reported that $\text{Li}[\text{Ni}_x\text{Mn}_x\text{Co}_{1-2x}]\text{O}_2$ ($1/4 < x < 3/8$) materials delivered a discharge capacity of 160 mAh g^{-1} . Another Mn based material proposed as a possible alternate was Li_2MnO_3 , but it was found to be electrochemically inactive and the capacity obtained was mainly due to the exchange of H^+ ions [10, 11]. It was believed that the oxidation of Mn^{4+} to Mn^{5+} was not easier due to the tetravalent arrangement of Mn. At the same time, numerous studies have been devoted to the development of Mn based cathodes, due to its high specific capacity, low-cost and environmentally benign nature. To overcome the electrochemical inactivity of Li_2MnO_3 , a concept of preparing a one to one solid state solution with other layered materials has been adopted. Recently, many solid state solutions have been widely studied, such as $\text{Li}_2\text{MnO}_3\text{--LiMO}_2$ ($\text{M}=\text{Ni, Cr \& Co}$) [12-15], $\text{LiNiO}_2\text{--Li}_2\text{MnO}_3\text{--LiCoO}_2$ [16], $\text{Li}_2\text{MnO}_3\text{--LiNi}_{1-x}\text{Co}_x\text{O}_2$ [17] $\text{LiNi}_{0.5}\text{Mn}_{0.5}\text{O}_2\text{--Li}_2\text{MnO}_3\text{--LiCoO}_2$ [18], and $\text{Li}_2\text{MnO}_3\text{--LiCo}_{1/3}\text{Ni}_{1/3}\text{Mn}_{1/3}\text{O}_2$ [19]. Of late, layered materials containing lithium rich

compositions, $\text{Li}(\text{Li}_x\text{M}_{1-x})\text{O}_2$, where M is Mn, Ni or Co attracted the researchers. For instance, Zhang et al. [13] and Shin et al. [20] demonstrated that Li–Mn–Ni–O materials with excess lithium delivered a much higher capacity than that of the stoichiometric composition, $\text{LiMn}_{0.5}\text{Ni}_{0.5}\text{O}_2$, due to the structural stabilization formed between $\text{LiMn}_{0.5}\text{Ni}_{0.5}\text{O}_2$ and Li_2MnO_3 solid solutions. More recently, Ma et al. [21] also reported the preparation of an $\text{Li}_{1+z}(\text{Mn}_{0.4}\text{Ni}_{0.4}\text{Co}_{0.2})_{1-z}\text{O}_2$ solid solution without any secondary phase materials, unlike in the case of Li_2MnO_3 .

The above-mentioned Li_2MnO_3 based solid solutions comprising Co and Cr doped materials exhibited good electrochemical performances, however, their high cost and relatively high toxicity, when compared to native compound, have restricted their utilization in practical LIBs. Utilizing LiFeO_2 is thought to be the best way to reduce the cost and the amount of toxic elements in such layered materials [22]. Recently, Tabuchi et al. [23,24] reported the development of iron based Li_2MnO_3 as a 4 V cathode material prepared using a combination of co-precipitation followed by hydrothermal reaction and, finally, the solid state method to synthesize these materials. The results suggested the possibility of using this new cathode material in the 4 V regions because of its unique $\text{Fe}^{4+/3+}$ redox couple at ~ 4 V. In spite of their apparently good structural properties, these materials exhibited poor cycle performance, due to their preparation method which involved three complicated steps and may affect the electrochemical performance. In addition, an oxidizer is used during hydrothermal step, which increases the production cost as well. It is generally believed that the utilization of such a redox couple is impractical in layered type oxides, for example, LiFeO_2 , Li_2MnO_3 - LiFeO_2 solid solutions, etc. Of late, the preparation of “cobalt free” layered oxides comprising solid solutions of the type mentioned above was attempted with other transition metal elements such as Mn and

Ni. This study sparked our motivation to develop Fe substituted layered cathode materials with improved electrochemical performance via simple synthesis routes such sol-gel or solid state methods, and to scale this procedure up further. In this connection, we prepared a layered manganese oxide solid solution of $\text{Li}_{1+x}(\text{Mn}_{0.4}\text{Fe}_{0.2}\text{Ni}_{0.4})_{1-x}\text{O}_2$ ($0 < x < 0.4$) materials with three end members, viz. Li_2MnO_3 , LiNiO_2 and LiFeO_2 using a simple adipic acid assisted sol-gel technique. Although, the optimization of x value and calcination temperature was not discussed in this paper, the materials prepared with $x=0.2$ ($\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$) at 700 °C, which exhibited the best electrochemical properties among the compositions prepared, were described in detail. It is worth mentioning that the presence of di-carboxyl groups (COOH) in adipic acid effectively suppresses the particles growth during synthesis procedure when compared to the other members of the group such as oxalic acid, malonic acid, succinic acid, suberic acid and sebacic acid [25]. Furthermore, the powders obtained by the adipic acid assisted technique exhibited excellent hexagonal ordering and, moreover, sub-micron sized particles with a narrow particle-size distribution were observed for the $\text{LiNi}_{0.8}\text{Co}_{0.2}\text{O}_2$ system. In line with this research, we adopted adipic acid as chelating agent and its influence towards the electrochemical properties of $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ are studied and described in detail.

2. Experimental

The sol-gel method was adopted to synthesize $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ (LMNFO) using adipic acid (AA) as a chelating agent, though it can also act as source for carbon. In the present study, various molar ratios of adipic acid to total metal ions were used, viz. 0, 0.25, 0.5, 0.75 and 1 M. In the synthetic process, an appropriate amount of $\text{Li}(\text{CH}_3\text{COO})_2 \cdot \text{H}_2\text{O}$ (Wako, Japan), $\text{Fe}(\text{CH}_3\text{COO})_2 \cdot \text{H}_2\text{O}$ (Aldrich), $\text{Ni}(\text{CH}_3\text{COO})_2 \cdot 4\text{H}_2\text{O}$ (Aldrich), and $\text{Mn}(\text{CH}_3\text{COO})_2 \cdot 4\text{H}_2\text{O}$

(Aldrich) were dissolved in distilled water, and then added into a continuously stirred aqueous solution containing $C_6H_{10}O_4$ (Sigma Aldrich). The pH of the solution was maintained as neutral by incorporating ammonium hydroxide (NH_4OH) solution. The resultant solution was evaporated at 80 °C until a transparent sol is obtained. After the evaporation of water, the sol turned into a viscous transparent gel. The resulting gel precursors were decomposed at 400 °C for 4 h in air to eliminate the organic moieties such as acetate and carboxylic groups. The decomposed powders were ground, pressed into pellets and fired at 700 °C for 10 h in an oxygen atmosphere to obtain nanocrystalline powders. The samples prepared with 0.25, 0.5, 0.75 and 1 M AA were named sample s A, B, C and D, respectively.

Phase analysis of all the synthesized powders was carried out by X-ray diffraction using $Cu K\alpha$ radiation (XRD, Rint 1000 Regaku, Japan) with the scan speed of 2°min^{-1} between 10 and 80 ° at an applied potential of 40 kV and current of 30 mA. The surface morphology of the powders was observed by scanning electron microscopy (SEM, S-4700 microscope, Hitachi, Japan) and transmission electron microscopy (TEM, TecnaiF20, Philips, Holland). Cyclic voltammetry (CV) and electrochemical impedance spectroscopy (EIS) studies were performed using electrochemical analyzer (SP-150, Bio-Logic, France). Micromeritics ASAP 2010 surface analyzer (Micromeritics, USA) was used to calculate Brunauer-Emmett-Teller (BET) surface area of the prepared powders. The carbon content in the samples was determined by elemental analysis (Elementar Analysensysteme GmbH, Germany). Galvanostatic charge/discharge tests were performed using CR 2032 coin cells. The composite cathodes were prepared by pressing accurately weighed 20 mg of prepared material, 3 mg of Ketzen black and 3 mg of Teflonized acetylene black (TAB) mixture on 200 mm^2 stainless steel mesh and subsequently dried at 160 °C in a vacuum oven for 4 h. The test cell was fabricated in an argon filled glove box by pressing

composite cathode and lithium metal anode separated by a porous polypropylene separator (Celgard 3401). 1 M LiPF₆ in 1:1 EC/DMC (Techno Semichem. Co. Ltd, Korea) was used as the electrolyte. The test cells were cycled at a constant current density of 0.1 mA cm⁻² between 2 and 4.5 V at room temperature.

3. Results and Discussion

Fig. 1 shows the XRD patterns of LMNFO samples prepared with different molar ratios of AA synthesized at 700 °C. The well defined narrow reflections indicate the good crystalline nature of the synthesized powders with various ratios of AA. Moreover, the intensity of the diffraction peaks gradually increased with increasing amount of AA, revealing the improvement in the crystalline nature of the sample with a high AA content. The peaks are indexed based on hexagonal α -NaFeO₂ structure with a space group of $R\bar{3}m$, which indicates that the layer of lithium is substituted with a layer containing lithium, manganese, nickel and iron atoms [23]. In addition, the two super lattice peaks observed between 20 and 30°, caused by the short range ordering of Li, Ni, Mn and Fe in 3a sites, indicate the existence of a layered structure with Li₂MnO₃ character [16]. However, these super lattice peaks were gradually suppressed as the adipic acid ratio increased. Further, the suppression of these peaks with increasing AA content also infers that the undetectable monoclinic phase of Li₂MnO₃ turns into hexagonal layered rock-salt phase, which is in good agreement with the previous reports by Tabuchi et al. [23,24]. This is expected, because the incorporation of Fe³⁺ leads to the formation of the above solid solution, co-existing between α -LiFeO₂-Li₂MnO₃ with the same layered structure. The lattice parameter values are calculated and given in Table 1. The integrated ratio of I₍₀₀₃₎ / I₍₁₀₄₎ peaks has been proposed to be a critical indication of partial interchange of occupancy of the Li and transition

metal ions among the sites, or so called cation mixing [26]. The ratio of $I_{(003)}/I_{(104)}$ increases with increasing AA ratio from 0.75 to 0.94. This indicates that the cation mixing between Ni^{2+} and Li^{+} is decreased, and the ratio observed for sample D was in good agreement with the reported values, which means that good electrochemical performance can be expected [7,8]. Generally, the c/a ratio is used to determine the hexagonality of a layered material and, when it is more than 4.9, the material possess layered characteristics [16-18]. In our study, the c/a ratio determined for all of the samples is more than 4.9, which shows that they have well defined layered structural properties which would facilitate the diffusion of one dimensional Li^{+} ion transport in the matrix.

The XRD pattern of sample C was further subjected to Rietveld refinement with respect to the $\text{Li}_{1.2}\text{Ni}_{0.2}\text{Mn}_{0.6}\text{O}_2$ phase and the results are presented in Fig. 2. The refinement was conducted based on the assumption that the Li-ions occupy $3a$ sites, Ni, Mn and Fe are located in the $3b$ sites, and O is located in the $6c$ sites. Consequently, the analysis was carried out to find the cation mixing of nickel in lithium sites, because the radius of Ni^{2+} (0.69 Å) is close to that of Li^{+} (0.76 Å). As can be seen from Fig. 2, the presence of superstructure peaks in the region of 20–33 ° resulted from the ordering of lithium and manganese in the transition metal layers. From the Rietveld analysis, the cation distribution of these layers can be written as $(\text{Li}_{0.925}\text{Ni}_{0.075})_{3a}[\text{M}_{0.726}\text{Li}_{0.275}]_{3b}\text{O}_2$. This clearly indicates that, for the composition of $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$, only 0.075 moles of the formula unit of Ni^{2+} were incorporated into the Li layer, which means that a low level of cation mixing occurred.

The SEM images of the pristine, A, B, C and D samples calcined at 700 °C are shown in Fig. 3. All of the samples exhibited a cluster of weakly aggregated particulates in the scanned area. There is a greater deal of agglomeration of non-uniformed particles observed on the surface of

pristine sample. It can be clearly seen from the SEM images that as the content of AA increased, the tendency toward aggregation decreased. However, primary particles with a size of about 100-120 nm are observed for samples A (Fig. 3(b)) and B (Fig. 3(c)). It is well known that electrochemical lithium insertion/extraction is much easier in small size particles due to the reduction of diffusion pathways for Li^+ ions, which also enable faster electronic transport through their size effect. It was reported that polycrystalline materials with a grain size of up to 100 nm could exhibit enhanced diffusivity and a higher thermal coefficient than conventional materials [27,28]. The materials with a higher AA content exhibit a slightly larger particle size with a more uniform size distribution. As the content of AA increased from 0.25 to 1 M, the size of the primary particles increased to about 200 nm. Furthermore, sample D (Fig. 3(e)) consisted of uniform large particles and a very small proportion of aggregation. The sample with a higher AA content exhibited somewhat suppressed particle agglomeration but the average particle size is larger than that of the other AA treated samples, which is essential for good higher rate performance. Although the carbon coating cannot be clearly detected in Fig. 3, very small particles around 10-20 nm size are bound on the surface of LMNFO powders, especially at higher AA contents, and can be considered to be small carbon particles.

In order to confirm the presence of carbon, a TEM analysis was carried out for sample D (700 °C) and the results are presented in Fig. 4. It can be clearly seen from Fig. 4(a) and (b) that sample D has a uniform particle size distribution and small size residual carbon particles are also available, which is due to the carbonization of AA during the calcination process. The formation of nanosized materials may be ascribed to the sol-gel preparation procedure, which resulted in the molecular level mixing of the starting materials and enabled a high degree of homogeneity to be obtained with uniform particles having a high surface area. Fig. 4(c) - 4(f) shows the

distribution of metal ions in sample D containing carbon and the corresponding mapping area is shown in Fig. 4(b). The mapping of Mn (Fig. 4(c)) showed a similar intensity distribution to Ni and Fe, indicating that all of the elements are homogeneously mixed in the sample. Fig. 4(f) clearly demonstrates the presence of carbon with an even distribution on the surface of the powders. Sample D with a ratio of AA to metal ions of 1M, which showed the best performance among the synthesized powders, was found to contain only 1.6 wt% of carbon after the synthesis by CHN analysis. As its content is low, the carbon is not uniformly distributed and cannot cover the entire surface of the particles, as confirmed in the HR-TEM images in Fig. 4(g) [28].

A BET surface area analysis was also carried out to confirm the effect of AA on the surface area of the LMNFO powders. The analysis of the surface area is an important tool for the interpretation of the electrochemical performance, particularly in the case of Li_2MnO_3 -based electrode materials because samples with a large surface area exhibit better electrochemical behavior [23,29]. The specific surface area of the pristine sample and samples A, B, C and D are about 4.44, 4.73, 4.87, 6.94 and 7.28 m^2g^{-1} , respectively. From the above measurements, it is obvious that the surface area increases with increasing amount of AA, which indirectly confirms that the chelating agent, adipic acid, played a vital role in hindering the aggregation of particulates during calcination, increasing the surface area of the synthesized powders. The reason for the increase in the surface area and crystallinity of the material with increasing quantity of AA can be described as follows: it has been reported that AA not only acts as a chelating agent, but also provides the heat of combustion required for the preparation of highly crystalline powders [30-32]. Therefore, the high homogeneity of the precursor and a large amount of combustion heat is generated when a large amount of AA is used for the synthesis. The formation of a phase pure and lighter material, due to the large volume of voids formed by

the evolution of CO and CO₂ gases during the thermal decomposition of AA. The swelling of the materials was observed even though the gel precursors with AA were calcined at a fixed temperature. In addition, their highly crystalline nature and high surface area lead to the complete participation (in other words, highly exposed contact area towards the electrolyte) of the materials during an electrochemical reaction.

The galvanostatic charge-discharge profile of the pristine material and samples A, B, C, and D are presented in Fig. 5. The cycling tests were carried out between 2 and 4.5 V vs. Li/Li⁺ at a constant current density of 0.1 mAcm⁻². All of the synthesized samples exhibited smooth and monotonous curves, which is the typical behavior of layered materials and confirms the single phase reaction. During charging, the cell voltage started from open circuit voltage, rapidly increased to 3.7 V and then remained constant at 3.8 V where the oxidation of Ni²⁺ to Ni⁴⁺ occurred [33]. Since Mn⁴⁺ cannot be further oxidized to Mn⁵⁺, it is believed that it did not take part in the electrochemical reaction [2]. Similar to Mn⁴⁺, Fe³⁺ is also not oxidized in to Fe⁴⁺ and is subsequently reduced during discharge, as confirmed by the absence of an Fe³⁺/Fe⁴⁺ redox plateau at ~4V by partial occupation of the transition layers of the α -NaFeO₂ type structure by the Fe ions [34,2]. In this solid solution consisting Li_{1.2}(Mn_{0.32}Ni_{0.32}Fe_{0.16})O₂, both Mn and Fe simply act as the inactive matrix elements, which stabilize the crystal structure during the Ni^{4+/2+} redox couple. Moreover, a small amount of Fe³⁺ ions (3b cation) on the Li layer could act as an activator, prohibiting faster Li⁺ diffusion and resulting in slower Li₂O extraction from the layered structure (α -NaFeO₂) during the charging process, thus explaining the large discharge capacity value [34,35]. It can be seen from Fig. 5, that a large irreversible capacity loss (ICL) is observed for all of the samples tested. This may be ascribed to the oxidation of pre-existing Ni²⁺ ions which occupy Li⁺ layer and lead to the formation of electrochemically inactive region in the

electrode in the first cycle. From the 2nd cycle onwards, the columbic efficiency of the cell is over 99 % and this is noticed for all of the samples tested. As shown in Fig. 5, the discharge capacity of the pristine material is as low as 113 mAh g⁻¹ when compared with other materials, which may be due to its higher charge transfer resistance. In other words, the materials prepared with different AA ratios delivered almost the same discharge capacity value of about 160 mAhg⁻¹ with different cycling behavior. This improved capacity resulted from the addition of AA during the synthesis, which facilitated the formation of particles with a preferred surface morphology and enhanced the contact between the active materials, thereby improving the electrochemical performance. Nevertheless, the suppression of the elimination of oxides and lithium ion vacancies at the end of first charge cycle is effectively circumvented by the presence of carbon, which resulted in lower ICL and subsequently increased the columbic efficiency after first cycle [36].

Fig. 6 presents the cycling performance of the Li/LMNFO cells with different proportions of AA at a current density of 0.1 mA cm⁻² at room temperature. The Li/LMNFO with AA concentrations of 0, 0.25, 0.5, 0.75 and 1 M delivered initial discharge capacities of 113, 167, 165, 160 and 160mAh g⁻¹, respectively. The cycling performance tests of the Li/LMNFO cells were conducted for up to 25 cycles at room temperature. The discharge capacity of all of the samples slowly decreased with increasing cycling number, which is probably due to small structural distortion and/or side reactions during charge-discharge process. As far as the pristine material is concerned, the discharge capacity started to fade severely from 113 to 68 mAh g⁻¹ at the end of 25th cycle, which corresponds to a capacity retention of 60 %. On the other hand, the adipic acid mediated Li_{1.2}(Mn_{0.32}Ni_{0.32}Fe_{0.16})O₂ powder showed better cycleability than the pristine sample. Discharge capacities of 109, 134, 132 and 148 mAh g⁻¹ were observed for the

cells with concentrations of AA of 0.25, 0.5, 0.75 and 1 M at the 25th cycle. The capacity retentions of samples A, B, C and D were found to be 65, 81, 82 and 92% after 25th cycle, respectively. Among the adipic acid assisted powders, 1 M AA comprising $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ (sample D) exhibited excellent capacity retention. These improved properties result from the high crystallinity of the particles with a relatively larger surface area, which was confirmed by the SEM and BET analyses. The high surface area of such evenly distributed nanocrystalline materials improved the electrochemical performance by shortening the diffusion length of the lithium ions. The suppressed development of SEI layer gives rise to significantly improved cycling performance, which indicates the effect of AA on cycleability even with a small applied carbon content. The conductive carbon on the surface not only prevents the direct contact between the active cathode material and the electrolyte, but also provides pathways for electron transfer.

The rate capability is one of the important electrochemical properties of a lithium secondary battery, which is required for high power storage applications. In order to demonstrate the rate capability of the pristine and AA containing materials, the cells were cycled with various current rates from 0.03 to 13C between 2 and 4.5 V and the results are presented in Fig. 7. As mentioned earlier, some fading of the discharge capacity profile is observed when the cells are cycled at lower current rates (0.03C). In Fig. 7, it can be seen that the discharge capacity slowly decreased with increasing current density due to the polarization of electrodes at high current. This increase in polarization, while increasing current rate is believed to be due to the reduction in time required for Li^+ ion intercalation into the crystal lattice and the fact that only the surface of the active material participates in the reaction. It can be seen from Fig. 7, that the material prepared with 1 M AA exhibited excellent electrochemical behavior with improved cycleability even at

high current rates, whereas the pristine sample showed poor rate performance. This data reveals that the rate capability increased with increasing AA ratio, due to the improved electrical conductivity arising from the phase purity, uniformly distributed highly crystalline nanoparticles and the presence of carbon.

Cyclic voltammetry was conducted for the 1M AA containing $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ (sample D) to evaluate the redox potential of the transition metal ions during cycling. Fig. 8 represents the family of cyclic voltammetric traces (1, 2, 6 and 10th cycles) of sample D between 2 and 4.5 V at 0.5 mV s^{-1} , in which lithium acts as the counter and reference electrodes. It can be seen that an anodic peak appear at around 4.2 V during charging and corresponding cathode peak is seen at 3.6 V in the discharge process. According to earlier report [12], the anodic peak around 4.2 V corresponds to the oxidation of Ni^{2+} to Ni^{4+} . Furthermore, the absence of peaks around 3 V indicated that the $\text{Mn}^{4+}/\text{Mn}^{3+}$ redox reaction does not occur. This observation confirmed that Mn ions in our sample are electrochemically inactive and present in the 4+ state. Moreover, no transition of $\text{Fe}^{3+/4+}$ is observed throughout the region tested, which also confirms that the capacity obtained is due to the $\text{Ni}^{4+/2+}$ redox couple. As seen from the CV curves, the peak intensity became less sharp and shifted slightly towards the lower voltage region, whereas, in the galvanostatic cycling no shift in the plateaus was noticed. The fading of the peak intensity can be attributed to the cation mixing in the first cycle and thereafter, CV curves of 6th and 10th cycles almost overlap, which demonstrates the good reversibility of the Li^+ ion during insertion/extraction.

EIS studies were conducted to find the difference in electrochemical performance and polarization effect between the pristine and AA assisted materials. The impedance data was

recorded using a two electrode coin cell configuration and are presented in Fig. 9. The cells were initially charged and discharged at various current rates of $0.03C$ and $13C$, respectively, which continuously cycled for 5 cycles each and then investigated with EIS. The small variation of the electrolyte resistance (R_s) observed in Fig. 9 can be neglected [37]. The EIS plots were fitted according to the equivalent circuit given in the inset of Fig. 9 and the parameters are summarized in Table 2. All of the EIS spectra consist of three regions; a semi-circle in the low and medium frequency regions and an inclined line in the high frequency region. The low frequency semicircle is related to the Li^+ ion migration resistance (R_{sf}) through the solid-electrolyte interfacial (SEI) film; the intermediate frequency semicircle is attributed to the charge transfer resistance (R_{ct}) in the cathode–electrolyte interface and the line inclined at approximately 45° to the real axis corresponds to lithium ion diffusion into the bulk of the electrode material. The semicircles in the low frequency region are broad and depressed, due to the overlap of the two separate semicircles. Nyquist spectra comprising two semicircles and a linear part, similar to those in the present study, have been reported for layered cathode materials [38]. It was found that the AA assisted cathodes have a relatively lower R_{sf} compared with the pristine one. One possible reason for this is the change in the interfacial structure of the materials after they are modified with AA, which may further influence the properties of SEI layer, such as its thickness and density [39,40]. A much more obvious difference among all the samples lies in the second semicircle in the medium frequency region (R_{ct}). It can be seen from Table 2 that the diameter of semi-circle (i.e. R_{ct}) linearly decreased from $18.66\ \Omega$ to $3.2\ \Omega$ as the AA concentration increased. Among the samples, sample D delivered the lowest R_{ct} of about $3.2\ \Omega$, which might be caused by its relatively faster ionic migration. The decrease in R_{ct} with increasing ratio of AA to metal ions clearly demonstrated the importance of both the electronic conductivity and the Li^+ diffusion

ability for excellent electrochemical behavior of electrode materials during cycling at high current rates [41], which is well correlated with the charge/discharge cycling data.

Conclusion

Highly crystalline layered $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ cathode materials with and without the presence of a chelating agent, adipic acid, were successfully synthesized through the conventional sol-gel method. The XRD results revealed that the use of a high concentration of chelating agent improved the crystalline nature of the layered compound. The galvanostatic profiles demonstrated that the presence of adipic acid during the synthesis played a vital role in increasing the surface area of the material and enabled a discharge capacity of $\sim 160 \text{ mAh g}^{-1}$ to be delivered for all of the samples except for the bare compound. Among the samples, the material synthesized with 1 M adipic acid maintained 92 % of its initial discharge capacity even after 25 cycles. The rate capability of the above material was improved with those of the pristine material and samples with other concentrations of adipic acid (0.25, 0.5 and 0.75 M), due to the increase in conductivity. These experimental results suggest that adipic acid mediated $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ is an “eco-friendly” candidate for next generation cathode materials for lithium ion batteries.

Acknowledgements

This research work was financially supported by the Ministry of Knowledge Economy (MKE), Korea Institute for Advancement of Technology (KIAT) and Honam Leading Industry Office through the leading Industry Development for Economic Region.

References

- [1]. R.J. Brodd, K.R. Bullock, R.A. Leising, R.L. Middaugh, J.R. Miller, E. Takeuchi, *J. Electrochem. Soc.* 151 (2004) K1-K11
- [2]. B. Ammundsen, J. Paulsen, *Adv. Mater.* 13 (2001) 943-956
- [3]. G. Dutta, A. Manthiram, J.B. Goodenough, *J. Solid State Chem.* 96 (1992) 123-131
- [4]. Y. Gao, M.V. Yakovleva, W.B. Ebner, *Electrochem. Solid-State Lett.* 1 (1998) 117-119
- [5]. G. Vitins, K. West, *J. Electrochem. Soc.* 144 (1997) 2587-2592
- [6]. O.K. Park, Y. Cho, S. Lee, H.C. Yoo, H.K. Song, J. Cho, *Energy Environ. Sci.* **4** (2011) 1621-1633
- [7]. Y. Makimura, T. Ohzuku, *J. Power Sources* 119-121 (2003) 156-160
- [8]. T. Ohzuku, Y. Makimura, *Chem. Lett.* 30 (2001) 642-643
- [9]. S. Jouanneau, K.W. Eberman, L.J. Krause, J.R. Dahn, *J. Electrochem. Soc.* 150 (2003) A1637-A1642
- [10]. A.D. Robertson, P.G. Bruce, *Chem. Comm.* 23 (2002) 2790-2791
- [11]. A.D. Robertson, P.G. Bruce, *Chem. Mater.* 15 (2003) 1984-1992
- [12]. Z. Lu, J.R. Dahn, *J. Electrochem. Soc.* 149 (2002) A1454-A1459
- [13]. L. Zhang, H. Noguchi, M. Yoshio, *J. Power Sources* 110 (2002) 57-64
- [14]. Y. Sun, Y. Shiosaki, Y. Xia, H. Noguchi, *J. Power Sources* 159 (2006) 1353-1359
- [15]. M.M. Thackeray, S.H. Kang, C.S. Johnson, J.T. Vaughey, R. Benedek, S.A. Hackney, *J. Mater. Chem.* 17 (2007) 3112-3125
- [16]. Y. Sun, C. Ouyang, Z. Wang, X. Huang, L. Chen, *J. Electrochem. Soc.* 151 (2004) A504-A508

- [17]. P.S. Whitfield, S. Niketic, I.J. Davidson, *J. Power Sources* 146 (2005) 617-621
- [18]. L. Zhang, K. Takada, N. Ohta, K. Fukuda, T. Sasaki, *J. Power Sources* 146 (2005) 598-601
- [19]. N. Yabuuchi, K. Yoshii, S.T. Myung, I. Nakai, S. Komaba, *J. Am. Chem. Soc.* 133 (2011) 4404-4419
- [20]. L. Zhang, H. Noguchi, M. Yoshio, *J. Power Sources* 110 (2002) 57-64
- [21]. S.S. Shin, Y.K. Sun, K. Amine, *J. Power Sources* 112 (2002) 634-638
- [22]. M. Ma, N.A. Chernova, B.H. Toby, P. Zavalij, M.S. Whittingham, *J. Power Sources* 165 (2007) 517-534
- [23]. J. Li, J. Li, J. Luo, L. Wang, X. He, *Int. J. Electrochem. Sci.* 6 (2011) 1550-1561
- [24]. M. Tabuchi, Y. Nabeshima, K. Ado, M. Shikano, H. Kageyama, K. Tatsumi, *J. Power Sources* 174 (2007) 554-559
- [25]. M. Tabuchi, Y. Nabeshima, T. Takeuchi, H. Kageyama, K. Tatsumi, J. Akimoto, H. Shibuya, J. Imaizumi, *J. Power Sources* 196 (2011) 3611-3622
- [26]. G.T.K. Fey, J.G. Chen, Z.F. Wang, H.Z. Yang, T.P. Kumar, *Mater. Chem. Phys.* 87 (2004) 246-255
- [27]. T. Ohzuku, A. Ueda, M. Nagayama, *J. Electrochem. Soc.* 140 (1993) 1862-1870
- [28]. C. Suryanarayana, C.C. Koch, *Hyperfine Interact.* 130 (2000) 5-44
- [29]. R. Guo, P. Shi, X. Cheng, C. Du, *J. Alloys and Comp.* 473 (2009) 53-59
- [30]. D. Yu, K. Yanagida, K. Kato, H. Nakamura, *J. Electrochem. Soc.* 156 (2009) A417-A424
- [31]. Y.K. Sun, I.H. Oh, S.-A. Hong, *J. Mater. Sci.* 31 (1996) 3617-3621
- [32]. Y.K. Sun, I.-H. Oh, *J. Mater. Sci. Lett.* 16 (1997) 30-32

- [33]. Y.S. Lee, Y.K. Sun, K.S. Nahm, *Solid State Ionics* 109 (1998) 285-294
- [34]. Y. Koyama, I. Tanaka, H. Adachi, Y. Makimura, T. Ohzuku, *J. Power Sources* 119 (2003) 644-648
- [35]. M. Tabuchi, A. Nakashima, H. Shigemura, K. Ado, H. Kobayashi, H. Sakaebe, H. Kageyama, M. Kohzaki, A. Hirano, R. Kanno, *J. Electrochem. Soc.* 149 (2002) A509–A524
- [36]. B. Ammundsen, J. Paulsen, *Adv. Mater.* 13 (2001) 943-956
- [37]. C. Delmas, G. Prado, A. Rougier, E. Suard, L. Fournès, *Solid State Ionics* 135 (2000) 71-79
- [38]. Q.Y. Wang, J. Liu, A.V. Murugan, A. Manthiram, *J. Mater. Chem.* 19 (2009) 4965-4972
- [39]. J. Liu, A. Manthiram, *Chem. Mater.* 21 (2009) 1695-1707
- [40]. D. Aurbach, M.D. Levi, E. Levi and A. Schechter, *The Electrochem. Soc., Pennington* (1997), 124
- [41]. D. Aurbach, B. Markovsky, A. Rodkin, M. Cojocaru, E. Levi, H.J. Kim, *Electrochim. Acta* 47 (2002) 1899-1911
- [42]. G.T.K. Fey, P. Muralidharan, Y.D. Cho, *J. Power Sources* 160 (2006) 1294-1301
- [43]. H. Liu, C. Li, H. Zhang, L. Fu, Y. Wu, H. Wu, *J. Power Sources* 159 (2006) 717-720

Figure captions

Fig. 1. XRD pattern of pristine and adipic acid assisted $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ materials (a) pristine (b) 0.25 M AA (c) 0.5 M AA (d) 0.75 M AA (e) 1 M AA concentrations.

Fig. 2. Rietveld refinement pattern of 0.75 M adipic acid assisted $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$. The pattern were refined according to $\text{Li}[\text{Li}_{0.2}\text{Ni}_{0.2}\text{Mn}_{0.6}]\text{O}_2$ structure.

Fig. 3. SEM image of pristine and adipic acid assisted $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ materials (a) pristine (b) 0.25 M AA (c) 0.5 M AA (d) 0.75 M AA (e) 1 M AA concentrations.

Fig. 4. TEM image of (a and b) 1 M adipic acid assisted $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ particles (c) mapping of Mn (d) mapping of Ni (e) mapping of Fe (f) mapping of C and (g) coating layer.

Fig. 5. Charge-discharge profile of pristine $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ and materials prepared with different AA ratios cycled between 2.0 and 4.5 V at a current density of 0.1 mA cm^{-2} .

Fig. 6. Cycleability of pristine $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ and materials prepared with different AA ratios for 25 cycles in room temperature.

Fig. 7. Rate capability of pristine, 0.25 M AA, 0.5 M AA, 0.75 M AA and 1 M adipic acid assisted $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ samples at different current rates..

Fig. 8. Cyclic voltammetry of $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ prepared with 1 M AA recorded between 2 and 4.5 V at 0.5 mV s^{-1} .

Fig. 9. EIS spectra of pristine and adipic acid assisted $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$ after cycling at current rates of 0.03C and 13C, respectively. The Equivalent circuit is given in the inset.

Y.S. Lee *et al.* Fig. 1

Y.S. Lee *et al.* Fig. 2

Y.S. Lee *et al.* Fig. 3

Y.S. Lee *et al.* Fig. 4

Y.S. Lee *et al.* Fig. 5

Y.S. Lee *et al.* Fig. 6

Y.S. Lee *et al.* Fig. 7

Y.S. Lee *et al.* Fig. 8

Y.S. Lee *et al.* Fig. 9

Table 1: Lattice parameter values of $\text{Li}_{1.2}(\text{Mn}_{0.32}\text{Ni}_{0.32}\text{Fe}_{0.16})\text{O}_2$

Sample	a_h (nm)	c_h (nm)	c/a	I_{003}/I_{104}
Pristine	2.889	14.289	4.95	1.12
A	2.885	14.284	4.94	0.75
B	2.883	14.278	4.94	0.78
C	2.882	14.275	4.94	0.87
D	2.881	14.273	4.94	0.94

Table 2: EIS parameters of pristine and AA assisted materials obtained based on the equivalent circuit inserted in fig 9.

Sample	$R_s (\Omega)$	$R_{sf} (\Omega)$	$R_{ct} (\Omega)$
Pristine	5.40	6.53	18.66
A	4.67	2.23	4.36
B	3.83	1.68	3.79
C	4.95	1.52	3.44
D	4.74	0.88	3.20