Layered VOPO₄ as a cathode material for rechargeable Zinc-ion battery : effect of polypyrrole intercalation in the host and water concentration in the electrolyte

Verma, Vivek; Kumar, Sonal; Manalastas, William, Jr.; Zhao, Jin; Chua, Rodney; Meng, Shize; Kidkhunthod, Pinit; Srinivasan, Madhavi

2019

Verma, V., Kumar, S., Manalastas, W. J., Zhao, J., Chua, R., Meng, S., Kidkhunthod, P. & Srinivasan, M. (2019). Layered VOPO₄ as a cathode material for rechargeable Zinc-ion battery : effect of polypyrrole intercalation in the host and water concentration in the electrolyte. ACS Applied Energy Materials, 2(12), 8667-8674.
<https://dx.doi.org/10.1021/acsaem.9b01632>

<https://hdl.handle.net/10356/147547>

<https://doi.org/10.1021/acsaem.9b01632>

This document is the Accepted Manuscript version of a Published Work that appeared in final form in ACS Applied Energy Materials, copyright © American Chemical Society after peer review and technical editing by the publisher. To access the final edited and published work see <https://doi.org/10.1021/acsaem.9b01632>

Downloaded on 26 Apr 2023 22:07:02 SGT

Layered VOPO₄ as a Cathode Material for Rechargeable Zinc-Ion Battery: Effect of Polypyrrole Intercalation in the Host and Water Concentration in the Electrolyte

Vivek Verma,[†] Sonal Kumar,[†] William Manalastas Jr.,^{*,†} Jin Zhao,[†] Rodney Chua,[†] Shize Meng,[†] Pinit Kidkhunthod,[‡] and Madhavi Srinivasan^{*,†}

[†]*School of Materials Science and Engineering, Nanyang Technological University, 50 Nanyang Ave, 639798, Singapore*

[‡]*Synchrotron Light Research Institute (SLRI), Nakhon Ratchasima, 30000, Thailand*

Received October 5, 2019; E-mail: wmanalastas@ntu.edu.sg; madhavi@ntu.edu.sg

Abstract: Rechargeable zinc-ion batteries (RZIB) present an interesting alternative to rechargeable Li-ion batteries. Among the active materials, layered vanadium-based oxides show a poor cell voltage but modifying this structure by attaching a phosphate group to the vanadium redox center can drastically enhance the cathode voltage. With this layered VOPO₄ material, we demonstrate that pre-intercalating polypyrrole between crystallographic layers and using electrolyte with controlled water amounts are two absolutely essential conditions for easy and reversible Zn²⁺ (de)intercalation, thus vastly improving battery outputs and long-term capacity retention. We establish that the rational design of open-layered structures hinges imperatively on factors like host structural integrity and electrode-electrolyte compatibility in delivering the performance of multivalent-ion batteries.

Keywords: Rechargeable zinc batteries, intercalation cathode, open layered structure, polypyrrole pre-intercalation, VOPO₄

Introduction

Although rechargeable Li-ion batteries are widely popular in the field of portable electronics, their application in the large-scale grid energy technologies are less attractive when considering cost, safety and supply risk of Li metal.^{1–3} In this regard, rechargeable batteries using other metal-ions are receiving an increased attention.^{3–6} Among the various alternative metals, zinc metal can be a good choice as an anode when compared to lithium because of: 1) higher volumetric capacities,⁷ 2) lower cost and 3) possibility of transferring multiple charge per ion, when compared to lithium.^{3,4}

Given the advantages of using zinc metal as an anode, developing a good cathode material for this anode is of immense interest. However, most studies suggest that intercalating multivalent-ions (including Zn²⁺) into the host structure is difficult when compared to Li⁺ because of the high charge-to-size ratio of the multivalent-ions.^{8–10} The higher charge-to-size ratio of a multivalent-ion strongly polarizes the host structure and limits its diffusivity inside the host structure.¹⁰ Further, multivalent cations can also induce a heavy structural distortion causing the host structure to collapse as demonstrated by Park et al.¹¹ Hence, crystal structures with open frameworks which can both minimize the high electrostatic repulsion and buffer the steric destabilization are promising.^{10,12–15}

Various studies have explored layered vanadium-based oxides as a RZIB cathode,^{3,16} and these materials demonstrate successful zinc-cation storage via intercalation mecha-

nism.^{12,17–19} These materials possess a high interlayer spacing created by various pre-intercalated cations or water molecules.²⁰ The high interlayer spacing can minimize the electrostatic repulsion between host material and the intercalating cation, thus easing the multivalent-cation intercalation.^{12,21} In addition, the intercalated water molecules /cations act as “pillars”; preserving the structural integrity of the host structure during (de)intercalation.^{22,23} However, the intercalation voltage of this class of oxide materials is low, roughly at 0.7 V vs. Zn²⁺/Zn.^{3,16}

A phosphate group linked to the vanadium-ion center can enhance the cation intercalation voltage as compared to the vanadium oxides via an inductive effect.²⁴ VOPO₄·2H₂O is a material that exists as a layered phase with a high interlayer spacing.²⁵ The high interlayer spacing, created by the pre-intercalated water molecules between the VOPO₄ layers, can minimize the electrostatic repulsion between the intercalating Zn²⁺ and the host structure; hence, can make the Zn²⁺ migration inside the host easy. However, we observed a rapid capacity fade and a structural change in the host during repeated zinc (de)intercalation. On pre-intercalating polypyrrole between the VOPO₄ layers, we observe that the cycling stability improves and therefore, we study polypyrrole-intercalated VOPO₄ (PPy-VOPO₄) as a cathode host material for RZIB. Moreover, for using the Zn(CF₃SO₃)₂/acetonitrile electrolyte with the VOPO₄-based cathode for RZIB, Wang et al. have showed the benefits of adding low-amounts of water to the electrolyte for improving the battery performance.²⁶ However, the problems associated with adding high-amounts of water were not elaborated on. We find that there is a problem of severe cathode-material dissolution which in turn affects the cycling stability. By similar vein, we demonstrate that an optimum water amount in the electrolyte is needed to maximize the battery capacity and the cycling stability for this cathode material. With the optimized electrolyte, the battery could demonstrate a high average voltage of 1.1 V vs. Zn²⁺/Zn, along with a maximum capacity of 86 mAh g⁻¹ and cycling stability of 350 cycles. Finally, using a combination of XRD and XPS techniques, we elucidate the zinc storage mechanism for this system.

Results and discussion

The X-ray diffractogram for the synthesized VOPO₄·2H₂O (Figure 1a), matches well with the database (JCPDS 04-014-1253).²⁷ Tachez et al.²⁸ have described the crystal structure (Figure 1b) as a structure consisting of VOPO₄ layers wherein each vanadium-ion center is bonded to six O atoms

Figure 1. (a) XRD patterns for synthesized $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ and PPy-VOPO_4 (b) Crystal structure of $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ (c) schematic for PPy-VOPO_4 showing the polypyrrole units intercalated between the VOPO_4 layers (d) layered stacks of PPy-VOPO_4 in SEM image (e) V $2p_{3/2}$ XPS spectra for $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ (bottom) and PPy-VOPO_4 (top)

with slightly different bond lengths and thus forms a distorted VO_6 octahedra (shown as orange octahedra). Four of these V-O bonds, where O atoms are shared to phosphate tetrahedra (purple tetrahedra), lie in the equatorial or a-b plane. One of the axial bonds is formed with an O atom which is slightly shorter than the equatorial V-O bond length, while the other axial V-O bond is elongated as two H atoms are attached to this O atom, similar to a water molecule (red sphere bonded to two white spheres). Notably, this structure gives rise to extended hydrogen-bonding networks allowing for discrete water molecules to reside within the VOPO_4 layers (where O atom is represented in green). These H_2O molecules are weakly bonded and can be easily removed.²⁵

The XRD pattern for the synthesized PPy-VOPO_4 (Figure 1a) matches well with previous reports.^{29,30} While all the peak positions for the ' l '-dependent hkl planes shift to higher 2θ angles after polypyrrole intercalation, the ' l '-independent (020) plane does not shift, indicating that only the unit cell dimension along the direction perpendicular to the VOPO_4 layers (c -axis) contracts. This observation is consistent with the argument made by Benes et al. that most of the intercalating species leave the VOPO_4 layers unaltered and only change the VOPO_4 interlayer separation (Figure 1c).²⁵ The reduction in the ' c ' unit cell length, leads to a decrease in the spacing between the VOPO_4 layers from 7.43 Å (in $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$) to 6.72 Å, calculated using (001) planes. Although intercalating most organic species between the VOPO_4 layers increases the VOPO_4 layer spacing, a few species including polypyrrole have been shown to decrease the interlayer separation after intercalation (Table S1).²⁹ De et al. have suggested that the reduction in the interplanar spacing could be due to the replacement of weakly bonded water molecules with polypyrrole units.³⁰ The overlap of the

(020) and (012) planes, which has also been observed previously with polypyrrole intercalation into VOPO_4 , can be ascribed to the fact that all the XRD peaks are much broader after intercalating polypyrrole as the crystallite size reduces after polypyrrole intercalation.³⁰

SEM micrograph for PPy-VOPO_4 (Figure 1d) indicates that the material consists of an irregular stack of sheets, unlike the orderly-stacked layers of $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ (Figure S1). This observation is consistent with the XRD results, wherein the broadening of (001) type peaks after polypyrrole intercalation indicate that the crystallite size along the axis normal to the VOPO_4 layers is reduced.³¹ Polypyrrole intercalation changes the color of powder from bright yellow to dark green (Figure S2).³² The presence of polypyrrole in the host was confirmed by FTIR (Figure S3), and the chemical composition of the final material as determined by using TGA and CHN analyzer is $(\text{PPy})_{0.4}\text{VOPO}_4 \cdot 1.17\text{H}_2\text{O}$ (Figure S4 and Table S2).

The chemical interaction between the intercalated polypyrrole and the VOPO_4 layers was further illustrated in the XPS results (Figure 1e). Before the polypyrrole intercalation, V in the material shows mostly +5 oxidation state at an energy of 518.7 eV along with a small amount in +4 oxidation state at 516.8 eV.^{33,34} However, after the polypyrrole intercalation: 1) the relative ratio of $\text{V}^{4+}/\text{V}^{5+}$ increases, indicating that the vanadium-ions exist in a mixed oxidation state of $\text{V}^{4+/5+}$. The existence of mixed oxidation state of V was also confirmed by V K-edge XANES spectra which showed that the average oxidation state of V lies between +4 and +5 (Figure S5). 2) Both the peaks shift to lower binding energies with the host intercalation by polypyrrole, a phenomenon which has also been observed during layered VOPO_4 host intercalation with other carbon materials.³⁴

The mixed valency of the V-ion center enhances the elec-

Figure 2. (a) EIS spectra for RZIB using VOPO₄·2H₂O or PPy-VOPO₄ as a cathode material, (b) comparison of the cycling stabilities for VOPO₄·2H₂O and PPy-VOPO₄ at a current rate of 30 mA g⁻¹ in 1 M Zn(CF₃SO₃)₂/acetonitrile electrolyte with 10 vol% water. (c) charge-discharge curve of second cycles and (d) EIS spectra for PPy-VOPO₄ RZIB in Zn(CF₃SO₃)₂/acetonitrile electrolyte with different water concentrations

tronic conductivity of the PPy-VOPO₄ host structure when compared to VOPO₄·2H₂O (Figure S6),^{30,35} because the electron charge cloud can be delocalized between adjacent V-ions when present in the mixed oxidation state.^{36,37} Intercalant polypyrrole also improves the electronic conductivity as it is partially present in its oxidized state when intercalated between VOPO₄ layers.^{29,30} Due to the improved electronic conductivity, the semicircle in the EIS spectra, which Kundu et al. ascribed to the charge-transfer resistance at the electrode-electrolyte interface,²² is smaller for PPy-VOPO₄ as compared to VOPO₄·2H₂O (Figure 2a and Figure S7).

Additionally, polypyrrole intercalation between the VOPO₄ layers benefits the structural integrity as it acts as a better pillaring unit when compared to water. For VOPO₄·2H₂O, a drastic capacity fading is observed during charge/discharge (Figure 2b and Figure S8). Ex-situ XRD (Figure S8c) for the cycled electrodes revealed that the interplanar spacing between the VOPO₄ layers reduce over repeated cycling, which can be ascribed to the loss of the hydrogen-bonded water molecules from the host structure.^{25,31} On the other hand, the capacity retention showed a drastic improvement in the case of PPy-VOPO₄ (from 25% to 90% in 30 cycles, Figure 2b and Figure S9). A similar improvement in the capacity retention was also observed when Wei. et al. preintercalated some charged cations between the layered structure of vanadium oxide.³⁸ Wei et al.

explained that the intercalating species holds the layered structure intact and reduces the structural distortion in the host structure during repeated (de)intercalation.

While our aim was to use a water-solvent based electrolyte for testing the PPy-VOPO₄ as the RZIB cathode material, a purely aqueous electrolyte could not be used as the PPy-VOPO₄ material slowly dissolves in water (Figure S10). Therefore, an acetonitrile solvent-based electrolyte was used. However, without any addition of water in the acetonitrile-based electrolyte, the battery could show hardly any capacity (Figure 2c). On adding small amounts of water to the electrolyte, we see an improvement in the capacities. A similar trend in the capacity improvement was also observed for the case of VOPO₄·2H₂O (Figure S11b).

To investigate why the addition of water in the electrolyte increases the capacity, we measured the EIS impedance spectrum for the battery system with varying water amounts (Figure 2d). We observed a reduction in the semicircle diameter on increasing the water concentration in the electrolyte. Kundu et al. had previously ascribed the semicircle to the charge-transfer impedance at the electrode-electrolyte interface, specifically to the energy penalties involved in desolvating Zn²⁺ from its solvation shell during Zn²⁺ charge transfer at either the cathode or the anode.²² Studies have found that the energy penalty to desolvate a multivalent-ion is much lower in water when compared to solvents like acetonitrile or propylene carbonate.^{22,39} This is also evident in

Figure 3. (a) Cyclic voltammetry for PPY-VOPO₄ RZIB in 1 M Zn(CF₃SO₃)₂/acetonitrile electrolyte with 10 vol% water, each pair of peaks is marked with a dashed line and assigned a numerical identifier (b) Battery cycling performance at 0.1 A g⁻¹, and (c) rate capability for PPY-VOPO₄ RZIB in 1 M Zn(CF₃SO₃)₂/acetonitrile electrolyte with 10 vol% water

the broadening of the CV peaks in the system without any added water in the electrolyte, and indicates sluggish kinetics (Figure S12).³⁵ Similar to the PPY-VOPO₄ system, we find the same trend of broadened CV peaks and reduced capacities in a water-free electrolyte for VOPO₄·2H₂O, again indicating poor kinetics (Figure S11).

While adding a small amount of water in the electrolyte is beneficial, increasing the water amounts beyond 10 vol% is detrimental. Adding a higher water amount leads to a marginal increase in the capacity, but deteriorates the capacity retention due to the PPY-VOPO₄ material dissolution in the water (Figure S13). Therefore, a trade-off exists between: 1) increasing the water content in the electrolyte to reduce zinc cation desolvation energies at the electrolyte-electrode interface, and 2) decreasing the electrolyte water content to limit the cathode material dissolution. Based on the capacities and cycling performance of the Zn/PPY-VOPO₄ system with different electrolytes, we find the electrolyte with 10 vol % water to be the optimum and investigate this system in detail.

The cyclic voltammogram (Figure 3a) for PPY-VOPO₄ in 10 vol % water electrolyte shows three pair of oxidation-reduction peaks. A similar CV profile with multiple peaks was also observed for VOPO₄-based cathode for Li, Mg and K systems,^{35,40,41} and the appearance of multiple peaks was attributed to the guest cation insertion in multiple stages.⁴⁰

We also note that the polypyrrole itself, when used as a cathode material, does not give any redox peak in CV (Figure S14a).

The Galvanostatic Charge Discharge (GCD) test at a high current rate of 0.1 A g⁻¹ shows a good cycling stability up to 350 cycles (Figure 3b). We report an unprecedented operational lifetime of 455 hours, surpassing the other reported works on VOPO₄ based ZIAB (Table S3); indicating that the cathode material dissolution over an extended period of time is much lower in our system. We note that the capacity values decrease initially in the first few cycles and then subsequently increase, similar to other reported works.^{23,42,43} The initial capacity drop has been attributed to the fact that during the discharging step, some Zn²⁺ ions intercalated in the host structure remain in the host structure as “dead Zn²⁺ sites” and can not be fully extracted during the charging step. The subsequent capacity rise has been ascribed to the gradual activation of the electrodes by other reports on RZIB.^{19,23} Notably, the capacity rise during the gradual activation regime was significant (≈ 50%) and lasted for nearly 200 cycles. This slow and long activation has also previously been observed in the Zn(CF₃SO₃)₂/acetonitrile electrolyte systems and was attributed to both sluggish kinetics in the electrolyte and a decrease in charge transfer impedance at the zinc anode via the progressive electrochemical polishing.²² The rate performance of the battery (Fig-

Figure 4. (a) Ex-situ XRD of PPy-VOPO $_4$ cathode showing shift in the $(00l)$ type planes at various stages of charging. XPS spectra for (b) Zn 2p peaks and (c) V 2p $_{3/2}$ during different states of charging. (d) Schematic depicting overall mechanism of zinc (de)intercalation into PPy-VOPO $_4$ host structure. Green spheres indicate Zn $^{2+}$ ions

ure 3c) demonstrates that the maximum discharge capacities achieved at a current rate of 25, 50, 100, 200, 500 mA/g are 86, 76, 65, 57 and 43 mAh/g, respectively. When the current is returned to the rate of 25mA/g, the battery could still achieve a discharge capacity of 78 mA/g, which is 90.6 % of the initial capacity. We also note that the polypyrrole shows a very limited capacity contribution (Figure S14b).

To gain insights into the host material intercalation behavior, we take ex-situ XRD of the cathode material in the

charged and discharged states of the fifth cycle (Figure 4a). We note that the X-ray diffraction patterns of the electrodes show a preferential orientation along the $(00l)$ type planes which can be ascribed to the PPy-VOPO $_4$ sheets orienting parallel to the electrode surface after electrode fabrication. As shown in Figure 4a, the shifts in (001) and (002) planes to higher 2θ angles in the discharged sample indicates an interlayer contraction as compared to the pristine sample. The interlayer layer spacing, as estimated using the (001) plane,

shrinks from 6.72 Å to 6.39 Å. This contraction in the interlayer spacing was also observed when Zn^{2+} is intercalated in other layered materials.^{12,17,23} The reason was ascribed to the electrostatic attraction between the guest Zn^{2+} cation and the host material layers; pulling the layers close to each other. When the cathode material is charged, the (001) and (002) planes again shifts to lower 2θ angles and closely resembles the diffractogram of the pristine sample. We note that even after a charging/discharging of 100 cycles, the host structure can retain its layered structure (Figure S15). The (001) interplanar spacing is 6.14 Å in the 100th discharged state which implies that the host structure is still electrochemically active and intercalates Zn-ions. This interplanar spacing is slightly lower than the 6.39 Å spacing observed for the fifth discharge cycle suggesting more zinc cations is stored in the host; and is consistent with an increase in the capacity observed in the later cycles after the initial electrochemical activation (Figure S13).

XPS further supports the zinc intercalation phenomena into the host structure. The Zn 2p XPS spectra in the pristine, charged and discharged states of the cathode material is shown in Figure 4b. While no zinc is present in the pristine electrode, Zn 2p_{3/2} (1022.07 eV) and Zn 2p_{1/2} (1045.27 eV) peaks appear in the discharged state, indicating the presence of Zn^{2+} species. Further, when the electrode is charged, the zinc peak intensities reduce, indicating that most of the zinc cations have been extracted out of the cathode material. However, we also note that some residual amount of Zn^{2+} species still remains inside the host structure after charging, even when the interlayer spacing is observed to be restored from the XRD results. This observation is consistent to the studies made by Kundu et al. where the authors observed that a small quantity of Zn^{2+} ions are trapped in the host vanadium oxide structure in the first cycle, and thereafter the slightly modified host structure shows a reversible Zn^{2+} (de)intercalation.²²

Vanadium XPS spectra provides further evidence of the zinc (de)intercalation inside the host (Figure 4c). The pristine electrode showed two peaks present in the sample at the binding energy values of 517.8 eV and 516.3 eV. When the electrode was discharged, both the peaks showed a red shift to the values of 517.1 and 516.0 respectively, indicating a reduction of the vanadium-ion centers during Zn^{2+} intercalation. When the electrode was charged, both the peaks are blue-shifted compared to the discharged electrode, to the final values of 517.5 eV and 516.3 eV, respectively. However, we note that the final peak position of the V^{5+} model peak in the charged state was slightly red-shifted compared to the pristine sample, indicating that not all the Vanadium-ion centers were oxidized back during the charging process. This can be ascribed to the fact that some Zn^{2+} -ions remain trapped in the host structure after charging; therefore, the vanadium-ion environment is modified in the charged electrode as compared to the pristine electrode.

Therefore, based on the structural characterization studies, we can deduce the following mechanism (Figure 4d). During discharging, the vanadium-ion centers reduce as zinc cations intercalate into the host structure. The intercalated zinc cations pull the VOPO_4 layers close to each other via the electrostatic attractive forces. During charging, the vanadium-ion centers oxidize again as the zinc cations are deintercalated from the host structure, and the VOPO_4 layers restore their original separation. However, few zinc cations remain trapped inside the host structure and thus

the vanadium-ion environment cannot fully revert to the original state.

Conclusions

In conclusion, we demonstrate that PPy- VOPO_4 can deliver a high average discharge voltage of 1.1 V vs. Zn^{2+}/Zn as a RZIB cathode. From the host material's perspective, a high interlayer spacing between the VOPO_4 layers made Zn^{2+} cation (de)intercalation feasible. However, only after the polypyrrole intercalation between the VOPO_4 layers, a high structural stability was achieved and the battery could perform reversibly up to 350 cycles. From the electrolyte perspective, we observed that contrary to the popular belief, an aqueous electrolyte might not always be better than a non-aqueous electrolyte as it might lead to problems like the electrode material dissolution. On the other hand, a non-aqueous electrolyte might not also be the best choice due to poor kinetics, and the choice of the electrolyte is subjective to the electrode material. These findings will help us in designing better cathode and electrolyte materials not only for zinc-ions but in general for all multivalent-ions.

Associated Content

Supporting Information The supporting information is available free of charge from ACS.

Experimental section, synthesis procedure and additional characterization details (TGA, CHN analysis, XANES, ex-situ XRD, and cyclic voltammetry)

Author Information

Corresponding authors

*email: wmanalastas@ntu.edu.sg

*email: madhavi@ntu.edu.sg

Notes

The authors declare no competing financial interest.

Acknowledgement This work was funded by the National Research Foundation of Singapore Investigatorship Award Number NRFI2017-08/NRF2016NRF-NRFI001-22. V.V would like to thank Fang Yanan and Sai S. H. Dintakurti for a fruitful discussion on XRD analysis; Teddy Salim for XPS analysis; Disha Gupta and Suchinda Satayaporn for XANES analysis; Tan Han Khiang for CHN analysis; and Yi Cai, Du Yuan and Hao Ren for help in designing electrochemical experiments. The authors thank Synchrotron Light Research Institute (BL5.2), Nakhon Ratchasima, Thailand for XANES measurements; and Facility for Analysis, Characterization, Testing and Simulation, Nanyang Technological University, Singapore, for use of their electron microscopy/X-ray facilities.

References

- (1) Wanger, T. C. The Lithium future-resources, recycling, and the environment. *Conservation Letters* **2011**, *4*, 202–206.
- (2) Helbig, C.; Bradshaw, A. M.; Wietschel, L.; Thorenz, A.; Tuma, A. Supply risks associated with lithium-ion battery materials. *Journal of Cleaner Production* **2018**, *172*, 274–286.
- (3) Verma, V.; Kumar, S.; Manalastas Jr, W.; Satish, R.; Srinivasan, M. Progress in Rechargeable Aqueous Zinc-and Aluminum-Ion Battery Electrodes: Challenges and Outlook. *Advanced Sustainable Systems* **2019**, *3*, 1800111.
- (4) Manalastas Jr, W.; Kumar, S.; Verma, V.; Zhang, L.; Yuan, D.; Srinivasan, M. Water in rechargeable multivalent-ion batteries: an electrochemical Pandora's box. *ChemSusChem* **2018**, *12*, 379–396.

- (5) Kumar, S.; Satish, R.; Verma, V.; Ren, H.; Kidkhunthod, P.; Manalastas, W.; Srinivasan, M. Investigating FeVO_4 as a cathode material for aqueous aluminum-ion battery. *Journal of Power Sources* **2019**, *426*, 151–161.
- (6) Chua, R.; Cai, Y.; Kou, Z. K.; Satish, R.; Ren, H.; Chan, J. J.; Zhang, L.; Morris, S. A.; Bai, J.; Srinivasan, M. 1.3 V superwide potential window sponsored by Na-Mn-O plates as cathodes towards aqueous rechargeable sodium-ion batteries. *Chemical Engineering Journal* **2019**, *370*, 742–748.
- (7) Haynes, W. M. *CRC handbook of chemistry and physics*; CRC press, 2014; pp 8–20.
- (8) Levi, E.; Gofer, Y.; Aubach, D. On the way to rechargeable Mg batteries: the challenge of new cathode materials. *Chemistry of Materials* **2009**, *22*, 860–868.
- (9) Whittingham, M. S.; Siu, C.; Ding, J. Can multielectron intercalation reactions be the basis of next generation batteries? *Accounts of chemical research* **2018**, *51*, 258–264.
- (10) Rong, Z.; Malik, R.; Canepa, P.; Sai Gautam, G.; Liu, M.; Jain, A.; Persson, K.; Ceder, G. Materials design rules for multivalent ion mobility in intercalation structures. *Chemistry of Materials* **2015**, *27*, 6016–6021.
- (11) Park, M. J.; Yaghoobnejad-Asl, H.; Therese, S.; Manthiram, A. Structural Impact of Zn-insertion into Monoclinic $\text{V}_2(\text{PO}_4)_3$: Implications for Zn-ion Batteries. *Journal of Materials Chemistry A* **2019**, *7*, 7159–7167.
- (12) Kundu, D.; Adams, B. D.; Duffort, V.; Vajargah, S. H.; Nazar, L. F. A high-capacity and long-life aqueous rechargeable zinc battery using a metal oxide intercalation cathode. *Nature Energy* **2016**, *1*, 16119.
- (13) Knight, J. C.; Therese, S.; Manthiram, A. Chemical extraction of Zn from ZnMn_2O_4 -based spinels. *Journal of Materials Chemistry A* **2015**, *3*, 21077–21082.
- (14) Li, H.; Yang, Q.; Mo, F.; Liang, G.; Liu, Z.; Tang, Z.; Ma, L.; Liu, J.; Shi, Z.; Zhi, C. MoS_2 nanosheets with expanded interlayer spacing for rechargeable aqueous Zn-ion batteries. *Energy Storage Materials* **2019**, *19*, 94–101.
- (15) Huang, J.; Wang, Z.; Hou, M.; Dong, X.; Liu, Y.; Wang, Y.; Xia, Y. Polyaniline-intercalated manganese dioxide nanolayers as a high-performance cathode material for an aqueous zinc-ion battery. *Nature Communications* **2018**, *9*, 2906.
- (16) Song, M.; Tan, H.; Chao, D.; Fan, H. J. Recent Advances in Zn-Ion Batteries. *Advanced Functional Materials* **2018**, *28*, 1802564.
- (17) Soundharrajan, V.; Sambandam, B.; Kim, S.; Alfuruqi, M. H.; Putro, D. Y.; Jo, J.; Kim, S.; Mathew, V.; Sun, Y.-K.; Kim, J. $\text{Na}_2\text{V}_6\text{O}_{16} \cdot 3\text{H}_2\text{O}$ barnsite nanorod: an open door to display a stable and high energy for aqueous rechargeable Zn-ion batteries as cathodes. *Nano letters* **2018**, *18*, 2402–2410.
- (18) Xia, C.; Guo, J.; Li, P.; Zhang, X.; Alshareef, H. N. Highly Stable Aqueous Zinc-Ion Storage Using a Layered Calcium Vanadium Oxide Bronze Cathode. *Angewandte Chemie International Edition* **2018**, *57*, 3943–3948.
- (19) Zhang, N.; Dong, Y.; Jia, M.; Bian, X.; Wang, Y.; Qiu, M.; Xu, J.; Liu, Y.; Jiao, L.; Cheng, F. Rechargeable Aqueous $\text{Zn-V}_2\text{O}_5$ Battery with High Energy Density and Long Cycle Life. *ACS Energy Letters* **2018**, *3*, 1366–1372.
- (20) Clites, M.; Pomerantseva, E. Bilayered vanadium oxides by chemical pre-intercalation of alkali and alkali-earth ions as battery electrodes. *Energy Storage Materials* **2018**, *11*, 30–37.
- (21) Novak, P.; Desilvestro, J. Electrochemical insertion of magnesium in metal oxides and sulfides from aprotic electrolytes. *Journal of The Electrochemical Society* **1993**, *140*, 140–144.
- (22) Kundu, D.; Vajargah, S. H.; Wan, L.; Adams, B.; Prendergast, D.; Nazar, L. F. Aqueous vs. nonaqueous Zn-ion batteries: consequences of the desolvation penalty at the interface. *Energy & Environmental Science* **2018**, *11*, 881–892.
- (23) Alfuruqi, M. H.; Mathew, V.; Song, J.; Kim, S.; Islam, S.; Pham, D. T.; Jo, J.; Kim, S.; Baboo, J. P.; Xiu, Z.; Lee, K.-S.; Sun, Y.-K.; Kim, J. Electrochemical Zinc Intercalation in Lithium Vanadium Oxide: A High-Capacity Zinc-Ion Battery Cathode. *Chemistry of Materials* **2017**, *29*, 1684–1694.
- (24) Sun, Y.; Wu, C.; Xie, Y. Sonochemical synthesis of nanostructured $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ /carbon nanotube composites with improved lithium ion battery performance. *Journal of Nanoparticle Research* **2010**, *12*, 417–427.
- (25) Beneš, L.; Melanova, K.; Svoboda, J.; Zima, V. Intercalation chemistry of layered vanadyl phosphate: a review. *Journal of Inclusion Phenomena and Macrocyclic Chemistry* **2012**, *73*, 33–53.
- (26) Wang, F.; Sun, W.; Shadiki, Z.; Hu, E.; Ji, X.; Gao, T.; Yang, X.-Q.; Xu, K.; Wang, C. How Water Accelerates Bivalent Ion Diffusion at the Electrolyte/Electrode Interface. *Angewandte Chemie International Edition* **2018**, *57*, 11978–11981.
- (27) Tietze, H. R. The crystal and molecular structure of oxovanadium (V) orthophosphate dihydrate, $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$. *Australian Journal of Chemistry* **1981**, *34*, 2035–2038.
- (28) Tachez, M.; Theobald, F.; Bernard, J.; Hewat, A. Intercalation Of Water Molecules in a layer structure of vanadyl phosphate. Crystal structure of vanadyl phosphate dihydrate. *Chemischer Informationsdienst* **1983**, *14*, 291–300.
- (29) De Stefanis, A.; Foglia, S.; Tomlinson, A. A. Assembly and polymerisation of some aromatic amines in $\alpha\text{-VOPO}_4 \cdot 2\text{H}_2\text{O}$. *Journal of Materials Chemistry* **1995**, *5*, 475–483.
- (30) De, S.; Dey, A.; De, S. Characterization and electrical properties of vanadyl phosphate-polypyrrole nanocomposites. *Journal of Physics D: Applied Physics* **2006**, *39*, 500.
- (31) Dupre, N.; Gaubicher, J.; Angenault, J.; Querton, M. Electrochemical study of intercalated vanadyl phosphate. *Journal of Solid State Electrochemistry* **2004**, *8*, 322–329.
- (32) Johnson, J. W.; Jacobson, A. J.; Brody, J. F.; Rich, S. M. Coordination intercalation reactions of the layered compounds vanadyl phosphate (VOPO_4) and vanadyl arsenate (VOAsO_4) with pyridine. *Inorganic Chemistry* **1982**, *21*, 3820–3825.
- (33) Igarashi, H.; Tsuji, K.; Okuhara, T.; Misono, M. Effects of consecutive oxidation on the production of maleic anhydride in butane oxidation over four kinds of well-characterized vanadyl pyrophosphates. *The Journal of Physical Chemistry* **1993**, *97*, 7065–7071.
- (34) Chen, N.; Zhou, J.; Zhu, G.; Kang, Q.; Ji, H.; Zhang, Y.; Wang, X.; Peng, L.; Guo, X.; Lu, C.; Chen, J.; Feng, X.; Hou, W. A high-performance asymmetric supercapacitor based on vanadyl phosphate/carbon nanocomposites and polypyrrole-derived carbon nanowires. *Nanoscale* **2018**, *10*, 3709–3719.
- (35) Dupré, N.; Gaubicher, J.; Le Mercier, T.; Wallez, G.; Angenault, J.; Querton, M. Positive electrode materials for lithium batteries based on VOPO_4 . *Solid State Ionics* **2001**, *140*, 209–221.
- (36) Park, J. G.; Aubrey, M. L.; Oktawiec, J.; Chakarawet, K.; Darago, L. E.; Grandjean, F.; Long, G. J.; Long, J. R. Charge Delocalization and Bulk Electronic Conductivity in the Mixed-Valence Metal–Organic Framework $\text{Fe}(\text{1, 2, 3-triazolate})_2(\text{BF}_4)$. *Journal of the American Chemical Society* **2018**, *140*, 8526–8534.
- (37) West, A. R. *Solid state chemistry and its applications*; John Wiley & Sons, 2014; pp 102–104.
- (38) Wei, Q.; Jiang, Z.; Tan, S.; Li, Q.; Huang, L.; Yan, M.; Zhou, L.; An, Q.; Mai, L. Lattice breathing inhibited layered vanadium oxide ultrathin nanobelts for enhanced sodium storage. *ACS applied materials & interfaces* **2015**, *7*, 18211–18217.
- (39) Mizuno, Y.; Okubo, M.; Hosono, E.; Kudo, T.; Zhou, H.; Oh-ishi, K. Suppressed activation energy for interfacial charge transfer of a Prussian blue analog thin film electrode with hydrated ions (Li^+ , Na^+ , and Mg^{2+}). *The Journal of Physical Chemistry C* **2013**, *117*, 10877–10882.
- (40) Hyoung, J.; Heo, J. W.; Chae, M. S.; Hong, S.-T. Electrochemical Exchange Reaction Mechanism and Role of Additive Water to Stabilize Structure of $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ as a Cathode Material for Potassium-Ion Batteries. *ChemSusChem* **2019**, *12*, 1069–1075.
- (41) Ji, X.; Chen, J.; Wang, F.; Sun, W.; Ruan, Y.; Miao, L.; Jiang, J.; Wang, C. Water-Activated VOPO_4 for Magnesium Ion Batteries. *Nano letters* **2018**, *18*, 6441–6448.
- (42) He, P.; Quan, Y.; Xu, X.; Yan, M.; Yang, W.; An, Q.; He, L.; Mai, L. High-Performance Aqueous Zinc-Ion Battery Based on Layered $\text{H}_2\text{V}_3\text{O}_8$ Nanowire Cathode. *Small* **2017**, *13*, 1702551.
- (43) He, P.; Zhang, G.; Liao, X.; Yan, M.; Xu, X.; An, Q.; Liu, J.; Mai, L. Sodium Ion Stabilized Vanadium Oxide Nanowire Cathode for High-Performance Zinc-Ion Batteries. *Advanced Energy Materials* **2018**, *8*, 1702463.

Keywords: Rechargeable zinc batteries, intercalation cathode, open layered structure, polypyrrole pre-intercalation, VOPO_4