Incineration bottom ash treatment through accelerated carbonation

Lin, Yvonne Wenlin

2016

Lin, Y. W. (2016). Incineration bottom ash treatment through accelerated carbonation.
Doctoral thesis, Nanyang Technological University, Singapore.

<https://hdl.handle.net/10356/65935>

<https://doi.org/10.32657/10356/65935>

**NANYANG
TECHNOLOGICAL
UNIVERSITY**

Incineration Bottom Ash Treatment through Accelerated Carbonation

Lin Wenlin Yvonne

SCHOOL OF CIVIL AND ENVIRONMENTAL ENGINEERING

2016

Incineration Bottom Ash Treatment through Accelerated Carbonation

Lin Wenlin Yvonne

SCHOOL OF CIVIL AND ENVIRONMENTAL ENGINEERING

A thesis submitted to the Nanyang Technological University
in partial fulfillment of the requirement for the degree of
Doctor of Philosophy

2016

ACKNOWLEDGEMENT

The PhD journey has been a humbling experience. I started my PhD with the notion that research is a solitary work. However, throughout this journey, I was given so much help from my fellow colleagues that I cannot possibly thank each one of them here. The following three people played a pivotal role in my PhD completion and I would like to express my deepest gratitude to them.

A/P Wang Jing-Yuan, my supervisor for my PhD, is more than a teacher to me. Besides inspiring me with his research passion in solid waste management, he always reminds me not to neglect my family over research. I am glad that I am his student and I would like to thank him for letting me work under him.

Dr. Sun Xiaolong is my mentor for the last two years of my PhD journey. He is a strict mentor but I learned a lot while under him, especially in technical writing. Despite his busy work schedule, he still made extra effort to proof read my report in detail. I greatly admire his research attitude.

Heng Kim Soon is a fellow colleague whom I greatly admire his research talent. Some of the laborious laboratory work in my PhD could not have been easily carried out without his selfless help. I am very grateful that he joined me as a colleague during the last year of my PhD. I was able to bounce off research ideas with him, which helped defined my final research direction.

Lastly, I would like to thank my husband Mervin for his unconditional love and support throughout these four years. Without him, I would not have been able to have the best of both worlds: a career and a wonderful family. To my two lovely little children, Raye and Roy, I dedicate my research work to you.

TABLE OF CONTENT

	PAGE
ACKNOWLEDGEMENT	i
ABSTRACT	vi
PUBLICATIONS	viii
LIST OF TABLES	ix
LIST OF FIGURES	x
LIST OF ABBREVIATIONS	xvi
 CHAPTER 1: INTRODUCTION	
1.1 Background	1
1.2 Problem statement	3
1.3 Objective and scope	3
1.3.1 Characterisation of IBA	3
1.3.2 Accelerated carbonation of IBA under controlled environment	4
1.3.3 Leaching tests	4
1.3.4 Mineralogical study	5
1.4 Organisation of report	5
 CHAPTER 2: LITERATURE REVIEW	
2.1 Introduction	7
2.2 Characteristics of IBA	7
2.2.1 Physical characteristics	7
2.2.2 Chemical characteristics	8
2.2.3 Distribution of heavy metals among size fractions	10
2.3 Utilisation potential of IBA	10
2.4 Treatment of IBA - Carbonation	11
2.4.1 Natural weathering	11
2.4.2 Accelerated carbonation	12
2.5 Leaching	14
2.5.1 Physical aspects of leaching	14

2.5.2	Chemical aspects of leaching	15
2.5.3	Leaching tests	16
2.6	Effect of carbonation on leaching	18
2.6.1	Ca	19
2.6.2	Pb and Zn	19
2.6.3	Cr and Cu	20
2.6.4	Other trace elements	20
2.6.5	Highly soluble salts	21
 CHAPTER 3: MATERIALS AND METHODS		
3.1	Sampling of IBA	22
3.2	Handling of IBA	23
3.3	Analysis	23
3.3.1	Total element content	24
3.3.2	Total inorganic carbon content	24
3.4	Leaching Tests	24
3.4.1	EN 12457-2	25
3.4.2	CEN/TS 14429 (pH-static test)	25
 CHAPTER 4: CHARACTERISATION OF IBA		
4.1	Introduction	26
4.2	Materials and Methods	26
4.3	Results and Discussion	27
4.3.1	Physical characteristics	27
4.3.2	Total trace element content	29
4.3.3	Leaching	32
4.4	Conclusion	34
 CHAPTER 5: INFLUENCE OF MOISTURE CONTENT AND TEMPERATURE ON THE EFFICIENCY OF ACCELERATED CARBONATION OF IBA		
5.1	Introduction	35
5.2	Materials and Methods	36

5.2.1	Incineration bottom ash	36
5.2.2	Accelerated carbonation	36
5.2.3	Analysis	37
5.2.4	Linear correlation coefficient	37
5.3	Results and Discussion	38
5.3.1	Total element content	38
5.3.2	Degree of carbonation as a function of time	40
5.3.3	Effect of actual moisture content on rate of carbonation	43
5.3.4	pH profile as a function of time	46
5.3.5	Leaching profile as a function of time	48
5.4	Conclusion	68

CHAPTER 6: EFFECT OF ACCELERATED CARBONATION ON DIFFERENT SIZE FRACTIONS OF IBA

6.1	Introduction	71
6.2	Materials and Methods	72
6.2.1	Incineration bottom ash	72
6.2.2	Accelerated carbonation	72
6.2.3	Analysis	73
6.3	Results and Discussion	73
6.3.1	Characteristics of IBA	73
6.3.2	Degree of carbonation of different size fractions	77
6.3.3	Effect of accelerated carbonation on pH	78
6.3.4	Effect of accelerated carbonation on leaching	79
6.3.5	Effect of different size fractions on pH-static leaching	87
6.4	Conclusion	92

CHAPTER 7: INVESTIGATION ON THE MINERALOGICAL COMPOSITION OF IBA

7.1	Introduction	94
7.2	Materials and Methods	95
7.2.1	Materials	95

7.2.2 XRD	95
7.3 Results and Discussion	96
7.3.1 XRD analysis of untreated IBA	96
7.3.2 XRD analysis of carbonated IBA	104
7.4 Conclusion	109
CHAPTER 8: CONCLUSION AND RECOMMENDATION	
8.1 Conclusion	110
8.2 Recommendation	115
REFERENCE	117

ABSTRACT

In Singapore, incineration is the main waste management technology used for handling municipal solid waste (MSW), in conjunction with recycling and other waste minimisation policy. After incineration, the volume of waste can be reduced up to 90%, thereby significantly reducing the demand of land space for the final disposal of waste. However, incineration cannot completely eradicate the need for landfill as the end product of incineration, i.e. incineration ash, still has to be disposed of properly in a sanitary landfill. Currently, Singapore's only offshore landfill, Pulau Semakau, is estimated to last till 2035. With a lack of suitable alternative landfill in land scarce Singapore, there is an urgency to utilise incineration bottom ash (IBA), which accounts for 85-95% of the total residues produced after incineration, so as to prolong the lifespan of the landfill. Before IBA can be utilised, it has to be treated to reduce the leaching of heavy metals. This research proposes accelerated carbonation for IBA treatment as it has some advantages over other methods, and has not yet been explored in Singapore. Literature review has also shown this process is sustainable and economically viable.

Before accelerated carbonation was carried out, the physical and chemical characteristics of untreated IBA were studied by collecting and analysing IBA from two incineration plants in Singapore, over a 6 months period. The two incineration plants, i.e. SWTEP and TSIP, were selected based on the types of waste received, which could then produce different mineralogical compositions of IBA. The 6 months sampling period was decided to cover the possible temporal variation of IBA characteristics. This characterisation study showed that the total element contents of IBA from both incineration plants in Singapore are similar to those in other countries reported in literature. However, elements like Cd, Co, Hg, Pb and Se exhibited high variation over the investigated sampling period. Pb showed similar high variation in leaching test. Lastly, Cu and Pb from both incineration plants did not meet the criteria for watercourse discharge while F⁻ from SWTEP did not meet the sewer criteria, if no treatment was carried out. This 6 months study has found Pb to be a potential problem in the utilisation of IBA due to its high variation.

The accelerated carbonation experiment was divided into two parts. In the first part, the influence of moisture content and temperature on accelerated carbonation was investigated using the 0-2 mm size fraction of IBA. The optimum operating conditions found in the first part was then applied to other size fractions (i.e. 2-4 mm, 4-20 mm and 20-50 mm) in the second part of the experiment. Results showed that the optimum operating conditions fixed at 20% CO₂ at 1 atm for the two incineration plants were slightly different. For SWTEP, it was 35°C and 15% moisture content. For TSIP, it was 50°C and 15% moisture content. The carbonation duration for both plants was 2 hours. XRD analysis showed slight difference between the mineralogical compositions of the two incineration plants, which could explain the different optimum carbonation temperatures.

Most of the heavy metals (i.e. Pb, Zn, Cu and Cr) were found to reduce in leaching after accelerated carbonation, whereas Mo and Sb leaching generally increased after carbonation. After sieving the IBA into four different size fractions, the amount of soluble salts released from untreated IBA showed decrement as the size increased. The leaching mechanism among the different size fractions was found to be similar. Despite the limitations in reducing the leaching of certain trace elements (i.e. Mo and Sb), accelerated carbonation was able to significantly reduce the amount released of Pb, Zn, Cu and Cr. On the other hand, accelerated carbonation was found to be ineffective in reducing the leaching of soluble salts.

This study showed that the increase in calcite after carbonation was not the direct contributor to the reduction in leaching. Rather, the effect of carbonation resulted in the decrease in pH and the formation of secondary minerals, which then contributed to the reduction in leaching through solubility control and adsorption. Lastly, the difference in mineral content in the different size fractions gave rise to varying percentage of reduction in leaching after carbonation.

In conclusion, this study has shown that accelerated carbonation has the potential to treat IBA effectively within a short time frame.

PUBLICATIONS

Papers published on peer-review journals

1. **Lin, W.Y.**, K.S. Heng, X.L. Sun, and J.-Y. Wang (2015). “Accelerated carbonation of different size fractions of MSW IBA and the effect on leaching.” Waste Management 41: 75-84.
2. **Lin, W.Y.**, K.S. Heng, X.L. Sun, and J.-Y. Wang (2015). “Influence of moisture content and temperature on degree of carbonation and the effect on Cu and Cr leaching from incineration bottom ash.” Waste Management 43:264-272.

Conference papers

1. **Lin, W.Y.** and Wang, J.Y. (2012). “Investigation on Accelerated Carbonation of MSW Bottom Ash for Application of Biogas Purification.” 3rd International Conference on Industrial and Hazardous Waste Management, 12-14 September 2012, Chania, Crete, Greece.
2. X.L. Sun, **W.Y. Lin**, L. Ge, I.J.R. Ho, O.A. Mohamed Noh, K.S. Heng, S.Y. Choy, M.Q. Nguyen, X.D. Zhou, T. Aung, A. Liu, J.-Y. Wang (2014). “Sampling and Characterization of Singapore’s Municipal Solid Waste Incineration Bottom Ash.” Fifth International Symposium on Energy from Biomass and Waste, 17-20 November 2014, San Servolo, Venice, Italy.
3. K.S. Heng, **W.Y. Lin**, X.L. Sun, J.-Y. Wang (2014). “Effect of Washing and Accelerated Carbonation on the Leaching Behaviour of Copper from MSW Incineration Bottom Ash.” Fifth International Symposium on Energy from Biomass and Waste, 17-20 November 2014, San Servolo, Venice, Italy.

LIST OF TABLES

	PAGE
Table 2-1 Range of composition of elements found in IBA sampled 18 times over a 1.5 year period from Canada, Denmark, Germany, the Netherlands, Sweden and the United States incineration plants (Chandler et al., 1997).	9
Table 2-2 Summary of reduction in Pb and Zn leaching from IBA after accelerated carbonation.	19
Table 3-1 Detection limits of heavy metals analysed by ICP-OES.	25
Table 4-1 Physical characteristics of IBA samples.	29
Table 4-2 Comparison of Singapore's IBA composition (in terms of trace elements) with other countries.	30
Table 4-3 Comparison of landfill disposal criteria and effluent criteria in Singapore to the mean of the IBA leachate (n=40).	33
Table 5-1 Abbreviation of the 9 sets of carbonation experiment carried out under different operating conditions.	37
Table 5-2 Total element content (mg/kg) of 0-2 mm size fraction of IBA from incineration plants SWTEP and TSIP.	39
Table 6-1 Characteristic of IBA collected from incineration plants SWTEP (S) and TSIP (T).	74
Table 6-2 Total element content (mg/kg) for the four size fractions from incineration plants SWTEP and TSIP.	76
Table 6-3 The degree of carbonation (mg/g) of the respective size fractions and the actual moisture content (%) remained after 2 hours of carbonation.	78
Table 7-1 Comparison of mineralogical composition (in wt%) of the different sources and size fractions of untreated IBA determined by quantitative XRD using Rietveld method.	100
Table 7-2 Comparison of mineralogical composition (in wt%) after accelerated carbonation at 35°C and 50°C, 15% moisture content for different size fractions of TSIP samples, using Rietveld method for quantitative XRD analysis.	107

LIST OF FIGURES

	PAGE
Figure 2-1	16
Figure 2-2	18
Figure 3-1	23
Figure 4-1	27
Figure 4-2	28
Figure 4-3	31
Figure 4-4	32

Figure 5-1	Degree of carbonation as a function of time for SWTEP and TSIP samples at various operating conditions.	41
Figure 5-2	Comparison of degree of carbonation for (a) SWTEP and (b) TSIP samples at 2 hours of carbonation.	42
Figure 5-3	Degree of carbonation (top) and corresponding actual moisture content (bottom) for SWTEP and TSIP samples at various operating conditions.	45
Figure 5-4	pH as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	47
Figure 5-5	Correlation between pH and degree of carbonation for (a) SWTEP and (b) TSIP samples.	48
Figure 5-6	Cu release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	50
Figure 5-7	Correlation between Cu leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Cu leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.	51
Figure 5-8	DOC leaching (mg/L) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	53
Figure 5-9	DOC leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (a) SWTEP and (b) TSIP samples.	54
Figure 5-10	Correlation between Cu and DOC leaching for (a) SWTEP and (b) TSIP samples.	54
Figure 5-11	Cr release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	56

Figure 5-12	Correlation between Cr leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Cr leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.	57
Figure 5-13	Mo release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	59
Figure 5-14	Correlation between Mo leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Mo leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.	60
Figure 5-15	Sb release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	62
Figure 5-16	Correlation between Sb leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Sb leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.	63
Figure 5-17	Cl ⁻ release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	65
Figure 5-18	Correlation between Cl ⁻ leaching and degree of carbonation for (a) SWTEP and (b) TSIP samples.	66
Figure 5-19	SO ₄ ²⁻ release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.	67
Figure 5-20	Correlation between SO ₄ ²⁻ leaching and degree of carbonation for (a) SWTEP and (b) TSIP samples.	68

Figure 6-1	The pH of the different size fractions showing untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	79
Figure 6-2	Zn release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	80
Figure 6-3	Cu release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	81
Figure 6-4	Correlation between Cu and DOC leaching for the different size fractions of SWTEP and TSIP samples carbonated for 2 hours at 15% moisture content and (a, c) 35°C and (b, d) 50°C. R = Pearson's R.	82
Figure 6-5	Cr release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	83
Figure 6-6	Mo release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	84
Figure 6-7	Sb release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	85
Figure 6-8	Concentration of DOC (mg/L) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	85
Figure 6-9	Cl ⁻ release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	86
Figure 6-10	SO ₄ ²⁻ release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.	87
Figure 6-11	The acid neutralising capacity (ANC) of the different size fractions of untreated (a) SWTEP and (b) TSIP samples.	88

Figure 6-12	Pb leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test. The detection limit of ICP-MS for Pb is 0.1 µg/L. The represented value used here is 5×10^{-4} mg/kg.	89
Figure 6-13	Zn leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test. The detection limit of ICP-MS for Zn is 0.5 µg/L. The represented value used here is 2.5×10^{-3} mg/kg.	90
Figure 6-14	Cu leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test.	90
Figure 6-15	Cr leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test.	91
Figure 6-16	Mo leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test.	91
Figure 6-17	Sb leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test. The detection limit of ICP-OES for Sb is 10 µg/L. The represented value used here is 0.05 mg/kg.	92
Figure 7-1	XRD patterns of untreated (a) S0-2 and (b) T0-2 samples. [An = anhydrite, Ca = calcite, D = diopside, Gib = gibbsite, H = hematite, Ha = hydroxylapatite, M = magnetite, P = portlandite, Q = quartz]	96
Figure 7-2	XRD patterns of untreated T0-2, T2-4, T4-20 and T20-50 samples. [An = anhydrite, Ca = calcite, D = diopside, H = hematite, M = magnetite, P = portlandite, Q = quartz]	97
Figure 7-3	XRD spectrum of untreated S0-2 sample.	103

Figure 7-4 XRD patterns of untreated and carbonated IBA at 50°C and 104
15% moisture content of (a) T0-2 and (b) T20-50 samples.
[An = anhydrite, Ca = calcite, H = hematite, M = magnetite,
P = portlandite, Q = quartz]

LIST OF ABBREVIATIONS

Abbreviation	Description
CCS	Carbon Capture Storage
DI	Deionised
DOC	Dissolved Organic Carbon
GOF	Goodness of Fit
IBA	Incineration Bottom Ash
IFA	Incineration Fly Ash
ICP-MS	Inductively Coupled Plasma-Mass Spectrometry
ICP-OES	Inductively Coupled Plasma-Optical Emission Spectrometry
IC	Ion Chromatography
LOI	Loss on Ignition
MSW	Municipal Solid Waste
SWTEP	Senoko Waste to Energy Plant
TC	Total Carbon
TIC	Total Inorganic Carbon
TOC	Total Organic Carbon
TSIP	Tuas South Incineration Plant
XRD	X-Ray Diffraction

CHAPTER 1: INTRODUCTION

1.1 Background

Municipal solid waste (MSW) is an inevitable by-product of human lifestyle. The management of MSW has become a challenge as the rate of generation per person per day increases at exponential rate. According to the World Bank report (2012), the world cities are currently generating about 1.3 billion tonnes of solid waste per year, or 1.2 kg per person per day. Ten years ago, it was only 0.64 kg per person per day. And by 2025, it is projected to increase to 2.2 billion tonnes per year. Hence, the management of municipal solid waste has to be efficient and affordable so as to maintain a reasonable level of hygiene for human community.

The common method for waste disposal used worldwide is landfill (World Bank, 2012). In 1999, the European Union (EU) issued a Landfill Directive to reduce the use of landfills and the type of wastes that are acceptable to landfill (CEU, 1999). This means that EU members are encouraged to improve the recycling rate or use alternative waste treatment technology (such as composting and incineration) to reduce the amount of waste needed to be landfilled. However, incineration is not the last step in the treatment of MSW as incineration ash, which is the remains of the non-combustible portion of MSW, is produced. Incineration ash cannot be disposed directly into the landfills without treatment as the council of EU has issued a set of criteria for leaching limits acceptable at landfills for hazardous waste (CEU, 2003).

Incineration is the main technology used for the management of MSW in Singapore. It is the preferential choice for a tiny island like Singapore. Firstly, waste can be disposed of in an efficient and hygienic manner through mass burning, thereby maintaining a high level of cleanliness in the country; secondly, the volume of the waste is reduced by approximately 90% after incineration, so the amount of land needed for the final disposal of ash is greatly reduced. In addition, by providing affordable waste disposal through the extensive use of incineration, Singapore has been able to control illegal dumping. Hence, incineration plants have been playing an important role in Singapore's waste management since the first plant was

commissioned in 1979. However, incineration should not be considered as the final step for waste management as the ash generated still needs to be treated and disposed properly.

Currently in Singapore, all the incineration bottom ash (IBA) and fly ash (IFA) are mixed at the bottom ash pits inside the incineration plants, before they are landfilled in an offshore island, Pulau Semakau. The only resource recovery is done by a magnetic separator placed above the conveyor belt to recover the scrap ferrous metal before the incineration ash reaches the ash pits. Pulau Semakau, the only landfill in Singapore, is estimated to last till 2035. In view of the lack of alternative landfill option in land-scarce Singapore, there is an urgent need to explore ways to utilise the incineration ash. In recent years, Singapore has been exploring ways to utilise IBA as European Waste Catalogue classifies IBA as a non-hazardous waste and hence, can be utilised after proper treatment. A major concern in the utilisation of IBA is the leaching of heavy metals and highly soluble salts, which may occur over the period of utilisation due to the interaction of IBA with water such as rain or groundwater. The dissolved heavy metals pose a risk in polluting the surrounding groundwater to toxic levels while soluble salts such as chloride salts are detrimental to the soundness of structural buildings. Therefore, IBA has to be treated to reduce leaching before utilisation. Some of the treatment technologies include washing, extraction with chelating agents, stabilisation/solidification with cement, and natural weathering (Todorovic and Ecke, 2006).

IBA from burning of MSW undergoes carbonation with atmospheric CO₂ naturally at ambient conditions, due to its metastable state after quenching with water straight after combustion at high temperature (Rendek et al., 2006). This process, known as natural weathering or aging, is beneficial to the quality of IBA as the leaching of certain heavy metals is reduced (Fernández Bertos et al., 2004a; Arickx et al., 2006). Compared to other treatment technologies, aging does not require advance facility and is cost effective. Unlike washing, which produces large volume of wastewater that requires treatment after washing IBA, there are less waste streams to deal with after aging. However, the aging process is slow. In Denmark, IBA are naturally

aged for 2 to 3 months, sometimes up to 12 months, before the leaching is reduced to the limit set in Danish legislation (Astrup, 2007). The long aging process poses a challenge to Singapore due to the lack of available land to hold the IBA. However, it has been demonstrated that the duration of this process can be shortened to complete within hours or days by optimising operating conditions such as the concentration of CO₂, reaction temperature, moisture content of ash, and particle size of ash (Costa et al., 2007). Arickx et al. (2006) compared natural weathering to accelerated carbonation process. The authors reported that by using accelerated carbonation process, the reduction in leaching was achieved in shorter time, from 3 months of natural weathering to 4 weeks of accelerated carbonation. The shorter carbonation period will help to ease the burden of having to set aside a large piece of land to naturally age IBA in land-scarce Singapore.

1.2 Problem statement

For Singapore, where the research on the treatment technologies of IBA is still in its infancy, it is vital to explore various treatment options and accelerated carbonation has been overlooked up till now. Most of the research in Singapore had been focused on using stabilisation/solidification treatment for civil application (Tay, 1988; Tay and Cheong, 1991; Tay and Goh, 1991; Goh et al., 2003). This study aims to fill in this gap by investigating accelerated carbonation process for IBA treatment.

1.3 Objective and scope

The aim of this research is to understand the physicochemical mechanism of accelerated carbonation and its influences on the leaching behaviour of IBA, using leaching tests and analytical methods such as mineralogical characterisation. The following tasks were carried out:

1.3.1 Characterisation of IBA

To understand the physicochemical mechanism of accelerated carbonation, IBA was collected from two incineration plants with different types of waste input – one

receives predominantly household waste and the other receives predominantly industrial waste. This is to determine the influence of mineralogical composition of IBA on accelerated carbonation process. Physical and chemical characterisation of IBA was carried out to compare the similarities and differences of IBA from the two incineration plants. The physical characterisation includes size fraction distribution and density. The chemical characterisation includes total element content, loss on ignition (LOI), total carbon content, and X-ray diffraction (XRD).

1.3.2 Accelerated carbonation of IBA under controlled environment

The accelerated carbonation process was carried out under a controlled environment using a CO₂ incubator. The concentration of CO₂ is fixed at 20% at atmospheric pressure for all the experiments as it would be more realistic than using pure CO₂. The influence of operating conditions, i.e. moisture content and temperature, on the degree of carbonation was investigated using 0-2 mm size fraction of IBA, which was ground to <425 µm. This is to determine the optimum operating condition that can achieve the highest rate of carbonation. The optimum operating condition for the accelerated carbonation process was then applied to other size fractions of IBA, which were also ground to <425 µm to minimise the effect of particle size on carbonation. This is to investigate the response of different size fractions of IBA towards the accelerated carbonation treatment.

1.3.3 Leaching tests

To understand the effect of accelerated carbonation on the leaching behaviour of IBA, two leaching tests were carried out. EN 12457-2 was used to evaluate the leaching behaviour of IBA before and after carbonation. This leaching test was selected for this research as it is developed for determination of waste compliancy with regulated values set by respective European countries such as Finland, France, Germany and Italy. The second leaching test, i.e. CEN/TS 14429, was done to investigate the effect of pH on IBA leaching. This leaching test was carried out to compare the leaching behaviour of IBA as a function of pH due to externally added acid versus the change in pH due to carbonation.

1.3.4 Mineralogical study

To further complement the understanding in the carbonation and leaching mechanism of IBA after accelerated carbonation, mineralogical composition of IBA was analysed using XRD. This study investigated the differences in mineralogical composition in terms of IBA collected from two different incineration plants and the different size fractions of IBA.

1.4 Organisation of report

This report starts with an introduction of the background and the identification of research gap in Chapter 1. Chapter 2 provides the literature review of the characteristics of IBA and the research done previously on accelerated carbonation of IBA. The leaching mechanism of IBA and the effect of carbonation on its change in leaching behaviour reported by other researches are also discussed here. Chapter 3 describes an overview of the sampling, handling and analysis of IBA for the accelerated carbonation process. To achieve the objective of this study, the research was divided into four experimental works. The characterisation of IBA was discussed in Chapter 4. This chapter summarises the physical and chemical characteristics of IBA collected from two incineration plants over a 6 months period. This study was accepted as a conference paper “Sampling and Characterisation of Singapore’s Municipal Solid Waste Incineration Bottom Ash” in Venice Symposium 2014. The accelerated carbonation experiments carried out are described in Chapter 5 and 6. Chapter 5 looks at the influence of moisture content and temperature on the degree of carbonation, using 0-2 mm size fraction of IBA. The optimum operating conditions were then selected and applied to other size fractions, which is detailed in Chapter 6. In both Chapter 5 and 6, the effect of degree of carbonation on leaching behaviour of IBA was investigated using leaching tests. Chapter 5 focuses on discussing factors that play a dominant role in the leaching mechanisms of constituents in the 0-2 mm size fraction. In Chapter 6, it compares the differences in the leaching behaviour in terms of the difference in chemical composition in the four size fractions. The last experimental work used mineralogical characterisation (i.e. XRD) to evaluate and compare the mineralogical composition of untreated IBA from two different incineration plants

and among the different size fractions, which is discussed in Chapter 7. Selected carbonated samples were also analysed to evaluate the possible leaching mechanism that were influenced by mineralogical composition. Part of the results from Chapters 5 to 7 were published in two papers “Accelerated carbonation of different size fractions of MSW IBA and the effect on leaching” and “Influence of moisture content and temperature on degree of carbonation and the effect on Cu and Cr leaching from incineration bottom ash”. Chapter 8 concludes on the knowledge gained in this research and discusses the potential of applying this study to treat IBA, and recommends how to continue this research.

CHAPTER 2: LITERATURE REVIEW

2.1 Introduction

Incineration is a type of thermal waste treatment technology that combusts the organic portion of the municipal solid waste, and converts the non-combustible portion into by-products such as incineration ash, flue gases and heat. Despite the advantages of incinerating waste, such as volume and weight reduction, and the destruction of pathogens during the combustion of waste, incineration cannot completely eradicate the need for landfills. The production of incineration ash and flue gases are the major concerns that have to be addressed together with the use of incineration plants for MSW management. This literature review covers the characteristics of fresh and naturally weathered IBA, the researches done on accelerated carbonation of IBA and the changes in the leaching behaviour of IBA after carbonation.

2.2 Characteristics of IBA

2.2.1 Physical characteristics

IBA consists of ash that remains unburned from the grate, and includes siftings that fall through the grate. In Singapore, IBA also includes the boiler ash, i.e. the ash that condenses on the walls of the boiler, which is mixed with grate ash and grate siftings before quenching. Upon exiting the quench tank, the water content of IBA ranges from 9.4% to 58.4%, depending on the system used to quench IBA (Chandler et al., 1997). IBA has a wide particle size distribution that makes up a well-graded material of fine to coarse particles. By visual inspection, IBA is found to be made up of refractory materials such as glass, ceramic, scrap metals and minerals. These materials are non-combustible and account for 85 to 95% of the total solid by-products (Chandler et al., 1997). Chimenos et al. (1999) conducted a visual sorting of IBA with particle size greater than 1 mm into glass, ceramics, minerals, magnetic metals, diamagnetic metals, and unburned organic matter. Glass was found to be the highest in all the size fractions investigated, ranging from the

lowest 35 wt% in the 1-2 mm size fraction to the highest 68 wt% in the 4-6 mm size fraction from the same incineration plant. Ceramics and minerals were the next two materials most commonly found in IBA. Unburned organic content after incineration is usually low. It is measured by LOI test, where the weight lost is measured after heating dried IBA at 550°C for 2 hours. Some countries, like Spain, regulate the maximum allowable LOI value to be 5% (Izquierdo et al., 2002).

2.2.2 Chemical characteristics

Studies were done to identify the minerals present in IBA, using analytical techniques such as X-ray diffraction (XRD) and energy-dispersive X-ray spectroscopy (EDS) (Kirby and Rimstidt, 1993; Eighmy et al., 1994; Speiser et al., 2001; Wei et al., 2011). The purpose of these studies is to develop a better understanding in the leaching behaviour of IBA, which determines the treatment needed for IBA and the potential utilisation of IBA. SiO₂ and Ca-based minerals are found to be present in dominant concentrations in IBA (Kirby and Rimstidt, 1993).

In terms of the elemental composition of IBA, silicon is one of the major elements present in IBA. Other elements present in IBA are shown in Table 2-1, which is not exhaustive. These elements had been investigated by Chandler et al. (1997). The data was collected from 39 incineration plants over a 1.5 year period and spanned across 6 different countries. Chandler et al. (1997) classified the elements found in IBA into major (>10,000 mg/kg), minor (1,000 to 10,000 mg/kg) and trace elements (<1,000 mg/kg).

Although IBA can be acid-digested into solution for the analysis of its elemental composition, in reality, such harsh condition is not attainable and IBA is considered to be insoluble in water. The pH of a freshly quenched IBA ranges from 10.5 to 12.2 due to the hydrolysis of CaO (Chandler et al., 1997). IBA is also resistant to slight changes in pH due to its buffering capacity. Johnson et al. (1995) found that fresh IBA have an ANC_{7.5} of 1.2 to 1.7 ± 0.05 meq/g. This means that 1.2 milliequivalent of acid was required to reduce the pH of 1 g of IBA to pH 7.5 from pH 11 (Johnson et al., 1995). The endpoint for ANC does not need to be fixed at 7.5.

Table 2-1: Range of composition of elements found in IBA sampled 18 times over a 1.5 year period from Canada, Denmark, Germany, the Netherlands, Sweden and the United States incineration plants (Chandler et al., 1997).

Major Elements (>10,000mg/kg)	
Si	91,000 – 308,000
Fe	4,120 – 150,000
Ca	370 – 123,000
Al	21,900 – 72,800
Na	2,870 – 42,000
K	750 – 16,000
Minor Elements (1,000 to 10,000mg/kg)	
Mg	400 – 26,000
Cl	800 – 4,190
Mn	83 – 2,400
Ba	400 – 3,000
Zn	613 – 7,770
Cu	290 – 8,240
Pb	98 – 13,700
Cr	23 – 3,170
Trace Elements (<1,000mg/kg)	
Sn	2 – 380
Sb	10 – 432
V	20 – 122
Mo	2.5 – 276
As	0.12 – 189
Se	0.05 – 10
Sr	85 – 1,000
Ni	7 – 4,280
Co	6 – 350
Cd	0.3 – 70.5
Ag	0.29 – 36.9
Hg	0.02 – 7.75

2.2.3 Distribution of heavy metals among size fractions

The elemental composition of the different size fractions of IBA were investigated (Chimenos et al., 1999; Baciocchi et al., 2010). These studies have found that certain heavy metals were more abundant in the fine fraction. Chimenos et al. (1999) reported that Pb, Zn and Cu were more concentrated in the 1-2 mm size fraction and their concentrations decreased significantly as the size fraction increased. Baciocchi et al. (2010) found Pb, Cr and Sb to be concentrated in the $<0.425\ \mu\text{m}$ size fractions, while Cu, Zn, Ni and V were evenly distributed. The soluble salts were more concentrated in the fine fractions (Baciocchi et al., 2010).

2.3 Utilisation potential of IBA

Although there are concerns of heavy metal leaching from IBA which makes it unattractive for utilisation, IBA has been found to be suitable for civil engineering applications such as aggregate substitute in the sub-base of road paving, partial replacement of raw materials in cement production, and as filler in concrete production (Chandler et al., 1997).

Izquierdo et al. (2002) studied the IBA in Catalonia for use in road sub-base and found that IBA complied with Spanish Specifications for road construction. A similar trial using IBA to replace 50% of aggregate in a binder course asphalt pavement was conducted in New Hampshire by Musselman et al. (1994). The physical properties of IBA was found to meet the requirements of New Hampshire Department of Transportation but the high moisture content of IBA resulted in lower manufacturing throughput of the asphalt.

There are a few problems with using IBA as partial replacement in cement production. Pera et al. (1997) reported gaseous emission during the mixing of IBA and ordinary Portland cement (OPC), which resulted in high porosity and low strength material. However, the authors found that this was due to the reaction between metallic Al and OPC, which was resolved by immersing IBA in NaOH solution for 15 days. Filipponi et al. (2003) compared the mineralogy of IBA with that of OPC, blast furnace slag (BFS) and coal fly ash. They found that IBA has

similar composition with Class F of coal fly ash. However, upon mixing IBA with OPC, Filippini et al. (2003) found that the pozzolanic properties of IBA were weak.

In a study conducted using IBA from Singapore, the specific gravity and compacted density of fine IBA fraction was found to be 2.67 and 1.54 mg/m³ respectively, similar to the typical sand values of 2.65 and 1.90 mg/m³ respectively (Tay and Goh, 1991). The authors also found that the fine IBA had high permeability, which made it suitable for land reclamation.

2.4 Treatment of IBA – Carbonation

Before the utilisation of IBA, treatment must be done to reduce the leaching of heavy metals. Various treatment technologies are available, such as washing, solidification and carbonation. This research proposes to use accelerated carbonation as the treatment technology for IBA. This is because accelerated carbonation has several advantages over other treatment technologies: carbon neutral, ease of application, and less waste stream produced after carbonation. This section reviews the work done on the carbonation of IBA.

2.4.1 Natural weathering

In nature, rocks and minerals undergo chemical reactions, such as carbonation with atmospheric CO₂ and hydrolysis, to form new or secondary minerals. This process is thermodynamically favoured. However, the kinetics of carbonate formation with appropriate minerals is exceedingly slow at ambient temperatures and pressures, occurring over geologic time frames. It involves reacting CO₂ with abundantly available alkaline rocks. Similarly, IBA undergoes natural weathering or aging at ambient conditions due to its metastable state after quenching straight after combustion at high temperature, but the process is slow. The act of quenching IBA at high temperature resulted in a large proportion of IBA to consist of reactive amorphous materials (Meima and Comans, 1997a). At this stage, freshly quenched IBA has a pH range of 10.5 to 12.2 (Chandler et al., 1997). Its alkaline nature was reported to be controlled by portlandite (Ca(OH)₂) (Meima and Comans, 1997a). Upon carbonation with atmospheric CO₂, the pH of IBA will drop to neutral.

For carbonation of IBA to occur, firstly, CO₂ has to be dissolved in water to form weak carbonic acid. Secondly, the weak acid will react with the dissolved alkaline minerals to form carbonates. Calcite (CaCO₃) had been reported to be the principal newly formed mineral after weathering (Piantone et al., 2004). Rendek et al. (2006) provided a simplified chemical expression of the carbonation process:

In the natural weathering process, besides carbonation, many complex reactions, such as hydration/oxidation of metals or metal oxides, corrosion of glassy phase, and dissolution/precipitation of salts, take place at the same time (Speiser et al., 2000).

2.4.2 Accelerated carbonation

Lackner et al. (1995) were one of the pioneers to conduct detailed investigations on accelerating the carbonation of minerals to sequester CO₂ into thermodynamically stable carbonate minerals. Their focus was on Ca- and Mg- bearing minerals that are available in abundant quantities. However, the main disadvantage of using minerals for carbon capture storage (CCS) is the transportation of minerals to the CO₂ emission sites. Other disadvantages include the need for mining of such minerals, pre-treatment of minerals and non-ambient conditions during accelerated carbonation, all of which indirectly drives up the cost of using minerals for CCS.

Since the weathering of IBA is based on the same principle of using alkaline earth minerals to react with CO₂, several researchers have been investigating the use of IBA as an alternative material for CCS (Fauth et al., 2002; Rendek et al., 2006; Prigiobbe et al., 2009; Lim et al., 2010). Another important advantage of using accelerated carbonation is to treat IBA as the leaching behaviour of IBA can be improved in a shorter period of time compared to natural weathering, hence allowing for use in civil engineering applications or for safer final disposal to landfills (Costa et al., 2007).

The main difference between natural weathering and accelerated carbonation is the concentration of CO₂ present during the treatment process. In natural weathering, IBA is left in an open area for aging to take place with atmospheric CO₂. As the reaction is exothermic, there is no need for energy input, except for the occasional turning over the pile of IBA. However, the concentration of CO₂ used in accelerated carbonation is much higher than atmospheric CO₂. Arickx et al. (2006) proposed that the stack gas from incineration plant of around 10% CO₂ can be used as a CO₂ source for accelerated carbonation process. Generally, the rate of carbonation increases with the concentration of CO₂ (Fernandez Bertos et al., 2004b). The rate of carbonation has also been found to increase with the partial pressure of CO₂ but higher partial pressure did not increase the amount of CO₂ sequestered (Rendek et al., 2006).

Other factors that affect the rate of carbonation are the moisture content of IBA and temperature of carbonation. The presence of moisture in IBA is necessary for the dissolution of CO₂ and Ca minerals for the precipitation of carbonates, as shown in Eq. 2-1. Rendek et al. (2006) showed that carbonation did not take place for dry IBA and the optimum moisture content was found to be 15% at room temperature under CO₂ pressure of 2 bar. However, excess moisture retards penetration and diffusion of CO₂ to IBA particle surface, thus reducing the rate of carbonation process (Fernandez Bertos et al., 2004b). Temperature of carbonation does not have a linear relationship with the rate of carbonation either. Although higher temperature results in higher Ca²⁺ dissolution, the solubility of CO₂ in water decreases (Fernandez Bertos et al., 2004b). Costa et al. (2007) summarised the studies done on the operating conditions of accelerated carbonation, and the investigated moisture content and temperature were 5-60% and ambient to 50°C respectively.

Besides the operating conditions that affect the rate of carbonation, the amount of CO₂ sequestered is dependent on the surface area of IBA available for the carbonation reaction and the chemical composition of IBA. The finer the particle size of IBA, the greater the surface area for carbonation reaction, and the less

moisture is needed (Fernandez Bertos et al., 2004b). In terms of the chemical composition of IBA, Baciocchi et al. (2010) studied the effect of the different chemical composition on accelerated carbonation by sieving the IBA into different size fractions and grinding to $<425\text{ }\mu\text{m}$. Under the same operating conditions of 30°C , L/S of 0.3 and 100% CO_2 at 10 bar, the coarse fractions (i.e. $>0.425\text{ mm}$) sequestered around 4% of CO_2 after 8 hours of carbonation, compared to 14% for the fine fraction (i.e. $<0.150\text{ mm}$). The elemental composition of the different size fractions showed that the fine fraction had higher Ca content than the coarse fraction, which could promote higher CO_2 uptake (Baciocchi et al., 2010).

The most important advantage of accelerated carbonation over natural weathering in IBA is the shorter carbonation period needed for the reduction in certain heavy metals leaching. This will indirectly reduce the need for vast amount of land to store IBA during natural weathering, which is economically unviable for land-scarce Singapore. Arickx et al. (2006) reported that by using accelerated carbonation process, the reduction in leaching was achieved in shorter time, from 3 months of natural weathering to 4 weeks of accelerated carbonation.

2.5 Leaching

Leaching can be described as the dissolution of elements from IBA, when IBA comes into contact with a liquid. In terms of leaching, this liquid is known as the leachant. The leachant can be water, acid or alkaline, or mixed with other chemicals. Although the chemical and mineralogical composition of IBA greatly influences the leaching behaviour of IBA, there are several external factors that also affect the degree of dissolution. This motivates in-depth study of leaching due to concerns over the environmental impact on either the safe disposal of IBA, or during the utilisation of IBA.

2.5.1 Physical aspects of leaching

The main factors that influence the leaching of IBA are particle size and porosity of IBA, degree of mixing between leachant and IBA, and temperature. Dissolution of elements will generally increase with increase in surface area and porosity (Van der

Sloot et al., 1997). This is due to the greater contact between the leachant and IBA. In determining the leachability of elements from IBA, the leaching result is more reproducible when equilibrium is reached during the contact between the leachant and IBA. Sufficient contact time for mixing will ensure that equilibrium of the leaching system is reached (Chandler et al., 1997). The presence of mixing will further ensure the homogenisation of the leachant and IBA. However, if the mixing is not aggressive, equilibrium condition may not be achieved in the required time frame. In leaching standards, the contact time is usually specified together with the type of mixing device. And leaching is usually carried out at room temperature.

2.5.2 Chemical aspects of leaching

The difference in pH has been found to affect the leaching behaviour of elements from IBA (Van der Sloot et al., 1997; Chandler et al., 1997). For example, at neutral pH, the leaching of Pb and Zn from IBA is the lowest but increases at low and high pH. This type of element is known as amphoteric element. On the other hand, leaching of soluble salts like NaCl is independent of pH. Therefore, the pH of the leachant used to study the leaching behaviour of IBA will not be comparable to another leachant with a different pH.

Leaching results are also not comparable when leaching tests are performed under different liquid-to-solid (L/S) ratios. When the leachate concentration (expressed in mg/L) is compared to regulatory requirements such as WHO drinking water, confusion arises when different L/S ratios produce different results. This can be resolved by converting the leaching result from element concentration in mg/L to element release in mg/kg, which expresses the mass of element dissolved to per unit dry mass of IBA subjected to leaching. Although this conversion allows the comparison of leaching results done using different L/S ratio, solubility controlled constituents are greatly influenced by the L/S ratio used in leaching tests. For example in Figure 2-1, Si shows the same leachate concentration for the different L/S ratios investigated (top right graph). However, when the leaching results are expressed in release, Si actually leaches more as the L/S ratio increases (top left graph).

Figure 2-1: Illustration of solubility versus availability control of leaching. Data expressed in mg/kg reflect availability control, when data for different L/S ratios coincide (e.g. Cl). Data expressed in mg/L reflect solubility control when data for different L/S ratios coincide (e.g. Si) (Van der Sloot et al., 1997)

2.5.3 Leaching tests

Leaching standards were developed in recognition of the influences from the external factors discussed earlier. To ensure the leaching data done by different laboratories are comparable, leaching tests are standardised so as to minimise the influence from external factors. This allows the leaching results to be compared and the analysis will then be solely based on the intrinsic leaching behaviour of IBA. However, due to the presence of several leaching factors, numerous leaching tests were developed to cover all aspects of leaching. Two leaching standards are chosen for this research to evaluate the effect of accelerated carbonation on the leaching of IBA.

Batch leaching test: EN 12457-2

This European standard uses deionised water as the leachant at L/S 10. The pH of the leachate will then be the inherent pH of IBA. The requirement for the particle size of IBA is less than 4 mm. The portion of the IBA with particle size larger than 4 mm is allowed to be crushed. The mixing device is recommended to be rotating at 360° and at 10 rpm. The mixing duration is set at 24 hours, as this has been validated that near-equilibrium condition is reached between the leachant and IBA.

This European standard was developed as a compliance test. Hence, this leaching test is simple and takes shorter time to conduct, compared to other leaching tests which may simulate the actual condition during the utilisation of IBA. Toxicity characteristic leaching procedure (TCLP) was developed by US EPA and like EN 12457-2, it is a batch leaching test. However, the leachant for TCLP is acetic acid, which is to simulate leaching of IBA if it were mixed with food waste in a landfill. Since the purpose of this study is to evaluate the changes in leaching behaviour of IBA after accelerated carbonation, and IBA will not be mixed with food waste or be in extreme acidic condition, EN 12457-2 is chosen over TCLP.

pH-static test: CEN/TS 14429

This European standard evaluates the influence of pH on the leaching behaviour of IBA, so at least 8 bottles with different pH are tested at the same time. The L/S is fixed at 10 but the concentration of the acid or base used to reach the different pH for the 8 bottles are pre-determined. The total mixing duration is 48 hours, rotating at 360° and at 10 rpm. To ensure that equilibrium condition is reached within this time frame, the recommended particle size is less than 1 mm.

Unlike EN 12457-2, pH-static test falls under the category of basic characterisation. This means that this leaching test is not used to determine whether the IBA complies with a certain regulation or criteria. It is done to understand the fundamental leaching behaviour of IBA as affected by pH and the acid/base consumption to reach the required pH.

2.6 Effect of carbonation on leaching

Some researchers used material analytical techniques and mineralogical studies to examine IBA in greater detail to understand the possible carbonation mechanisms (Zevenbergen et al., 1996; Piantone et al., 2004; Wei et al., 2011), and the relationship between carbonation and leaching (Eighmy et al., 1994; Arickx et al., 2008; Bayuseno and Schmahl, 2010).

During natural weathering of IBA, the first observable change is the release of heat as the hydrolysis of metal oxides is an exothermic reaction (Chandler et al., 1997). The pH will then decrease from alkaline range to neutral range, due to the reaction between CO_2 and the alkaline metals, thus reducing the concentration of hydroxides (Rendek et al., 2006). This is then followed by the formation of new minerals, such as carbonates, and dissolution of minerals. All these changes have been found to change the leaching behaviour of IBA and these are discussed in details in the following, in terms of the heavy metals.

The leaching of IBA is a very complex system to study due to the heterogeneous nature of the material. The relationship between the factors affecting the leachability of IBA can be inter-related, and Figure 2-2 has summed up the complexity in a simple diagram.

Figure 2-2: Simplified leaching system that shows the inter-relationship between the different factors (Chandler et al., 1997).

2.6.1 Ca

Although Ca is not considered a heavy metal, the leaching behaviour of Ca was studied as it is one of the major constituents leached from IBA. Comans and Meima (1994) found that Ca-minerals played a dominant role in controlling the pH of IBA, which then indirectly influenced the leaching of other trace elements from IBA. As IBA forms carbonates during natural weathering, Comans and Meima (1994) proposed that heavy metals such as Cd, may be sorbed on the newly formed calcite, thus reducing Cd leaching.

2.6.2 Pb and Zn

Accelerated carbonation of IBA was reported to be beneficial to both Pb and Zn by several papers (Freyssinet et al., 2002; Fernández Bertos et al., 2004a; Arickx et al., 2006). Table 2-2 summarises some of the studies done. The studies showed that regardless of the operating conditions used for accelerated carbonation and the leaching tests used to evaluate the efficiency of carbonation treatment, the reduction in Pb and Zn leaching can be up to two orders of magnitude. Meima and Comans (1999) suggested two possible reasons for the reduction in the leaching of Pb and Zn: firstly, it was due to the drop in pH after IBA carbonated as the solubility of Pb and Zn in IBA were dependent on pH; secondly, Pb and Zn had high affinity for sorbent minerals that were precipitated during carbonation.

Table 2-2: Summary of reduction in Pb and Zn leaching from IBA after accelerated carbonation.

Reference	Conc. of CO ₂	Leaching test	Effect
Fernández-Bertos et al. (2004a)	100%	EN 12457-2	Pb: 50-100mg/kg → <1mg/kg Zn: 10mg/kg → <1mg/kg
Arickx et al. (2006)	10%	EN 12457-2	Pb: 7.62mg/kg → 0.60mg/kg Zn: 3.76mg/kg → 1.63mg/kg
Freyssinet et al. (2002)	aging	Collection of leachate	Pb: 9.6mg/L → <25µg/L Zn: 0.8mg/L → <25µg/L

2.6.3 Cr and Cu

The reduction in the Cr leaching after accelerated carbonation was not significant and may be dependent on the degree of carbonation. Todorovic et al. (2006) reported a slight decrease in Cr leaching after moderate carbonation but Cr leaching increased if severe carbonation was used. On the other hand, Van Gerven et al. (2005) reported an increase in Cr leaching after a short period of carbonation but decreased with increasing carbonation duration.

Generally, most literature found that carbonation reduces the leaching of Cu. The mechanism for the reduction in Cu leaching has been widely studied (Meima et al., 2002; Van Zomeren and Comans, 2004; Dijkstra et al., 2006; Arickx et al., 2010). Meima et al. (2002) suggested that the reduction in Cu leaching after carbonation could be due to the sorption of Cu onto Al-minerals that precipitated during carbonation. Similarly, Dijkstra et al. (2006) and Arickx et al. (2010) proposed that secondary minerals formed after carbonation played a role in the reduction of Cu but found that the reduction was indirectly due to the sorption of fulvic acid to Fe/Al (hydr)oxides (secondary minerals formed after carbonation). Since many researchers have suggested that the presence of fulvic acid increased the solubility of Cu due to the formation of organic complexes (Van Zomeren and Comans, 2004; Olsson et al., 2007), the reduction in the mobility of fulvic acid after carbonation would also contribute to the reduction of Cu leaching.

2.6.4 Other trace elements

Some trace elements, such as As, Mo and Sb, are capable of forming oxyanions (negatively charged species containing O), which are more soluble than their cationic species (Cornelis et al., 2008). Similar to Cu, the reduction in mobility of As, Mo and Sb have been reported to be due to the adsorption to ferric oxide at high pH, but competing anions like carbonate would result in desorption (Cornelis et al., 2008). Cornelis et al. (2006) also suggested that ettringite acts as a sink for Sb and further carbonation will increase Sb mobility due to the dissolution of ettringite.

2.6.5 Highly soluble salts

According to Kirby and Rimstidt (1994), highly soluble salts exhibit rapid dissolution during leaching tests and the concentration drops only after depletion of the soluble phase. Components that constitute highly soluble salts include Na, K, Ca, SO_4^{2-} , and Cl^- , of which Ca and SO_4^{2-} have the highest concentration in the leachate (Chandler et al., 1997). It has been reported that the carbonation of IBA has no effect on the leaching behaviour of Cl^- (Todorovic et al., 2006). A direct and inexpensive method to improve the leaching concentration of Cl^- is to wash IBA with water (Todorovic and Ecke, 2006b). The leaching trend of SO_4^{2-} after carbonation was observed to be different from Cl^- . Meima and Comans (1997) found that carbonation may have caused the decomposition of ettringite in IBA to form soluble gypsum, resulting in increased SO_4^{2-} leaching.

CHAPTER 3: MATERIALS AND METHODS

3.1 Sampling of IBA

All the IBA used in this research was collected from Tuas South Incineration Plant (TSIP) and Senoko Waste-to-Energy Plant (SWTEP). TSIP is Singapore's largest incineration plant, with a capacity of handling 3,000 tonnes of MSW per day, while SWTEP is designed to handle 2,100 tonnes per day. These two incineration plants were selected for this research as the plants receive slightly different composition of waste. TSIP receives predominantly industrial waste, in addition to residential waste, while SWTEP receives mostly residential waste.

IBA was collected at a location along the conveyor belt before the magnetic separator. To ensure a representative sample was collected, the sampling location was selected based on both the recommendation from Chandler et al. (1997) and the incineration plants' layout. For TSIP, IBA was collected from a falling stream (Figure 3-1a). The sampling tool used to collect the IBA from the falling stream was custom made to be as long as the width of the conveyor belt. For SWTEP, there is no standing platform next to a falling stream. So IBA was collected by shoveling a full cross-section cut from a moving stream (Figure 3-1b). Around 50 kg of wet IBA was collected. IBA was not sampled directly from bottom ash pits because freshly quenched IBA eventually become mixed with IFA at the bottom ash pits. However, due to the design of both incineration plants, freshly quenched IBA still consists of grate siftings, boiler and economiser ash.

Figure 3-1: IBA sampling location within (a) TSIP (white arrow indicates the IBA falling stream) and (b) SWTEP.

3.2 Handling of IBA

Immediately upon collection, a small portion of the wet IBA was dried at 105°C for 1 day to measure its moisture content. The remaining IBA was dried at 40°C for 3 days to minimise further weathering and leaching from taking place. A lower temperature was used to dry IBA for the experimental works so as to minimise the loss of volatile constituents, which would otherwise result in lower leaching from these constituents. The dried IBA was then sieved into four size fractions, using automatic sieve shaker: 0-2 mm, 2-4 mm, 4-20 mm and 20-50 mm. The weight of each size fraction was recorded, including the oversized fraction, i.e. >50 mm. However, the oversized fraction was not included in this research. Ferrous and non-ferrous metals were manually removed from all the size fractions, except 0-2 mm, and their weight was recorded.

All the size fractions were further crushed and ball-milled to <425 μm . By doing so, the influence from the morphological difference between different size fractions on carbonation efficiency can be minimised, and the consequent effect on metal leaching comes mainly from the chemical and mineralogical differences between different IBA samples.

3.3 Analysis

3.3.1 Total element content

Untreated IBA was analysed for total element content by digesting IBA with aqua regia followed by HF acid. The solution was then analysed for cations using Inductively Coupled Plasma – Mass Spectrometer (ICP-MS Nexlon 300D, Perkin Elmer) and anions using Ion Chromatography (IC 882 Compact IC Plus, Metrohm).

3.3.2 Total inorganic carbon content

The amount of carbonate content in IBA was determined by Analytik Jena Multi N/C 2100/2100S analyser (solid module). To obtain total carbon content (TC), a small amount of the sample was weighed onto the quartz boat and combusted at 900°C. The amount of CO₂ released during the combustion was detected by nondispersive infrared sensor in the analyser. To obtain total organic carbon (TOC) of IBA, the sample was acidified using 2M HCl to remove the inorganic carbonate content before combustion. The total inorganic carbon (TIC) content of IBA was obtained by subtracting TOC from TC. TC and TOC analysis were conducted in triplicates. The absolute increase in TIC is defined as the degree of carbonation (Eq. 3-1), which is determined by subtracting TIC of the untreated sample from the TIC at the sampling time t.

$$\text{Degree of carbonation (mg/g)} = \text{TIC}_t - \text{TIC}_{\text{untreated}} \quad (\text{Eq. 3-1})$$

3.4 Leaching Tests

Two leaching tests were used to study the leaching behaviour of IBA. After leaching, the leachates were filtered through 0.45 µm nylon membrane and analysed for pH, dissolved organic carbon (DOC), heavy metals and soluble salts. The pH of the leachate was measured by DGi115-SC pH electrode connected to Mettler-Toledo G20 Compact Titrator. The Analytik Jena Multi N/C 2100/2100S (liquid module) was used to determine the DOC content. Soluble salts were analysed by Dionex ICS-1100 RFIC Ion Chromatography (IC) System. The concentrations of heavy metals were determined using Inductively Coupled Plasma – Optical Emission Spectrometer (ICP-OES) from Perkin Elmer Optima 8300. The

concentrations of most of the heavy metals in the IBA leachate were found to be below the detection limit of ICP-OES, hence only the heavy metals shown in Table 3-1 were discussed in this study.

Table 3-1: Detection limits of heavy metals analysed by ICP-OES.

Heavy metals	Detection limit (µg/L)
Cr	10
Cu	5
Mo	10
Pb	5
Sb	10
Zn	5

3.4.1 EN 12457-2

15 ± 0.02 g of dried IBA was mixed with 150 ± 1 ml of deionised (DI) water in a 250 ml polypropylene bottle to obtain a liquid to solid ratio (L/S) of 10 L/kg. The capped bottle was then clamped in a rotary device and agitated in 360° for 24 hours. Triplicate leaching was carried out for each sample.

3.4.2 CEN/TS 14429 (pH-static test)

8 portions of dried IBA, each weighing 15 ± 0.02 g, were leached with leachants containing different amount of acid to reach an end pH value ranging from around 4 to 12. The last pH value was based on the inherent pH of IBA. No base was added to further increase the pH. The L/S ratio was fixed at 10 L/kg. A preliminary leaching test was first carried out to determine the amount of acid was required to add to IBA to reach the relevant pH values. The total contact time between the leachant and IBA was 48 hours, mixed in a rotary device.

CHAPTER 4: CHARACTERISATION OF IBA

4.1 Introduction

In Singapore, incineration of MSW is used in parallel with recycling. For household waste, recycling is on volunteering basis. After the recyclables are segregated, most incineration plants burn waste in the as-received condition, i.e. no further sorting is done before incineration. Hence, this gives rise to a highly heterogeneous waste input to the incineration plants.

IBA accounts for 85-95% of all the residues generated after MSW incineration (Chandler et al., 1997). Depending on the waste that is fed into the incineration plants and the different combustion conditions of individual plants, the physical and chemical characteristics of IBA varies among countries and seasons. IBA can be considered a heterogeneous material, consisting of fine powder-like particles to coarse remains of incombustible MSW such as glass, ceramics, minerals and unburned organic matter (Chimenos et al., 1999).

Before IBA can be utilised in an environmentally safe manner, the physical and chemical characteristics of IBA must be clearly investigated. This includes monitoring the variation of IBA characteristics with time. This study aims to evaluate the statistical characteristics of Singapore's IBA, so as to provide a knowledge base for effective IBA treatment. To determine the temporal variation on the characteristics of IBA in Singapore, IBA was collected over a 6 months period in 2013.

4.2 Materials and Methods

The procedure for the sampling and analysis of IBA was as detailed in Chapter 3. The sampling of IBA was carried out over a 6 months period in 2013 for both incineration plants. In the first month, IBA was collected daily, except on weekends. For the rest of the five months, IBA was collected once a week. In all, a total of 40 samples were collected for this study. The procedure for the handling of IBA for

this characterisation study is shown in the schematic diagram (Figure 4-1). After removing the ferrous and non-ferrous metals, the size fractions greater than 4 mm was crushed using a jaw crusher to <4 mm. After crushing, the four size fractions were recombined according to their original percentage into subsamples for further testing. This was done by using a sample splitter to homogeneously reduce the sample size of each size fractions before recombining. The characterisation of IBA includes moisture content, particle size distribution, LOI, TOC, total trace element content and leaching test based on EN 12457-2.

Figure 4-1: Sample preparation process of IBA for characterisation.

4.3 Results and Discussion

4.3.1 Physical characteristics

Figure 4-2 shows the particle size distribution of IBA collected from TSIP and SWTEP. The particle size distribution from both incineration plants were found to be mostly concentrated in the 0-2 mm and 4-20 mm size fractions, where their weight percentage ranged from 30.6-31.6 wt% and 38.0-47.9 wt% respectively.

Figure 4-2: Particle size distribution of (a) TSIP, and (b) SWTEP. The bottom and top of the box is 25 and 75 percentile respectively. The band inside the box is the median and the tiny box is mean. The end of the whiskers is 5 to 95 percentile. The cross is the outliers and the stars represent the minimum to maximum values.

LOI values give an indication on the combustion efficiency of incineration plants. In Singapore, the LOI value is required to be less than 3%, which explains the average low readings (Table 4-1) compared to reported values from other incineration plants, such as 2.1-9.8% for Catalonia in Spain (Izquierdo et al., 2002), and 5.5% and 7.2% for VALOR-SUL and LIPOR II in Portugal, respectively (Monteiro et al., 2008). As some factors unrelated to organic content could contribute to mass loss in the LOI test, another analysis using Analytik Jena Multi N/C 2100/2100S analyser (solid module) was performed to evaluate the organic carbon content in finely ground IBA. The TOC result from this analysis is solely measuring the amount of CO_2 released during the combustion, which was then detected by nondispersive infrared sensor in the analyser. The average TOC for the two plants was thus found to be 0.73% and 0.64%. This is also found to be lower than those reported by Rendek et al. (2007) where the lowest TOC value was 0.88%.

Table 4-1: Physical characteristics of IBA samples.

	Number of samples	TSIP		SWTEP	
		Range	Average	Range	Average
Moisture content (%)	40	11.9-20.9	16.2	15.0-25.1	18.6
Ferrous content (wt%)	40	6.9-15.3	11.2	6.3-11.9	10.0
LOI (%)	35	0.29-2.12	1.09	0.50-4.65	1.15
TOC (%)	40	0.48-1.91	0.73	0.30-1.34	0.64

4.3.2 Total trace element content

Table 4-2 shows the average total trace element content of Singapore's IBA (n=40) compared with other countries (Chandler et al., 1997). Generally, both incineration plants produced IBA with similar composition, except for elements like Cd, Mn, Pb and Sb, whereby the average differed by an order of magnitude. Cd, Pb and Sb were present in higher concentration in SWTEP than TSIP IBA. These elements are commonly used in batteries, a common household waste, which could explain their higher concentration in SWTEP as SWTEP receives predominantly household waste while TSIP receives more industrial waste. Mn is used mainly as an alloy for metallurgy, which could be contributed from steel related waste from industry, resulting in higher concentration in TSIP IBA. Overall, the tested elements are found to fall into the range reported by Chandler et al. (1997).

Table 4-2: Comparison of Singapore's IBA composition (in terms of trace elements) with other countries.

Element (mg/kg)	TSIP	SWTEP	Range reported by Chandler et al., 1997
Ag	4.04	4.31	0.29-36.9
As	34.38	28.57	0.12-189
B	244	285	38-510
Ba	2207	1615	400-3,000
Be	1.15	0.95	-
Cd	5.19	28.61	0.3-70.5
Co	26.67	40.55	6-350
Cr	178	161	23-3,170
Cu	1463	1373	190-8,240
Hg	0.48	0.23	0.02-7.75
Mn	1228	707	83-2,400
Mo	44.97	13.86	2.5-276
Ni	134	113	7-4,280
Pb	688	1385	98-13,700
Sb	98.53	148	10-432
Se	0.36	0.71	0.05-10.0
Sn	104	176	2-380
Sr	367	676	85-1,000
Tl	0.18	0.15	-
V	41.38	23.32	20-122
Zn	2398	2261	613-7,770

Most of the elements showed narrow variation over the 6 months sampling period. The possible reasons could be that the volume and chemistry of waste feedstock containing these elements was fairly consistent and the mixing of waste in the holding bunker before incineration was helpful in homogenizing the waste to some extent. However, certain elements like Cd, Co, Hg, Pb and Se displayed high coefficient of variation, as can be seen in Figure 4-3.

Figure 4-3: Total trace element contents of 6 months' IBA from (a) TSIP; and (b) SWTEP in Singapore. The bottom and top of the box is 25 and 75 percentile respectively. The band inside the box is the median and the tiny box is mean. The end of the whiskers is 5 to 95 percentile. The cross is the outliers and the stars represent the minimum to maximum values.

4.3.3 Leaching

Leaching test was conducted based on EN 12457-2 for all the IBA collected (n=40). The leaching behavior of untreated IBA and its variation with time are shown in Figure 4-4. A number of trace elements of concerns selected for their toxicity were analysed but only seven of them were within the detection limits of ICP-OES. For Sb, the leachates of the majority of the samples were consistently found to be undetectable and so was not presented here. The trace element concentrations for SWTEP were mostly higher than TSIP, which is surprising as TSIP receives more industrial waste. For example, Pb leaching from SWTEP had a significantly higher average and broader data dispersion than TSIP.

Figure 4-4: (a) TSIP and (b) SWTEP leaching test results based on EN12457-2. The bottom and top of the box is 25 and 75 percentile respectively. The band inside the box is the median and the tiny box is mean. The end of the whiskers is 5 to 95 percentile. The cross is the outliers and the stars represent the minimum to maximum values.

The average leaching levels of 40 samples from TSIP and SWTEP were compared with the landfill disposal criteria and effluent criteria in Singapore in Table 4-3. The comparison with the landfill disposal criteria is made with the understanding that the leaching test used in this study (i.e. EN12457-2) was different from that used in the criteria (i.e. TCLP). The different leachants used in these two leaching tests tend to give rise to different leaching behaviour. This means that although based on EN12457-2, TSIP and SWTEP samples were able to meet the landfill disposal

criteria, the same samples may not meet the criteria if the leaching was done using TCLP. However, comparison can be made with the effluent criteria. Based on the leaching result carried out using EN12457-2, only Cu and Pb were not able to meet the discharge into the watercourse without treatment for both incineration plants, and F⁻ from SWTEP was not able to meet the discharge into the sewer.

Table 4-3: Comparison of landfill disposal criteria and effluent criteria in Singapore to the mean of the IBA leachate (n=40).

Elements (mg/L)	Landfill disposal ¹	Sewer ²	Watercourse ³	TSIP	SWTEP
Ag	5	5	0.1	N.D.	N.D.
As	5	5	0.1	N.D.	N.D.
B	-	5	5	N.D.	N.D.
Ba	100	10	2	0.25	0.59
Be	-	5	-	N.D.	N.D.
Cd	1	1	0.1	N.D.	N.D.
Cr	5	5 (III and VI)	1 (III and VI)	0.061	0.048
Cu	100	5	0.1	0.69	1.14
Fe	100	50	10	N.D.	N.D.
Hg	0.2	0.5	0.05	Not tested	Not tested
Mn	50	10	5	N.D.	N.D.
Ni	5	10	1	N.D.	N.D.
Pb	5	5	0.1	0.98	1.86
Se	1	10	0.5	N.D.	N.D.
Sn	-	10	10	N.D.	N.D.
Zn	100	10	1	0.48	0.80
F ⁻	150	15	-	4.66	17.43
CN (total)	10	2	0.1	Not tested	Not tested
Phenol	0.2	0.5	0.2	Not tested	Not tested
Cl ⁻	-	1000	-	419	822
SO ₄ ²⁻	-	1000	-	788	629
Leaching	TCLP	-	-	EN 12457-2	

N.D. = not detectable by ICP-OES

¹ <http://www.nea.gov.sg/docs/default-source/default-document-library/leaching-test.pdf?sfvrsn=2>

² http://www.pub.gov.sg/general/usedwater/Documents/requirements_UW.pdf

³ <http://www.nea.gov.sg/anti-pollution-radiation-protection/water-pollution-control/allowable-limits>

4.4 Conclusion

The characteristic of Singapore's IBA was evaluated in this study. The results discussed here are a summary of data obtained through a deliberate sampling and testing done over a 6 months period in 2013. The statistical result shows that the total trace element content was found to be within the range of several other countries reported in literature. However, elements like Cd, Co, Hg, Pb and Se exhibited high variation over the investigated sampling period. Pb showed similar high variation in leaching test. The average value of the IBA leachates from both incineration plants were compared to landfill disposal criteria and effluent criteria in Singapore. Cu and Pb from both incineration plants did not meet the criteria for watercourse discharge while F⁻ from SWTEP did not meet the sewer criteria, if no treatment was carried out. This 6 months study has found Pb to be a potential problem in the utilisation of IBA due to its high variation. The treatment method proposed in this study, i.e. accelerated carbonation, will further discuss the efficiency of reducing Pb leaching and other heavy metals.

ACKNOWLEDGEMENT

This research work on characterisation of IBA was funded by National Environment Agency (NEA) of Singapore.

PUBLICATION

X.L. Sun, **W.Y. Lin**, L. Ge, I.J.R. Ho, O.A. Mohamed Noh, K.S. Heng, S.Y. Choy, M.Q. Nguyen, X.D. Zhou, T. Aung, A. Liu, J.-Y. Wang (2014). "Sampling and Characterization of Singapore's Municipal Solid Waste Incineration Bottom Ash." Fifth International Symposium on Energy from Biomass and Waste, 17-20 November 2014, San Servolo, Venice, Italy.

CHAPTER 5: INFLUENCE OF MOISTURE CONTENT AND TEMPERATURE ON THE EFFICIENCY OF ACCELERATED CARBONATION OF IBA

5.1 Introduction

Natural weathering, a simple IBA treatment process, is one of the treatment technologies commonly used in countries that utilise IBA (Chandler et al., 1997). However, natural weathering is a slow process that takes months to complete. In view of the difficulty of finding a sufficient large space to naturally weather IBA in land-scarce Singapore, accelerated carbonation would be a more attractive alternative treatment method. The natural weathering process can be shortened through optimising operating conditions, such as concentration of CO₂, pressure, moisture content, and temperature (Costa et al., 2007), to accelerate the carbonation process.

The influence of these operating conditions on the kinetics of accelerated carbonation has been studied individually. However, the range of the optimum operating conditions is still wide and varies across studies. Fernández Bertos et al. (2004a) found that the optimum moisture content was 30-40% for IBA size fraction <710 µm. Van Gerven et al. (2005) carried out accelerated carbonation treatment on 0.1-2 mm size fraction of IBA. In terms of leaching results, the optimum moisture content and temperature was 13-25% and 50°C, respectively. Rendek et al. (2006) reported the optimum moisture content for <4 mm IBA was 15% at a pressure of 2 bar using pure CO₂. The reasons for the slight difference in the optimum moisture content reported in these studies could be attributed to the different IBA size fractions and temperature studied. Furthermore, although steps were taken to ensure that the moisture content remained unchanged in these studies, Van Gerven et al. (2005) showed that moisture content decreased over the carbonation period. This would have an impact on the efficiency of carbonation.

The objective of this study is to investigate the influence of operating conditions on the degree of carbonation and the leaching behaviour as a function of carbonation time. This investigation was carried out using IBA size fraction 0-2 mm to obtain the optimum operating condition for further study on other size fractions (discussed in Chapter 6). Since industrial emission with 10-20% CO₂ has been suggested to be the source of CO₂ for accelerated carbonation (Arickx et al., 2006), this study used 20% CO₂ at atmospheric pressure as it would be more realistic than using pure CO₂. The study on the factors influencing the degree of carbonation was chosen to focus on moisture content and temperature. These operating conditions, i.e. fixed CO₂ concentration, varying moisture content and temperature, were selected for this study in consideration of minimising energy and cost of the process. Lastly, this study aims to address the possible factors influencing the leaching mechanism by investigating leaching as a function of carbonation time.

5.2 Materials and Methods

5.2.1 Incineration bottom ash

The IBA used for the accelerated carbonation experiment was the same as those discussed in Chapter 4. A single day was randomly chosen from the IBA collected in the first month from SWTEP and TSIP. For this study, only the size fraction 0-2 mm ball-milled to <425 µm was used.

5.2.2 Accelerated carbonation

The accelerated carbonation process was carried out in CO₂ incubator (Sanyo MCO-18AIC). 20% CO₂ at 1 atm was used for all the experiments. The nominal moisture contents were set at 5, 15, 18.8 and 25% in weight percentage. The investigated temperatures were 35, 42.5 and 50°C. In total, 9 sets of experiment were conducted for the investigated nominal moisture content and temperature, as shown in Table 5-1. DI water was added to the dried IBA to obtain the required moisture content. A tray of DI water was placed at the bottom of the incubator to maintain a constant atmospheric humidity. IBA sample was spread on plastic petri dishes to no more

than 2 mm thick. Samples were collected after different carbonation durations at 2, 4, 6, 8, 24, and 168 hours, and the actual moisture content was measured.

Table 5-1: Abbreviation of the 9 sets of carbonation experiment carried out under different operating conditions.

Moisture content \ Temp	35°C	42.5°C	50°C
5%	35C5MC	42.5C5MC	50C5MC
15%	35C15MC	42.5C15MC	50C15MC
18.8%	-	42.5C18.8MC	-
25%	35C25MC	-	50C25MC

5.2.3 Analysis

The total element content analysis for this study was carried out as detailed in Section 3.3.1. The degree of carbonation was determined by subtracting TIC of the untreated sample from the TIC at the sampling time t (details in Section 3.3.2), as shown in Eq. 3-1.

$$\text{Degree of carbonation (mg/g)} = \text{TIC}_t - \text{TIC}_{\text{untreated}} \quad (\text{Eq. 3-1})$$

Both EN 12457-2 and CEN/TS 14429 leaching tests were used for this study. EN 12457-2 was used to evaluate the leaching behaviour of IBA before and after carbonation as a function of time. The leaching test was carried out in triplicates for each sample after different carbonation durations. CEN/TS 14429 was done to investigate IBA leaching dependence on pH of leachant. This pH-static leaching test was carried out for untreated samples only.

5.2.4 Linear correlation coefficient

The relationship between leachability and its possible influencing factors was evaluated by calculating the linear correlation coefficient, i.e. Pearson's R. Pearson's R is a measure of the strength of the relationship between two random variables. The value of the correlation coefficient varies between -1 to +1, whereby ± 1 means

the two variables have absolute positive or negative correlation, and 0 means no correlation. The Pearson's R was calculated using Originlab software.

5.3 Results and Discussion

5.3.1 Total element content

Table 5-2 shows the total element content of IBA from the two incineration plants. Generally, both plants had similar elemental composition in the 0-2 mm size fraction, except for Cd, Fe, Mn, Mo, Sb, Sn and Cl⁻, which differed by an order of magnitude. Of the aforementioned elements, Cd, Sb, Sn and Cl⁻ were found to be in higher concentration in SWTEP sample while Fe, Mn and Mo were found to be in higher concentration in TSIP sample. This trend was similar to the average total trace element content results, which consists of all the four size fractions, as discussed in Section 4.3.2.

Table 5-2: Total element content (mg/kg) of 0-2 mm size fraction of IBA from incineration plants SWTEP and TSIP.

Element (mg/kg)	SWTEP	TSIP
	0-2 mm	0-2 mm
Ag	19	18
Al	32,467	32,033
As	20	64
Ba	81	65
Be	0.9	1.2
Ca	180,333	139,667
Cd	11	5.3
Co	52	48
Cr	235	206
Cu	2,453	2,437
Fe	51,467	111,000
K	9,270	9,857
Mg	10,113	10,633
Mn	895	1,600
Mo	17	121
Na	15,333	13,067
Ni	183	169
Pb	611	199
Sb	246	85
Sn	161	95
Sr	340	327
Ti	6,720	5,267
V	27	55
Zn	3,073	4,050
Cl ⁻	11,200	5,900
SO ₄ ²⁻	8,307	6,987

5.3.2 Degree of carbonation as a function of time

Figure 5-1 shows the degree of carbonation under different operating conditions, as a function of carbonation time. Samples with 5% and 15% moisture content both showed significant increase in the degree of carbonation after 2 hours of carbonation, regardless of temperature and source of IBA. Beyond 2 hours of carbonation, the increase in degree of carbonation was minimal. 18.8% moisture content showed similar trend at 42.5°C. Only samples with 25% moisture content showed an initial lag in carbonation degree. This shows that 25% moisture content was too high, hindering the diffusion of CO₂ through water to reach IBA particle surface for effective carbonation, in particular for IBA ground to <425 µm. But they subsequently caught up with other samples with lower moisture content after 8 hours of carbonation, and reached a plateau thereafter. The onset of plateau in the degree of carbonation implies that the samples had reached saturation in carbonation under the given operating conditions. This saturation in carbonation is due to the formation of a layer of calcite (CaCO₃) around the IBA particle, which according to Sun et al. (2008), causes the rate of reaction to decrease as the CO₂ diffusion is now dependent on the porosity of the newly formed calcite layer. With prolonged carbonation, i.e. 1 week of carbonation, the IBA from the same plant reached similar degree of carbonation under different operating conditions. This could be associated with the amount of Ca available for carbonate formation. The total Ca content for 0-2 mm size fraction of SWTEP and TSIP samples were 180,333 mg/kg and 139,667 mg/kg respectively (Table 5-2), which corresponds to higher degree of carbonation attained by SWTEP sample.

Figure 5-1: Degree of carbonation as a function of time for SWTEP and TSIP samples at various operating conditions.

This study has shown that 2 hours of carbonation was sufficient for the samples to reach a relatively high degree of carbonation that was close to the degree of

carbonation observed after 1 week of carbonation. Although the degree of carbonation at 2 hours was not the highest in this study, 2 hours of carbonation was the most efficient in terms of the rate of carbonation. In terms of heavy metals leaching, 2 hours of carbonation was also found to be effective in causing significant reduction in leaching (refer to Section 5.3.5). Hence, 2 hours of carbonation was chosen as one of the optimum operating conditions. The optimum moisture content and temperature were then selected based on the highest degree of carbonation at 2 hours of carbonation. Figure 5-2 shows that both SWTEP and TSIP samples had the highest degree of carbonation at 15% moisture content. However, the optimum temperature for SWTEP and TSIP was different, at 35°C and 50°C respectively.

Figure 5-2: Comparison of degree of carbonation for (a) SWTEP and (b) TSIP samples at 2 hours of carbonation.

These findings were similar to the study done by Van Gerven et al. (2005), whereby they reported that the optimum moisture content and temperature was 13-25% and 50°C respectively, for IBA 0.1-2 mm size fraction. However, the higher moisture content of 25% reported by Van Gerven et al. (2005) did not show any lag at the beginning of carbonation, unlike in this study. This could be due to the difference in particle size as the IBA used in Van Gerven et al. (2005) was not ground (i.e. 0.1-2 mm). Compared to this study, IBA was ground to <425 µm, of which 25% moisture content was shown to be too high for effective carbonation. Baciocchi et al. (2010) reported that the significant carbonate increase lasted 8 hours and the finest size

fraction (<0.150 mm) had approximately 14% of CO_2 uptake. In the study done by Van Gerven et al. (2005) on IBA size fraction 0.1-2 mm, the significant increase in carbonate content occurred in the first 6 hours of carbonation with an increase of around 100%. Compared with other studies, this study observed the steep increase in degree of carbonation after only 2 hours of carbonation, followed by a plateau. Furthermore, the degree of carbonation after 2 hours of carbonation was 1.3 times higher, compared to the degree of carbonation at 0 hour, under the operating condition of 50°C and 15% moisture content for TSIP sample.

5.3.3 Effect of actual moisture content on rate of carbonation

The initial retardation in carbonation for samples with 25% moisture content showed that 25% moisture content was too high for effective carbonation to take place for IBA with particle size <425 μm . The duration of lag for 35°C lasted longer than 50°C , for both SWTEP and TSIP samples. The initial retardation and the difference in the lag period for 25% moisture content can be explained by observing the actual moisture content of the samples. It was found that the moisture content changed throughout the carbonation period (Figure 5-3).

Generally, moisture content decreased during the first 8 hours of carbonation, except for samples with 5% moisture content of which moisture was gained. As a tray of DI water was placed inside the incubator, the evaporation of water had resulted in an atmosphere saturated with moisture within the enclosed environment. Moisture was then gained by samples with low moisture content, i.e. 5%, but not by samples with higher nominal moisture content. At 50°C , the rate of moisture gain for 5% moisture content was the slowest while the rate of moisture loss for 25% moisture content was the highest. This is logical since at 50°C , water tends to evaporate. After 8 hours of carbonation, the moisture content of all the samples with different nominal moisture contents would coincide at certain time between 8 and 24 hours of carbonation, with respect to their temperatures. This equilibration in moisture content continued to the end of 1 week of carbonation. Again, at 50°C , the actual moisture contents after 24 hours of carbonation for all the three nominal moisture contents were the lowest among the three temperatures.

This change in the moisture content during carbonation had an impact on the initial rate of carbonation. This study has shown that by using an unfavourable high nominal moisture content of 25%, significant carbonation will only take place after the moisture content has decreased to a certain threshold. For 35°C, the sharp increase in degree of carbonation for 25% moisture content occurred between 6 to 8 hours, which corresponded to an actual moisture content decrease from 17.1% to 11.6% for SWTEP sample, and from 20.3% to 17.7% for TSIP sample. As for 50°C, the increase in degree of carbonation started after 2 hours of initial lag, whereby the actual moisture content had decreased to 14.0% and 21.4% for SWTEP and TSIP samples respectively. Thus, for significant carbonation to take place, the actual moisture content range should be 12-17% for SWTEP sample and 18-21% for TSIP sample. This observation is in agreement with samples with 18.8% moisture content, whereby the carbonation did not display an initial lag like those with 25% moisture content. Hence, 18.8% moisture was still effective as nominal moisture content for significant carbonation to take place. However, after factoring in the change in moisture content, the carbonation experiment has shown that the best nominal moisture content for the highest rate of carbonation was 15% for IBA of particle size <425 µm. On the other hand, although 5% nominal moisture content did not show any lag in carbonation, the degree of carbonation was lower compared to 15% nominal moisture content and remained lower compared to other moisture contents, as the gain in moisture was not sufficient to reach the threshold level discussed earlier.

This study has shown that the initial rate of carbonation was strongly dependent on the nominal moisture content of IBA. The rate of moisture loss or gain seems to be affected by the carbonation temperature, which in turn indirectly affects the rate of carbonation. The implication of this study is that the carbonation temperature may be determined by the flue gas used as the source of CO₂ for the accelerated carbonation process. If the temperature of the flue gas is high, e.g. >50°C, higher moisture content would have to be used to compensate for the decrease in moisture. The disadvantage is the lag in the initial rate of carbonation. However, this study

has shown that with time, the moisture content will decrease to the optimum threshold and significant carbonation will take place.

Figure 5-3: Degree of carbonation (top) and corresponding actual moisture content (bottom) for SWTEP and TSIP samples at various operating conditions.

5.3.4 pH profile as a function of time

Figure 5-4 shows the change in pH as a function of carbonation time. The pH of untreated IBA was found to be 12.4 and 12.6 for SWTEP and TSIP samples respectively. There was a significant decrease in pH for most of the samples during the first 2 hours of carbonation period, at least 1 to 2 units of reduction. The pH continued to decrease with carbonation time, reaching pH 8.5 at the end of 1 week of carbonation for both sources of IBA.

The decrease in pH was dependent on the degree of carbonation for the different operating conditions investigated, as shown by the high correlation coefficient in Figure 5-5. This observation shows that a lower pH can be achieved by applying the optimum operating conditions to obtain the highest degree of carbonation.

Figure 5-4: pH as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

Figure 5-5: Correlation between pH and degree of carbonation for (a) SWTEP and (b) TSIP samples.

5.3.5 Leaching profile as a function of time

The evolution of leaching as a function of carbonation time was monitored by carrying out leaching tests at each sampling time. Most of the trace elements were found to be below the detection limit by ICP-OES. Therefore, only certain trace elements are discussed here as these are regulated in most countries that utilise IBA.

Pb and Zn

Both Pb and Zn showed the most significant reduction in leaching after carbonation. The leaching trend for both Pb and Zn were not shown in figures as most of the concentrations were below the detection limit of ICP-OES (i.e. $<5 \mu\text{g/L}$). In untreated SWTEP and TSIP samples, the release of Pb was 30.05 mg/kg and 0.36 mg/kg respectively, which coincides with the higher total Pb content in SWTEP sample. After only 2 hours of carbonation, Pb was below the detection limit in the leachate from both sources of IBA, regardless of the degree of carbonation. Zn leaching was reduced by ~97% in the same period of carbonation. The reduction in the leaching of Pb and Zn could be due to the decrease in pH after carbonation, as suggested by Meima and Comans (1999). The pH for both SWTEP and TSIP samples decreased from an average of 12.5 to 10.2 after 2 hours of carbonation. The

pH-static tests of SWTEP and TSIP samples have shown that Pb and Zn leaching were not detectable by ICP-OES below pH 11.

Cu and DOC

Similar to Pb and Zn, Cu leaching decreased significantly after just 2 hours of carbonation and reached a plateau with further carbonation (Figure 5-6), regardless of the operating conditions. A possible factor influencing the leaching mechanism of Cu could be the degree of carbonation, which results in the formation of less soluble carbonate, as shown from the relatively high correlation coefficient in Figure 5-7 (a, c). The Cu leaching as a function of measured pH from carbonated samples were also compared to the pH-static leaching of untreated samples (Figure 5-7 (b, d)). It can be seen that below pH 10, Cu leaching continued to decrease for the carbonated samples whereas under the influence of pH, Cu leaching has increased. This decrease in Cu leaching as pH decrease with carbonation time showed the possibility of Cu forming a less soluble mineral (such as carbonate) during the carbonation process. Hence, pH did not contribute significantly to the decrease in Cu leaching. Van Gerven et al. (2005) had reported similar findings.

Figure 5-6: Cu release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

SWTEP

TSIP

Figure 5-7: Correlation between Cu leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Cu leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.

Many researches had suggested the leaching behaviour of Cu was affected by the presence of DOC in IBA due to Cu affinity to form organic ligands, which increase Cu solubility (Van Zomeren and Comans, 2004; Olsson et al., 2007). Hence, DOC leaching as a function of carbonation time was investigated. Generally, DOC leaching decreased with carbonation time, as shown in Figure 5-8. It is likely that

the decrease in DOC leaching could be due to the adsorption to Fe/Al (hydr)oxides formed during carbonation, as reported by Meima et al. (1999), Dijkstra et al. (2006), and Arickx et al. (2010). This is supported by this study shown in Figure 5-9 that compares the DOC leaching as a function of measured pH from carbonated samples to the pH-static leaching of untreated samples. Similar to Cu, the decrease in DOC leaching was not due to the decrease in pH.

The contribution from both DOC and degree of carbonation would have affected the Cu leaching, however, to different extent. For SWTEP sample, the contribution from DOC (Figure 5-10a) and degree of carbonation (Figure 5-7a) seems to affect Cu leaching equally as the R values were considered high for both factors. For TSIP sample, the contribution from degree of carbonation (Figure 5-7c) seems to be higher than that of DOC (Figure 5-10b), based on the higher R value between Cu leaching and degree of carbonation and lower R value between Cu leaching and DOC. This could imply that while DOC may have influenced Cu leaching, there are other factors, such as degree of carbonation, that contribute more to the decrease in Cu leaching. In the modelling done by Meima et al. (1999), they suggested that malachite ($\text{Cu}_2(\text{OH})_2\text{CO}_3$) and sorption to amorphous Fe/Al (hydr)oxides could be controlling leaching of Cu in carbonated IBA, although the oversaturation with respect to malachite was up to 1.5 orders of magnitude. It is possible that the higher R correlation between the degree of carbonation and Cu leaching for TSIP sample was contributed from the formation of insoluble carbonate mineral like malachite after carbonation.

Figure 5-8: DOC leaching (mg/L) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

Figure 5-9: DOC leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (a) SWTEP and (b) TSIP samples.

Figure 5-10: Correlation between Cu and DOC leaching for (a) SWTEP and (b) TSIP samples.

Oxyanions – Cr, Mo and Sb

Oxyanions refer to elements that form negatively charged species, such as As, Cr, Mo, Sb, Se, V and W (Cornelis et al., 2008). The leaching behaviour of these elements from IBA is not as well studied in literature due to the much lower total element content compared to other elements with higher total element content like Cu, Pb and Zn (Cornelis et al., 2008). However, these elements are now regulated in Europe for the acceptance of waste at landfills (CEU, 2003). Hence, this study discusses the effect of accelerated carbonation on Cr, Mo and Sb as the rest of the

oxyanion forming elements is below the detection limit of ICP-OES in the IBA leachate.

Cr leaching was slightly higher for untreated SWTEP sample than untreated TSIP sample at 3.59 mg/kg and 2.30 mg/kg respectively (Figure 5-11). Unlike Cu, Cr leaching did not decrease for all the operating conditions. Only samples with 15% moisture content consistently showed the most significant decrease in leaching for all the investigated temperatures. However, Cr leaching increased for SWTEP and TSIP samples with 25% and 5% moisture content respectively, which corresponded to lower degree of carbonation as compared to that at 15% moisture content at 2 hours of carbonation. After 1 week of carbonation, Cr leaching decreased for all the samples to concentration below the untreated samples, including those samples that showed an initial increase in leaching. This finding was similar to studies done by Van Gerven et al. (2005) and Rendek et al. (2006), who reported a decrease in Cr leaching with prolong carbonation. Cornelis et al. (2008) suggested that the decrease in Cr leaching could be due to the adsorption by Fe oxides.

Figure 5-12 shows the relationship between Cr leaching with two other factors, i.e. degree of carbonation and pH. The correlation coefficient between Cr leaching and degree of carbonation were relatively low at $R = -0.5765$ and -0.5500 for SWTEP and TSIP samples respectively. Figure 5-12 (b, d) shows that the leaching mechanism of Cr could be more dependent on pH, instead of the formation of carbonate. This is supported by the similarity in the measured pH profile of carbonated sample and pH-static leaching of untreated sample. Furthermore, Figure 5-12 (b, d) shows that Cr leaching increased initially during carbonation due to the slight decrease in pH. After prolonged carbonation, the pH decreased further to around pH 9, whereby the solubility of Cr becomes lower. Hence, to reduce Cr leaching significantly, the pH of carbonated IBA has to reach pH 7, which is the minimum solubility of Cr based on the pH-static leaching test. However, pH 7 cannot be attained through accelerated carbonation treatment alone. The use of chemical agents has to be considered.

Figure 5-11: Cr release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

SWTEP

TSIP

Figure 5-12: Correlation between Cr leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Cr leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.

Mo leaching from untreated TSIP sample was about 6 times higher than that from untreated SWTEP sample (Figure 5-13). This could be due to the higher total Mo content in TSIP sample. Generally, Mo leaching increased during the first 24 hours of carbonation. Van Gerven et al. (2005) reported that Mo leaching from the 0.1-2 mm IBA size fraction after carbonation did not increase significantly, i.e. from 1.1

mg/kg to between 0.8 and 1.2 mg/kg. However, in this study, the increase in Mo leaching was twofold after 2 hours of carbonation under certain operating conditions, especially SWTEP samples. Similar to Cr, Mo showed signs of decrease in leaching after prolonged carbonation, i.e. 1 week of carbonation. However, the decrease in leaching was not significant for SWTEP sample. Regardless of operating conditions, Mo leaching decreased to around the same level as untreated SWTEP sample. In contrast, TSIP sample had greater reduction in Mo leaching after 1 week of carbonation, especially for operating condition 50°C with 25% moisture content.

Figure 5-14 (a, c) shows that the correlation between Mo leaching and degree of carbonation was relatively poor, i.e. $R = -0.0706$ and -0.1541 for SWTEP and TSIP samples respectively. The initial increase in Mo leaching after carbonation could be due to the decrease in pH, as based on the pH-static leaching of untreated samples, the trend in Figure 5-14 (b, d) shows that Mo leaching increased as pH decreased. However, the measured pH profile of carbonated TSIP sample was different from that of SWTEP. Between pH 9-10, some TSIP carbonated samples showed extremely high Mo leaching, which resulted from operating condition 42°C at 15% and 18.8% moisture content. This inconsistent leaching behaviour between SWTEP and TSIP samples may indicate other factor, such as difference in mineralogical composition, is influencing Mo leaching. This will be further discussed in Chapter 7. After prolonged carbonation, the reduction in Mo leaching could be due to Mo adsorption to Fe/Al (hydr)oxides formed after carbonation (Dijkstra et al., 2006). However, again, the reduction in Mo leaching after prolonged carbonation was not consistent between SWTEP and TSIP samples. Hence, the leaching mechanism of Mo cannot be determined at this point yet.

Figure 5-13: Mo release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

SWTEP

TSIP

Figure 5-14: Correlation between Mo leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Mo leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.

Figure 5-15 shows Sb leaching as a function of carbonation time. The concentration of Sb in untreated TSIP sample was below the detection limit of ICP-OES (i.e. $<10 \mu\text{g/L}$) while untreated SWTEP sample released 0.16 mg/kg of Sb. The readings that were found to be below the detection limit were represented by a zero value in the graphs. TSIP samples carbonated at 35°C were not presented here as they were

below the detection limit too. In the first 2 hours of carbonation, most of the samples showed increase in Sb leaching and the amount of release fluctuated greatly for the first 24 hours of carbonation. This was followed by a decrease in Sb leaching after 1 week of carbonation. However, in general, the reduction in Sb leaching did not fall below the untreated level. This observation was also reported by both Van Gerven et al. (2005) and Cornelis et al. (2006), although in these studies, the Sb leaching did not show the same fluctuation as observed in this study. Cornelis et al. (2012) suggested that the increase in Sb leaching after carbonation could be due to Ca leaching from romeites ($\text{Ca}_{1.13}\text{Sb}_2\text{O}_6(\text{OH})_{0.26} \cdot 0.74\text{H}_2\text{O}$). Furthermore, Cornelis et al. (2006) found that at pH below 9, Sb leaching was reduced due to adsorption to hydrous ferric oxides, which could explain the slight decrease in Sb leaching after prolonged carbonation in this study.

The correlation between Sb leaching and degree of carbonation was relatively poor and inconsistent, i.e. a positive relationship for SWTEP but negative for TSIP, as shown in Figure 5-16 (a, c). Similar to Mo, the trend of the pH-static leaching of untreated samples showed that the leaching of Sb increased with decreasing pH (Figure 5-16 (b, d)), which implies that carbonation may unfavourably increase Sb leaching, as this study has shown. Comparing the measured pH profile of carbonated sample with the pH-static leaching of untreated sample, again, suggested the difference in mineralogical composition between SWTEP and TSIP samples may contribute to this difference in leaching behaviour. This will be further discussed in Chapter 7. Similar to Mo, the extremely high Sb leaching found between pH 9-10 (Figure 5-16d), resulted from operating condition 42°C at 15% and 18.8% moisture content.

Figure 5-15: Sb release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

SWTEP

TSIP

Figure 5-16: Correlation between Sb leaching and degree of carbonation for (a) SWTEP and (c) TSIP samples. Sb leaching as a function of measured pH for carbonated sample and pH-static leaching (CEN/TS 14429) of untreated (b) SWTEP and (d) TSIP samples.

Generally, the pH-static leaching trend for anionic forming metals would display the highest solubility around neutral pH and decreasing solubility at the two extreme pH values (Paoletti et al., 2001). Although Cr, Mo and Sb are considered as oxyanions here, it is obvious from Figures 5-12, 5-14 and 5-16 that Mo and Sb have more similarities in their leaching mechanisms as compared to Cr. For Cr, Figure 5-12 (b, d) shows a maximum solubility at pH 11-12 and a minimum at pH 7. For Mo

and Sb, only maximum solubility at pH 8-9 was observed (Figures 5-14 and 5-16 (b, d)). The amphoteric behaviour as seen in Figure 5-12 (b, d) could be due to the presence of Cr predominantly in its reduced form of Cr(III) as $\text{Cr}(\text{OH})_3$ at pH 7, which is insoluble in soil (Kotaś and Stasicka, 2000). As for Mo and Sb, the leaching trend of carbonated samples in terms of the different sources of IBA was found to be similar (Figures 5-14 and 5-16 (b, d)). Hence, it is possible the difference in mineralogy between SWTEP and TSIP may have contributed to the difference in leaching trend, which will be further discussed in Chapter 7.

Cl^- and SO_4^{2-}

Cl^- leaching did not show obvious trend of increasing or decreasing after carbonation at various operating conditions, only showing a slight decrease after 1 week of carbonation for certain operating conditions (Figure 5-17). The highest reduction in Cl^- leaching was 13.1% for SWTEP carbonated for 2 hours at 35°C, 15% moisture content, and 6.7% for TSIP carbonated for 2 hours at 35°C, 5% moisture content. It has been reported that carbonation has minimal effect on the immobilisation of Cl^- leaching (Todorovic and Ecke, 2006a). This study reports similar findings as Figure 5-18 shows the correlation coefficient between Cl^- leaching and degree of carbonation were relatively low at $R = 0.2508$ and 0.4201 for SWTEP and TSIP samples respectively.

Figure 5-17: Cl⁻ release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

Figure 5-18: Correlation between Cl⁻ leaching and degree of carbonation for (a) SWTEP and (b) TSIP samples.

SO₄²⁻ leaching was found to have increased for all samples after 2 hours of carbonation, regardless of operating conditions (Figure 5-19). The amount of leaching corresponded to the degree of carbonation for SWTEP sample but not TSIP sample. Figure 5-20 shows that $R = 0.7000$ and 0.0653 for SWTEP and TSIP samples respectively. The relatively high R value for SWTEP sample suggests the SO₄²⁻ leaching has strong dependence on the degree of carbonation, which could be explained by the dissolution of ettringite while CaCO₃ precipitates (Meima and Comans 1997b). However for TSIP sample, after 2 hours of carbonation, SO₄²⁻ leaching shows sign of plateau, with slight increment or decrement after 1 week of carbonation. This plateau, which resulted in the lower R value for TSIP, could be due to the difference in mineralogical composition between SWTEP and TSIP samples. This will be further discussed in Chapter 7.

Figure 5-19: SO_4^{2-} release (mg/kg) based on EN 12457-2 as a function of carbonation time for SWTEP and TSIP samples at various operating conditions.

Figure 5-20: Correlation between SO_4^{2-} leaching and degree of carbonation for (a) SWTEP and (b) TSIP samples.

Cl^- and SO_4^{2-} leaching are not considered toxic to human health. However, the high leachability of Cl^- is one of the main considerations preventing the use of IBA in concrete as Cl^- is detrimental to the structural soundness of building due to corrosion of steel reinforcement in concrete. Cl^- leaching from IBA usually exceeds the maximum allowable concentration in cement mixtures, which is set at 4,000 mg/kg (Boghetich et al., 2005). Similarly, SO_4^{2-} leaching from IBA leads to loss of integrity of concrete due to gypsum formation. However, several authors have reported the increase in SO_4^{2-} leaching after carbonation (Meima and Comans 1997b; Bodéan et al., 2000; Polettini and Pomi, 2004), as this study has shown.

5.4 Conclusion

This study aims to address two issues pertaining to treatment of IBA by accelerated carbonation: the influence of operating conditions on the degree of carbonation, and possible factors influencing the leaching mechanism.

In this study, the moisture content was found to strongly affect the initial rate of carbonation. The actual moisture content was found to change during carbonation. The rate of moisture loss and gain was dependent on the carbonation temperature, which indirectly affected the initial rate of carbonation. At IBA particle size ground to $<425 \mu\text{m}$, 15% nominal moisture content achieved the highest degree of

carbonation after 2 hours of carbonation. The optimum temperature was found to differ for the two sources of IBA, i.e. 35°C and 50°C for SWTEP and TSIP samples respectively. This part of study has shown that the lost (or gain) of moisture content during accelerated carbonation would have a significant impact on the carbonation efficiency on the industrial scale. It is possible that the moisture content of IBA be adjusted accordingly on the industrial scale. However, this study has shown that an optimised nominal moisture content can be obtained so as to avoid moisture content adjustment. This requires further study which has to take into other considerations such as the volume of IBA on the industrial scale, method of accelerated carbonation (i.e. enclosed or gas flow through system) and temperature of flue gas as CO₂ source. In summary, it is possible to conclude that a higher nominal moisture content would be more suitable for a higher carbonation temperature.

Based on the input of 20% CO₂ in an enclosed incubator system, 3.8% of CO₂ was taken up by TSIP sample after 2 hours of carbonation at 15% nominal moisture content and 50°C, which increased the degree of carbonation by 1.3 times, as compared to 0 h of carbonation.

After carbonation, the leaching mechanism was examined. Besides the factor of degree of carbonation, there are a few factors that were found to contribute to the leaching mechanism of Pb, Zn, Cu, Cr, Mo and Sb. For Pb and Zn, pH plays a dominant role on the significant reduction in leaching. For Cu leaching, the contributing factors are mainly degree of carbonation and DOC. The dominant contributing factors for Cu leaching after carbonation for the two sources of IBA were different. For SWTEP sample, degree of carbonation and DOC seem to affect Cu leaching equally. However, for TSIP sample, the contribution from degree of carbonation seems to be higher than that of DOC. As for Cr, pH seems to affect Cr leaching more than degree of carbonation. In contrast, Mo and Sb increased in leaching during the initial carbonation. This initial increase in leaching could be due to the pH of carbonated samples (i.e. around 9), which coincides with the maximum solubility of Mo and Sb. However, SWTEP and TSIP showed difference in their leaching behaviours, which could be due to the difference in mineralogical

composition. Eventually, Mo leaching decreased with prolonged carbonation to levels below untreated samples but not Sb, which could be due to adsorption to Fe/Al (hydr)oxides formed after carbonation.

For the highly soluble salts, i.e. Cl^- and SO_4^{2-} , carbonation did not affect Cl^- leaching significantly while SO_4^{2-} leaching increased significantly. For SO_4^{2-} , the amount of leaching corresponded to the degree of carbonation for SWTEP sample but not TSIP sample. After 2 hours of carbonation, SO_4^{2-} leaching shows sign of plateau, with slight increment or decrement after 1 week of carbonation, which resulted in lower R value for TSIP. This could be due to the difference in mineralogical composition between SWTEP and TSIP samples.

Through the investigation of leaching as a function of carbonation time, this study reveals that various factors, including temperature, moisture content, pH, DOC and source of IBA, contribute to the leaching level of each element to different extent. In addition, the difference in mineralogical composition between the two sources of IBA will be further explored in Chapter 7.

PUBLICATION

Lin, W.Y., K.S. Heng, X.L. Sun, and J.-Y. Wang (2015). "Influence of moisture content and temperature on degree of carbonation and the effect on Cu and Cr leaching from incineration bottom ash." Waste Management 43:264-272.

CHAPTER 6: EFFECT OF ACCELERATED CARBONATION ON DIFFERENT SIZE FRACTIONS OF IBA

6.1 Introduction

Many studies have found that IBA can be recycled as useful materials in the construction industry, as IBA exhibits similar properties to concrete aggregate (Tay and Cheong, 1991; Tay and Goh, 1991; Filipponi et al., 2003). However, while the abovementioned researches focused on deriving the optimum formulation (i.e. the ratio of IBA to cement) for higher compressive strength and to improve other physical properties, some pretreatment on IBA is needed to ensure the integrity of the construction material made with IBA. Sieving of IBA is a mandatory pretreatment step in countries, such as Denmark and the Netherlands, which utilise IBA (Chandler et al., 1997). The need to sieve IBA arises from the engineering requirement when utilising IBA in the applications as mentioned. From the engineering viewpoint, the total percentage of fine size fraction ($<60\ \mu\text{m}$) in IBA for use as asphalt pavement or structural fill has to be less than 10% as the fine size fraction has high absorption for water, which compromises durability due to freeze-thaw susceptibility (Chandler et al., 1997). Furthermore, sieving of IBA is essential for the removal of oversized fraction (i.e. $>50\ \text{mm}$) and metallic materials. Non-ferrous metals in IBA, such as Al, are detrimental to the structural integrity due to the evolution of H_2 when IBA comes into contact with water (Chandler et al., 1997).

In terms of treatment of IBA, sieving of IBA has several advantages. Firstly, sieving IBA in different size fractions improves the precious metals recovery (Muchova et al., 2008), which has the additional benefit of generating revenue during IBA treatment. Secondly, by sieving IBA into different size fractions, the leachability of trace elements was found to improve as the size of the considered fractions increased (Stegemann and Schneider, 1991). This will help to reduce the treatment cost of IBA by reducing the volume of IBA that needs to be treated.

This study explores the use of sieving before the accelerated carbonation treatment and its effect on the leaching behaviour of each size fraction. The optimum operating conditions obtained from Chapter 5 was used for all the size fractions in this study. Thus far, there were not many studies on the response of different size fractions towards accelerated carbonation (Chimenos et al., 2003; Baciocchi et al., 2010). Chimenos et al. (2003) studied the effect of natural weathering on different size fractions of MSW IBA while Baciocchi et al. (2010) applied accelerated carbonation on IBA from refuse derived fuel incinerator. On the other hand, this study focuses on the differences in the chemical composition among the different size fractions of IBA from MSW and its effect on the degree of carbonation and leaching behaviour. Further studies on the chemistry of accelerated carbonation of IBA through investigating the mineralogy of different size fractions will be discussed separately in Chapter 7.

6.2 Materials and Methods

6.2.1 Incineration bottom ash

The IBA used for this accelerated carbonation experiment was from the same samples as discussed in Chapter 5. The sampling and handling of IBA was as detailed in Chapter 3. A portion of the wet IBA was tested for moisture content and the dried IBA was then tested for LOI at 550°C. The rest of the wet IBA was dried at 40°C for 3 days and then sieved to obtain four size fractions: 0-2 mm (S0-2 and T0-2), 2-4 mm (S2-4 and T2-4), 4-20 mm (S4-20 and T4-20) and 20-50 mm (S20-50 and T20-50). The ferrous and non-ferrous metals that could not be crushed were removed and weighed. All the size fractions were further ball-milled to pass through a 425 µm stainless steel sieve. This is to minimise the influence of morphological difference between different size fractions on carbonation efficiency.

6.2.2 Accelerated carbonation

The accelerated carbonation process was carried out in CO₂ incubator (Sanyo MCO-18AIC), using 20% CO₂ at 1 atm for all the experiments. A tray of DI water was

placed at the bottom of the incubator to maintain a constant atmospheric humidity. The optimum operating conditions from Chapter 5 using 0-2 mm was applied to other size fractions: 35°C and 50°C at 15% moisture content. The required moisture content was obtained by adding DI water to dried IBA. IBA was spread on plastic petri dishes to no more than 2 mm thick. The carbonation was stopped after 2 hours. The actual moisture remained in the petri dish was monitored.

6.2.3 Analysis

The analysis for this study was as detailed in Section 3.3. Both EN 12457-2 and CEN/TS 14429 leaching tests were used for this study. In addition, the following analysis was carried out for this study. The density of each size fraction was measured by automatic density analyser (Ultracyc 1200e). The surface area after grinding each size fraction separately before accelerated carbonation was determined by Brunauer-Emmett-Teller (BET) test (Quadrachrome SI, Quantachrome Instruments).

6.3 Results and Discussion

6.3.1 Characteristics of IBA

Table 6-1 shows the characteristics of IBA collected from the two incineration plants. The oversize fraction of >50 mm was not used in this study but their weight percentages were noted as 4 wt% and 13 wt% from SWTEP and TSIP respectively. Both plants showed higher weight percentages for 0-2 mm and 4-20 mm size fractions than other fractions. The true density was found to increase as the size increased for TSIP samples but not for SWTEP. The true density for the different size fractions of SWTEP samples was quite close to one another. After ball-milling, the same size fraction from the two incineration plants was able to achieve a relatively similar surface area. The TOC, which measures the organic carbon remaining in IBA after combustion, was observed to decrease as the size increased. The high moisture content (16.8% for SWTEP and 15.5% for TSIP) was due to the sampling of IBA near to the exit of the quenching tank for both incineration plants. The LOI values for both plants (0.59% for SWTEP and 1.51% for TSIP) were

found to be much lower than mean values reported in Canada, Denmark and United States (Chandler et al., 1997).

Table 6-1: Characteristic of IBA collected from incineration plants SWTEP (S) and TSIP (T).

Incineration plant	SWTEP		TSIP	
Moisture content (%)	16.8		15.5	
LOI (%)	0.59		1.51	
Ferrous (wt%)	12.1		8.3	
Non-ferrous (wt%)	0.8		1.2	
Size fraction	0-2 mm	2-4 mm	4-20 mm	20-50 mm
Particle size distribution (wt%)	34.2 (S) 29.7 (T)	8.6 (S) 7.3 (T)	38.7 (S) 29.9 (T)	14.5 (S) 20.1 (T)
True density (kg/m ³)	2,782 (S) 2,928 (T)	2,822 (S) 2,997 (T)	2,766 (S) 3,023 (T)	2,772 (S) 3,099 (T)
BET (m ² /g) *After ground to <425 µm	4.34 (S) 4.70 (T)	3.63 (S) 4.95 (T)	2.46 (S) 2.42 (T)	3.07 (S) 2.74 (T)
TOC (mg/g)	5.86 (S) 9.98 (T)	4.45 (S) 10.30 (T)	3.01 (S) 5.73 (T)	1.78 (S) 1.63 (T)

The total element content for the four size fractions is shown in Table 6-2. Only the total concentrations of Ca, Cd, Co, Sb, Cl⁻ and SO₄²⁻ were observed to decrease as the size increased for both incineration plants. For the soluble salts, i.e. Cl⁻ and SO₄²⁻, this trend shows that sieving can be beneficial to IBA utilisation in concrete by selecting only coarser size fractions, in which the soluble salts contents are lower. This will minimise expansion problems arising from reactions associated with soluble salts (Tyrer, 2013). However, the 20-50 mm size fraction has the highest total Al content among all the size fractions, which will be unfavourable in IBA utilisation in concrete due to Al-induced expansion. However, this can be resolved by immersing IBA in NaOH, which reacts with Al to emit H₂ before utilisation (Pera et al., 1997). Other elements such as Cr was found to decrease in SWTEP sample as the size increased but increase in TSIP sample as the size increased. For

Cu, it was found to be most concentrated in S2-4 and T0-2. For Mn and Pb, both were highest in 2-4 mm size fraction while Zn was mostly concentrated in 0-2 mm for both incineration plants. The trend of total element content of Ca, Pb and Zn as a function of the size fractions was similar to those reported by (Chimenos et al., 2003).

Comparing between the two incineration plants, Pb, Sb, Sn and Cl^- were present in higher concentrations in all the size fractions of SWTEP than TSIP sample. As mentioned in Section 4.3.2, Pb and Sb are commonly used in batteries. Sn is used in the coating of steel cans and Cl^- can be found in PVC plastics and food waste. All these are common household wastes, which are not compulsory to be segregated for recycling in Singapore and hence, this could explain the higher concentrations of Pb, Sb, Sn and Cl^- in SWTEP sample since this incineration plant receives predominantly household waste. On the other hand, Fe, Mn and Mo were found to be at higher concentration in all the size fractions of TSIP sample. Mn and Mo are mainly used as alloy in metallurgy while Fe is used for the production of ferrous materials. These elements mainly come from industrial wastes, which incineration plant TSIP receives predominantly. These metallurgy wastes could have contributed to the higher true density for the coarser size fraction in TSIP samples. This trend, in terms of the presence of abovementioned elements in higher concentrations in different incineration plants, was similar to the average total trace element content results, which consists of all the four size fractions discussed in Section 4.3.2.

Table 6-2: Total element content (mg/kg) for the four size fractions from incineration plants SWTEP and TSIP.

Element (mg/kg)	SWTEP				TSIP			
	0-2 mm	2-4 mm	4-20 mm	20-50 mm	0-2 mm	2-4 mm	4-20 mm	20-50 mm
Ag	19	13	9	9	18	19	7	10
Al	32,467	33,767	30,600	62,900	32,033	37,867	36,667	40,167
As	20	24	37	17	64	63	38	24
Ba	81	57	41	52	65	74	66	50
Be	0.9	1.2	1.5	3.4	1.2	1.4	1.7	1.7
Ca	180,333	132,000	108,000	84,067	139,667	108,667	103,267	93,867
Cd	11	2.1	1.4	0.58	5.3	1.8	1.1	< 0.5
Co	52	34	30	17	48	41	33	28
Cr	235	216	184	140	206	210	248	287
Cu	2,453	3,513	1,703	733	2,437	2,070	2,243	1,883
Fe	51,467	59,067	56,700	51,067	111,000	117,333	133,667	141,000
K	9,270	9,447	8,977	14,500	9,857	10,467	9,970	9,363
Mg	10,113	9,723	11,133	8,217	10,633	10,300	11,367	11,433
Mn	895	1,030	679	718	1,600	2,127	1,987	1,733
Mo	17	14	11	8	121	96	85	88
Na	15,333	22,700	41,667	19,033	13,067	17,100	25,967	17,467
Ni	183	140	92	88	169	172	130	107
Pb	611	1,717	1,133	145	199	294	288	122
Sb	246	153	131	84	85	59	57	34
Sn	161	130	99	113	95	94	63	73
Sr	340	388	521	736	327	348	502	252
Ti	6,720	5,297	3,450	3,350	5,267	6,163	5,527	5,817
V	27	30	24	40	55	53	49	65
Zn	3,073	2,387	1,523	1,900	4,050	2,953	2,147	1,437
Cl ⁻	11,200	6,493	3,877	1,887	5,900	3,687	1,940	1,290
SO ₄ ²⁻	8,307	6,440	4,890	1,880	6,987	5,320	3,143	1,433

6.3.2 Degree of carbonation of different size fractions

Based on the study discussed in Chapter 5, the optimum operating conditions were 2 hours of carbonation at 15% moisture content, 35°C and 50°C for S0-2 and T0-2 samples respectively. Both 35°C and 50°C were used for carbonating the four size fractions of SWTEP and TSIP samples for comparison on the difference in degree of carbonation (Table 6-3). Generally, the degree of carbonation for the four size fractions decreased as the size increased. This decrease in the degree of carbonation corresponded to the decrease in the total Ca content as the size increased. This result echoed the findings of Baciocchi et al. (2010) and demonstrated that the amount of CO₂ sequestered by IBA is strongly dependent on the total Ca content.

In terms of the optimum operating conditions, SWTEP samples carbonated more effectively at 35°C, 15% moisture content, except for S20-50 sample. The same trend was observed for TSIP samples for operating conditions 50°C, 15% moisture content, except for T4-20 sample. However, the differences in the degree of carbonation for the exceptions were not great. In fact, there was very minute difference in degree of carbonation for 4-20 mm and 20-50 mm size fractions. This suggests that the coarse size fractions were not as sensitive to the difference in operating conditions.

Lastly, the actual moisture content remaining after 2 hours of carbonation was observed to be similar with respect to the carbonation temperatures, regardless of the source of IBA. The actual moisture content of all the size fractions from both plants had an average value of 14.3% at 35°C, while the average value at 50°C was 10.6%. This shows that the temperature used for carbonation would result in some loss of moisture with time. Furthermore, the effect of moisture content on the degree of carbonation was more pronounced for the 0-2 mm and 2-4 mm size fractions only.

Table 6-3: The degree of carbonation (mg/g) of the respective size fractions and the actual moisture content (%) remained after 2 hours of carbonation.

Operating conditions	Degree of carbonation (mg/g)	Actual moisture content (%)
S0-2		
35C15MC	9.20	14.00
50C15MC	8.79	9.58
S2-4		
35C15MC	4.34	15.18
50C15MC	3.78	11.25
S4-20		
35C15MC	3.55	14.31
50C15MC	3.26	11.00
S20-50		
35C15MC	4.42	14.75
50C15MC	4.47	10.75
T0-2		
35C15MC	8.56	13.31
50C15MC	10.41	12.03
T2-4		
35C15MC	4.89	14.31
50C15MC	6.53	10.50
T4-20		
35C15MC	4.15	14.09
50C15MC	4.11	9.75
T20-50		
35C15MC	2.51	14.53
50C15MC	2.86	9.75

6.3.3 Effect of accelerated carbonation on pH

Figure 6-1 shows the pH before and after carbonation at 35°C and 50°C, 15% moisture content. For the untreated SWTEP samples, the pH did not vary much among the four size fractions, from pH 12.4 to 12.1 (i.e. from finest to coarsest). However, the pH was found to decrease slightly from pH 12.6 to 11.9 as the size increased for the untreated TSIP samples. After 2 hours of carbonation at 35°C and 50°C, the pH of S0-2 and T0-2 decreased to an average of 9.6 and 9.8 respectively.

The average refers to the average pH of two carbonation temperatures. For the other size fractions, the pH reduced more, the lowest observed pH was 9.0 for S4-20 sample carbonated at 50°C and 15% moisture content. It was noted that the reduction in pH of T20-50 sample was slower than that of S20-50 sample, from 11.9 to an average of 9.4, as compared to 12.1 to an average of 9.3. The lower pH obtained by other size fractions after 2 hours of carbonation shows that the optimum operating conditions selected based on the 0-2 mm size fraction was able to satisfactorily carbonate the other size fractions too.

Figure 6-1: The pH of the different size fractions showing untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

6.3.4 Effect of accelerated carbonation on leaching

Pb and Zn

The decrease in pH after carbonation for all the size fractions has a positive impact on the reduction in Pb and Zn leaching, whereby the leaching mechanism of Pb and Zn is reported to be dependent on the pH of IBA (Meima and Comans, 1999). The leaching trend for Pb was not shown here as most of the IBA leachates were below the detection limit of ICP-OES (i.e. <5 µg/L). Untreated S0-2 and S2-4 had the highest Pb released at 30.0 mg/kg and 73.1 mg/kg respectively while Pb released for untreated S4-20 was 1.0 mg/kg. Untreated T0-2 was found to leach slightly at 0.36 mg/kg. The rest of the untreated size fractions in both SWTEP and TSIP

samples were undetectable in Pb leaching. However, accelerated carbonation was found to be very effective in reducing Pb leaching. Regardless of the size fractions and operating conditions of carbonation, Pb was undetectable after carbonation in all the leachates. This consistency in reduction of Pb leaching suggests that pH plays a dominant role in the leaching mechanism of Pb, as discussed in Section 5.3.5.

Figure 6-2 shows Zn leaching from untreated and carbonated IBA as a function of size fractions. The amount of Zn released from untreated SWTEP and TSIP samples decreased as the size increased. Generally, all the size fractions from untreated TSIP sample showed significantly less Zn leaching compared to those from untreated SWTEP sample. After carbonation, only S0-2 and T0-2 samples still had slight Zn leaching while Zn leaching in the rest of the size fractions were below the detection limit of ICP-OES (i.e. $<5 \mu\text{g/L}$). Similar to Pb, the reduction in Zn leaching could be due to the lower pH reached after carbonation.

Figure 6-2: Zn release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

Cu

Figure 6-3 shows Cu leaching decreased as the size increased for the untreated samples. However, unlike Pb and Zn, the percentage reduction varied for Cu after

carbonation. The percentage reduction in Cu leaching ranged from 64.8 to 85.3% for SWTEP samples and 69.5 to 82.4% for TSIP samples. Since the pH after carbonation for all the samples was consistently around 9, this suggests that the leaching mechanism of Cu was not strongly influenced by pH, but by other factors. In terms of the degree of carbonation, the reduction in Cu leaching was observed to be unaffected by the difference in carbonation temperatures. Figure 6-4 shows the correlation between the amount of Cu and DOC released was high, even at different carbonation temperatures. This suggests that Cu leaching was greatly influenced by DOC leaching due to the formation of more soluble organic complexes, instead of the degree of carbonation. However, as discussed in Section 5.3.5, considering 0-2 mm size fraction only, the leaching mechanism of Cu was affected by DOC and degree of carbonation to different extent for the two sources of IBA. Degree of carbonation was found to affect Cu leaching in T0-2 more than DOC, while both factors affect Cu leaching in S0-2 equally. This difference in conclusion for 0-2 mm and the rest of the size fractions could be due to the greater influence from the operating conditions on the degree of carbonation, which affected 0-2 mm more than other size fractions. In terms of the different size fractions, it seems that DOC contributed more to the reduction in Cu leaching for both SWTEP and TSIP samples.

Figure 6-3: Cu release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

Figure 6-4: Correlation between Cu and DOC leaching for the different size fractions of SWTEP and TSIP samples carbonated for 2 hours at 15% moisture content and (a, c) 35°C and (b, d) 50°C. R = Pearson's R.

Oxyanions – Cr, Mo and Sb

The amount of Cr released from untreated TSIP samples decreased as the size increased but SWTEP samples did not show the same trend as Cr leaching from untreated S2-4 sample was exceptionally low (Figure 6-5). After carbonation, S0-2 sample had an average of 48.3% reduction in Cr leaching while the other size fractions of SWTEP samples had more significant reduction in Cr leaching, ranging from 63.1 to 92.9%. Similarly, the reduction in Cr leaching for T0-2 samples was an

average of 62.2%, which was less significant compared to other size fractions (i.e. 83.0 to 94.9%). It was discussed in Section 5.3.5 that pH plays a dominant role in Cr leaching. In this study, after carbonation, the final pH of 0-2 mm size fractions was slightly higher than other size fractions (Figure 6-1). Therefore, the lower pH in the rest of the size fractions could have contributed to the lower Cr leaching.

Figure 6-5: Cr release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

The amount of Mo released from untreated TSIP samples were significantly higher than that from SWTEP samples (Figure 6-6). Coincidentally, the total Mo content in all the size fractions of TSIP was an order of magnitude higher than SWTEP, which could be a possible reason for the higher leaching from untreated TSIP samples. The leaching behaviour after carbonation was totally different for the two sources of IBA. Most of SWTEP samples showed an increase in Mo leaching after carbonation while TSIP samples showed varying levels of reduction. T4-20 had the highest reduction at 47.2% and 62.4%, while T0-2 had the lowest reduction at 3.5% and 2.6%, for samples carbonated at 35°C and 50°C respectively. In Section 5.3.5, one possible Mo leaching mechanism was discussed to be pH. However, in terms of the different size fractions, the pH after carbonation was similar between SWTEP and TSIP samples. Therefore, the decrease in Mo leaching for TSIP samples, but not SWTEP samples, could be due to the difference in mineralogical composition. This will be further discussed in Chapter 7.

Figure 6-6: Mo release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

The leachates from untreated SWTEP and TSIP samples were found to be below the detection limit of Sb (i.e. $<10 \mu\text{g/L}$), except for S0-2 (Figure 6-7). The values that were below the detection limit were represented by zero in the graphs. After carbonation, all the samples showed drastic increase in Sb leaching. The higher Sb leaching from all the size fractions of SWTEP could be due to its higher total Sb content. The effect of pH could be a possible factor contributing to the increase in Sb leaching as the pH-static leaching trend shows that the maximum solubility of Sb coincides with the final pH after carbonation (Figure 5-16 (b, d)). On the other hand, pH cannot fully explain the phenomenon observed for the different size fractions as all the respective size fractions between SWTEP and TSIP have similar pH after carbonation. But the increment in Sb leaching varied when compared among the same size fractions between the two sources of IBA. Nevertheless, this study has shown that accelerated carbonation would not favour the reduction in Sb leaching.

Figure 6-7: Sb release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

DOC, Cl^- and SO_4^{2-}

DOC displayed similar reduction in leaching for the untreated samples as the size increased (Figure 6-8). After carbonation, DOC leaching decreased but did not differ much between the two carbonated temperatures of the same size fractions of the same source of IBA. This shows that the degree of carbonation did not have much effect on the DOC leaching reduction. The percentage reduction for DOC ranges from 11.0 to 32.3% for all the size fractions and source of IBA, whereby S4-20 and T4-20 had the highest reduction.

Figure 6-8: Concentration of DOC (mg/L) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

Figure 6-9 shows the amount of Cl^- released from untreated samples decreased as the size increased. This trend is probably due to the higher surface area of the smaller size fraction, which results in higher incorporation of chlorine gas on its surface inside the combustion chamber (Ito et al., 2006). In terms of the different size fractions, Cl^- did not show reduction in leaching after carbonation. The amount of Cl^- released was also similar when comparing between the different carbonation temperatures. Therefore, this study and the earlier study in Chapter 5 have shown that carbonation has no effect on Cl^- leaching.

Figure 6-9. Cl^- release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

Similarly for SO_4^{2-} , the amount released from untreated samples decreased as the size increased (Figure 6-10). After carbonation, SO_4^{2-} leaching increased for all the size fractions. Generally, the amount of increment was not dependent on the carbonation temperatures (i.e. degree of carbonation). The increase in SO_4^{2-} leaching could be due to the dissolution of ettringite during carbonation (Meima and Comans 1997b).

Figure 6-10. SO_4^{2-} release (mg/kg) based on EN 12457-2 as a function of size fractions for untreated (a) SWTEP and (b) TSIP samples, and after carbonation.

6.3.5 Effect of different size fractions on pH-static leaching

The acid neutralising capacity (ANC) of the different size fractions was investigated (Figure 6-11). The ANC for both SWTEP and TSIP samples was observed to decrease as the size increased. However, the ANC of 0-2 mm size fractions for both SWTEP and TSIP samples was significantly higher than the rest of the size fractions. Both S0-2 and T0-2 samples required approximately 1.33 mol H^+ /kg of acid to reduce the pH from the initial of around 12 to 10. This amount of acid required was about 2 to 3 times higher than those required by other size fractions to reach a pH of 10. At around pH 10, the pH of other size fractions were found to decrease significantly from pH 10 to 7 with just an addition of 0.5 to 1 mol H^+ /kg of acid. The decreasing ANC as size increased was associated with the lower buffer capacity due to decreasing portlandite phase, whereby portlandite was reported to be a major contributor to the buffering capacity of IBA (You et al., 2006). The implication of this result in terms of carbonation means that 0-2 mm size fraction requires more CO_2 uptake (i.e. higher CO_2 percentage or longer carbonation duration) to reduce the pH from alkaline to neutral and the other size fractions requires less. This conclusion is similar to You et al. (2006).

Figure 6-11: The acid neutralising capacity (ANC) of the different size fractions of untreated (a) SWTEP and (b) TSIP samples.

The leaching behaviours of Pb, Zn, Cu, Cr, Mo and Sb in response to an externally added acid are shown in Figures 6-12 to 6-17. Leachate samples from this pH-static leaching test were analysed by ICP-MS for elements Pb and Zn only as their concentrations were below the detection limit of ICP-OES. Some of the concentration of these elements was also below the detection limit of ICP-MS and the corresponding values in the graphs were explained under the figures' captions.

Generally, the leaching trend as a function of pH for the individual elements was similar for all the different size fractions. This similarity in the pH dependency leaching among the different size fractions shows their similarity in leaching behaviour when tested in solubility controlling condition, as pH plays a dominant or possible role in the leaching mechanism for most of the elements discussed in this study, except for Cu. Comparing between untreated SWTEP and TSIP, the leaching trend was also similar, except for Cu, which showed two minimum solubility ranges for TSIP samples (Figure 6-14b). The leaching trend for Mo from TSIP also showed difference in terms of a slight increase in the alkaline pH (Figure 6-16b). The leaching data from the pH-static test can be used as input to modelling of chemical behaviour using geochemical speciation models, but this is beyond the scope of this study.

It was also observed that for the elements discussed here, the amount released in the pH-static leaching test decreases as the size increased. This is in contrast to the trend in the total element content of the different size fractions (Table 6-2). For example, the total Pb content was more concentrated in the 2-4 mm and 4-20 mm. For Cr, the total Cr content decrease as size fractions increase for SWTEP samples but increase with the size fractions for TSIP samples. However, both SWTEP and TSIP samples showed similar pH dependence leaching trend in Figure 6-15. This has further shown that coarse size fraction has lower release of elements and hence, requires less extensive treatment before utilisation. However, the pH-static leaching test would have to be carried out on more samples to ensure that this observation is statistically repeatable.

Figure 6-12: Pb leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test. The detection limit of ICP-MS for Pb is 0.1 µg/L. The represented value used here is 5×10^{-4} mg/kg.

Figure 6-13: Zn leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test. The detection limit of ICP-MS for Zn is $0.5 \mu\text{g/L}$. The represented value used here is $2.5 \times 10^{-3} \text{ mg/kg}$.

Figure 6-14: Cu leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test.

Figure 6-15: Cr leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test.

Figure 6-16: Mo leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test.

Figure 6-17: Sb leaching from different size fractions of untreated (a) SWTEP and (b) TSIP samples as a function of pH based on CEN/TS 14429 leaching test. The detection limit of ICP-OES for Sb is 10 $\mu\text{g/L}$. The represented value used here is 0.05 mg/kg.

6.4 Conclusion

This study evaluated the effect of accelerated carbonation on different size fractions of IBA collected from two incineration plants in Singapore. The differences between the IBA collected from different incineration plants and their different size fractions were examined through total element content. The total element content between the two incineration plants showed significant differences for certain elements (i.e. Fe, Mn, Mo, Pb, Sb, Sn, and Cl^-), which could be associated with the dominant type of waste received by the plants. In terms of different size fractions, the total element content showed that only some of the elements (i.e. Ca, Cd, Co, Sb, Cl^- and SO_4^{2-}) displayed decreasing total content as the size increased. This trend is especially important for total Ca content as the decreasing Ca content with increased size resulted in decreasing degree of carbonation. However, the 4-20 mm and 20-50 mm size fractions from both sources of IBA did not show significant difference in degree of carbonation when different carbonated temperatures were used.

In general, the pH of IBA reduced from around 12 to 9 after accelerated carbonation. Pb, Zn, Cu, Cr and DOC leaching decreased after carbonation, while carbonation did not affect Cl^- leaching. Mo leaching increased for SWTEP sample but not TSIP.

Lastly, Sb and SO_4^{2-} leaching increased significantly after carbonation. Generally, the amount of leaching after carbonation did not correspond to the degree of carbonation when compared among the same size fraction and source of IBA. The leaching mechanism of IBA was not sensitive to the different operating conditions used, which in this case was the carbonation temperature.

This study has shown through the leaching of untreated samples of different size fractions, the quality of IBA can be improved through the simple use of sieving before carrying out carbonation. Most of the elements discussed here showed decrease in leaching for the untreated samples as the size increased. This finding is important especially for highly soluble constituents like DOC, Cl^- and SO_4^{2-} , where the concentration in the 20-50 mm size fraction was significantly lower compared to 0-2 mm size fraction. Thus, size separation can help to increase the utilisation potential of IBA for the coarse size fraction as the coarse size fraction can generally be used with less treatment, depending on the regulation of each country. Furthermore, ANC results showed that 0-2 mm size fraction required more acid to reduce the pH as compared to other size fractions. Hence, it is possible that the carbonation duration may be further reduced for the coarse size fractions to achieve similar reduction in leaching as discussed in this study. This translates to monetary saving as sieving is simple and inexpensive to carry out.

PUBLICATION

Lin, W.Y., K.S. Heng, X.L. Sun, and J.-Y. Wang (2015). “Accelerated carbonation of different size fractions of MSW IBA and the effect on leaching.” Waste Management 41: 75-84.

CHAPTER 7: INVESTIGATION ON THE MINERALOGICAL COMPOSITION OF IBA

7.1 Introduction

IBA undergoes carbonation upon contact with air, due to its metastable state after quenching straight after combustion at high temperature, resulting in changes to the mineralogical composition of IBA and subsequently, the leaching behaviour. The first measurable change in IBA that has carbonated is its pH. As shown earlier in Eq. 2-1, when IBA reacts with CO_2 , the hydroxide mineral transforms to carbonate mineral, resulting in a decrease in pH. Comans and Meima (1994) reported that the pH of IBA was strongly influenced by Ca-minerals. Researchers that further examined the mineralogy of carbonated IBA showed the precipitation of calcite and formation of secondary minerals (Speiser et al., 2000; Piantone et al., 2004; Rendek et al., 2006; Bayuseno and Schmahl, 2010). These changes collectively alter the leaching behaviour of IBA after carbonation.

XRD is one of the analytical methods that can be used to determine the possible minerals present in IBA. The advantages of using XRD over other similar analytical methods, such as X-ray photoelectron spectroscopy (XPS) and energy-dispersive X-ray spectroscopy (EDX), are the ease of sample preparation for analysis and ease of raw data interpretation. The XRD equipment is also relatively less expensive than other analytical equipment. However, the limitation of using XRD to determine the mineralogical composition of IBA is the presence of numerous minerals, which will give rise to overlapping of peaks among the different minerals. This makes identification of minerals in IBA challenging and incomplete (Bayuseno and Schmahl, 2010). The Rietveld refinement method, developed by Hugo Rietveld (Rietveld, 1969), was able to overcome this limitation and has since been widely used in the structural analysis of polycrystalline materials. It is based on a least squares algorithm to refine the whole diffraction pattern until the calculated pattern is fitted to the experimentally observed pattern (Will, 2006). Without the need to use standard reference materials, this development also allows the refinement of

structural profile of materials as complex as IBA (Bayuseno et al., 2010; Mahieux et al., 2010). Furthermore, the Rietveld method is capable of quantifying the relative amount of minerals in a sample (Will, 2006).

The focus of this study is to carry out mineralogical analysis of IBA using XRD. It seeks to provide possible explanation for the results observed from the studies carried out in Chapters 5 and 6. This is done by investigating firstly, the mineralogy of untreated IBA from the two different incineration plants and among the different size fractions, and secondly, mineralogical changes that took place in selected IBA samples after accelerated carbonation. This perspective will complement the carbonation and leaching mechanisms as discussed in Chapters 5 and 6. This study also attempts to use the Rietveld refinement method to verify and quantify the minerals identified in IBA.

7.2 Materials and Methods

7.2.1 Materials

All the samples discussed in this chapter were selected from carbonated samples carried out per detailed in Chapter 5 and 6.

7.2.2 XRD

XRD analysis was performed on selected IBA samples. Before analysis, the samples were further ground using a mortar and pestle. XRD analysis was then performed in Bragg-Brentano geometry (Bruker AXS D8 Advance) with Cu-K α radiation ($\lambda = 1.54060\text{\AA}$) and fixed receiving slit (2.0 mm). The scan speed was set at 0.3°/min, with a scan step of 0.02° in continuous scan mode. Mineral identification was done by comparing the positions of the measured diffraction maxima with peak positions of possible minerals contained in the ICDD powder diffraction file database (ICDD, 2001). To quantify the minerals, further evaluation of the diffraction patterns by means of the Rietveld method was carried out using the TOPAS software V3.

7.3 Results and Discussion

7.3.1 XRD analysis of untreated IBA

The identification of minerals commonly found in IBA was first carried out and discussed qualitatively here. Figure 7-1 shows the XRD patterns of untreated IBA samples of 0-2 mm size fraction. The mineralogical compositions from different incineration plants were found to be slightly different. Diopside ($\text{CaMg}(\text{Si}_2\text{O}_6)$) was undetectable in S0-2 sample while hydroxylapatite ($\text{Ca}_5(\text{PO}_4)_3(\text{OH})$) and gibbsite ($\text{Al}(\text{OH})_3$) were undetectable in T0-2 sample. Both hematite (Fe_2O_3) and magnetite (Fe_3O_4) peaks were detected in S0-2 and T0-2 but they were labeled in T0-2 only, as the intensity of the peaks was more observable. The dominant anhydrite (CaSO_4) peak was also significantly higher than the quartz (SiO_2) peak in S0-2, in contrast to T0-2.

Figure 7-1: XRD patterns of untreated (a) S0-2 and (b) T0-2 samples. [An = anhydrite, Ca = calcite, D = diopside, Gib = gibbsite, H = hematite, Ha = hydroxylapatite, M = magnetite, P = portlandite, Q = quartz]

XRD analysis was also carried out for the different size fractions of untreated TSIP samples to determine the difference in mineralogical compositions (Figure 7-2). Generally, from a qualitative perspective, all the size fractions have similar mineralogical composition but with different characteristic peak intensity for each phase. Anhydrite, hematite, portlandite ($\text{Ca}(\text{OH})_2$) and calcite (CaCO_3) peaks showed decreasing intensity as the size of TSIP samples increased. On the other

hand, magnetite peaks increased with the size of TSIP samples. Anhydrite and diopside minerals are formed during the quenching process while calcite is present as a remnant from the combustion process (Speiser et al., 2000). The verification of the quantity of these minerals will be further discussed below. Overall, the XRD patterns showed the untreated IBA samples have high crystallinity, although IBA is commonly known to have high content of amorphous phase. This could be due to the inclusion of grate sifting, boiler and economiser ash to the IBA in this study.

Figure 7-2: XRD patterns of untreated T0-2, T2-4, T4-20 and T20-50 samples. [An = anhydrite, Ca = calcite, D = diopside, H = hematite, M = magnetite, P = portlandite, Q = quartz]

Besides the common minerals already discussed earlier, other minor minerals that may be present in IBA were first identified based on other mineralogical studies done using XRD (Speiser et al., 2000; Bayuseno and Schmahl, 2010; Santos et al., 2013). The minerals were then analysed by adding the minerals one at a time to the Rietveld refinement method.

Table 7-1 shows the mineralogical composition of untreated IBA quantified by Rietveld method. Most of the minerals that were quantifiable by the Rietveld method were Ca- and Si- minerals. Compared to other studies (Speiser et al., 2000; Bayuseno and Schmahl, 2010; Santos et al., 2013), the quantity (in wt%) of the minerals in this study were much higher. For example, around 6.26 to 18.05 wt% of calcite was found in the different size fractions of TSIP samples while Santos et al. (2013) only reported 3.5 wt% of calcite in their F sample (i.e. without size separation). Both S0-2 sample in this study and F sample from Santos et al. (2013) study consisted of industrial wastes. The large difference was due to the high percentage of amorphous material that was included in the analysis done by Santos et al. (2013), which this study has excluded.

The use of Rietveld method to quantify the mineralogical composition gave further insight on the differences between the analysed IBA samples. For S0-2 and T0-2 untreated samples, Table 7-1 shows that both calcite and anhydrite were found to be higher in S0-2 sample. On the other hand, both samples showed similar quantity for portlandite. It is possible that anhydrite was involved in the carbonation reaction, together with portlandite as suggested by Rendek et al. (2006). Carbonation of anhydrite takes place at a lower log K (25°C) than portlandite (Bodéan et al., 2000) (Eq. 7-1 and 7-2). This may have contributed to the lower carbonation temperature needed for S0-2 sample (i.e. 35°C), compared to T0-2 sample (i.e. 50°C).

Other mineralogical differences between S0-2 and T0-2 untreated samples were the absence of powellite (CaMoO_4) and goethite (FeOOH) in T0-2 and the higher content of quartz, hematite and magnetite in T0-2. At alkaline pH, powellite is proposed to control Mo leaching (Meima and Comans, 1999). Thus, the absence of powellite could be another reason for the higher Mo leaching in T0-2 untreated sample, in addition to the reason that total Mo content was higher in T0-2 compared to S0-2.

In terms of the different size fractions of untreated TSIP samples, the results show that calcite, anhydrite, portlandite and halite content decreased as the size increased. In contrast, quartz and corundum (Al_2O_3) content increased with size. Gehlenite ($\text{Ca}_2\text{Al}_2\text{SiO}_7$), anthophyllite ($\text{Mg}_7\text{Si}_8\text{O}_{22}(\text{OH})_2$) and diopside content, which contain silicates, were found to be higher at the coarse size fractions of 4-20 mm and 20-50 mm. This observation is consistent with the visual characterisation done by Chimenos et al. (1999), whereby glass was found mostly in the coarse size fraction. By observing the mineralogical compositions of the different size fractions of untreated TSIP samples, it is not possible to deduce the reason for the minute difference in degree of carbonation when the coarse size fractions were carbonated at two different temperatures, as found in Chapter 6. However, the decreasing anhydrite and portlandite content with increasing size was in agreement with the decreasing degree of carbonation as size increased. This mineralogical study has shown that the coarse size fractions of 4-20 mm and 20-50 mm consisted mostly of quartz. And several minerals found in 0-2 mm, especially halite (NaCl) and sylvine (KCl), were not present in the coarse size fractions. This study has further shown that the coarse size fractions have higher utilisation potential due to the lower salt content.

Table 7-1. Comparison of mineralogical composition (in wt%) of the different sources and size fractions of untreated IBA determined by quantitative XRD using Rietveld method.

Mineral	Chemical formula	S0-2	T0-2	T2-4	T4-20	T20-50
Calcite	CaCO_3	22.22	18.05	14.35	7.24	6.26
Anhydrite	CaSO_4	34.19	21.67	10.18	6.76	1.33
Magnesium calcite	$\text{Ca}_{0.97}\text{Mg}_{0.03}\text{CO}_3$	0.14	2.30	0.80	1.75	0.44
Portlandite	$\text{Ca}(\text{OH})_2$	1.37	1.54	0.64	0.35	N.D.
Ettringite	$\text{Ca}_6\text{Al}_2(\text{SO}_4)_3(\text{OH})_{12} \cdot 26\text{H}_2\text{O}$	1.33	1.35	0.49	0.83	N.D.
Gehlenite	$\text{Ca}_2\text{Al}_2\text{SiO}_7$	1.37	0.17	0.18	2.06	1.11
Diopside	$\text{CaMg}(\text{Si}_2\text{O}_6)$	N.D.	1.34	6.20	4.69	14.36
Hydroxylapatite	$\text{Ca}_5(\text{PO}_4)_3(\text{OH})$	2.48	0.80	0.60	N.D.	N.D.
Calcium Zinc Aluminosilicate	$(\text{Ca}_{0.97}\text{Zn}_{0.03})_2(\text{Al}_{0.63}\text{Zn}_{0.37})(\text{Si}_{0.69}\text{Al}_{0.31})_2\text{O}_7$	2.37	3.70	5.70	9.77	3.62
Powellite	CaMoO_4	1.08	N.D.	N.D.	N.D.	0.73
-	CaO_4Ti_2	2.60	3.87	4.64	N.D.	N.D.
Anthophyllite	$\text{Mg}_7\text{Si}_8\text{O}_{22}(\text{OH})_2$	1.39	0.89	1.10	5.75	4.00
Quartz	SiO_2	14.35	30.05	34.27	39.59	50.83
Hematite	Fe_2O_3	0.56	4.24	6.06	3.04	0.21
Magnetite	Fe_3O_4	0.69	2.52	5.49	10.84	8.67
Goethite	FeOOH	2.77	N.D.	N.D.	N.D.	0.16

Mineral (Cont'd)	Chemical formula	S0-2	T0-2	T2-4	T4-20	T20-50
Wuestite	FeO	0.40	0.08	0.83	0.96	0.26
Marcasite	FeS ₂	1.56	0.61	0.31	N.D.	0.75
Gibbsite	Al(OH) ₃	0.03	N.D.	N.D.	N.D.	0.11
Corundum	Al ₂ O ₃	1.05	1.17	1.81	4.45	6.52
Halite	NaCl	6.60	4.90	4.25	N.D.	N.D.
Sylvine	KCl	1.35	N.D.	N.D.	N.D.	N.D.
Malachite	Cu ₂ (OH) ₂ CO ₃	0.10	0.75	2.09	1.91	0.64
GOF		4.58	4.93	4.75	4.06	4.50
R _{exp}		14.06	13.80	14.77	17.70	17.15
R _{wp}		64.45	67.99	70.15	71.87	77.11

N.D.: not detected

The goodness of fit (GOF) describes how well the Rietveld refinement was carried out for a diffraction pattern. It is the ratio between R_{wp} (i.e. weighted pattern R index) and R_{exp} (expected R index), which are also known as R-indices. The R-indices are adopted from the single crystal structure analysis, whereby the value of R is defined as the difference between the experimentally observed data and calculated data (Will, 2006). A good refinement gives GOF values lower than 1.5 but it cannot be lower than 1 (Prince, 1995). This study was only able to obtain GOF values of ~4. The relatively high GOF values could, firstly, be attributed to the exclusion of amorphous materials in the calculation, and secondly, due to the lack of ICDD files for some unknown and highly complex mineral phases in IBA. The fit of the Rietveld calculation can be viewed graphically, as shown in Figure 7-3, which shows the XRD spectrum of untreated S0-2 sample. The blue and red spectra at the top are the experimental data and Rietveld calculated data respectively. The red spectrum shows how well the minerals are matching the experimental data. The grey spectrum in the middle shows the difference between the experimental data and Rietveld calculated data. The grey spectrum should be as flat as possible, if the calculated data fits the experimental data well. The markers at the bottom are the XRD fingerprint of the minerals shown at the top right. As can be seen from Figure 7-3 and GOF values (i.e. ~4), the Rietveld calculated data did not fit the experimental data well as certain peaks were not identified here. If the ICDD files of unknown minerals are available in the future, more minerals (usually the less common ones) can be identified and matched to the remaining peaks in a trial and error process. This may improve the GOF value. As a consequence, by adding more minerals, the calculated quantity of the initially identified minerals will decrease accordingly, as the sum of the weight percentage of all the minerals is fixed at 100%. Under the constraint faced for this study (i.e. the minerals present in IBA were not completely identified), this study selected 23 types of most major and common minerals, and applied them consistently to the Rietveld refinement of IBA samples so that the trend in the quantification of minerals among the different IBA samples can be compared to another.

Figure 7-3: XRD spectrum of untreated S0-2 sample.

7.3.2 XRD analysis of carbonated IBA

Figure 7-4 shows the XRD patterns of T0-2 and T20-50 samples before and after carbonation at 50°C and 15% moisture content. Qualitatively, it can be observed that the calcite peaks for both T0-2 and T20-50 samples increased after carbonation, together with the disappearance of portlandite peaks, which explains the decrease in pH after carbonation due to the conversion of portlandite to calcite.

Figure 7-4: XRD patterns of untreated and carbonated IBA at 50°C and 15% moisture content of (a) T0-2 and (b) T20-50 samples. [An = anhydrite, Ca = calcite, H = hematite, M = magnetite, P = portlandite, Q = quartz]

Table 7-2 shows the quantified mineralogical composition for different size fractions of TSIP samples after carbonation, determined by the Rietveld method. Comparing the values in Table 7-1 and 7-2, calcite content was verified to increase in quantity after carbonation while anhydrite, portlandite and ettringite decreased in quantity. This consistency in the decrease of anhydrite content after carbonation for all the size fractions shows that anhydrite was carbonated. Therefore, the increase in SO_4^{2-} leaching, as reported in Sections 5.3.5 and 6.3.4, could be due to the conversion of anhydrite to calcite. Other mineral, such as ettringite, is also known to contribute to SO_4^{2-} leaching due to its dissolution after carbonation (Meima et al., 2002). Although this study has shown possible high correlation between SO_4^{2-} leaching and degree of carbonation based on the conversion of anhydrite to calcite, Figure 5-20 shows relatively lower R value between SO_4^{2-} leaching and degree of

carbonation for T0-2 sample. As discussed in Section 5.3.5, Figure 5-19 shows that for most of the carbonation conditions for T0-2 sample, SO_4^{2-} leaching reached a plateau after 2 hours of carbonation. This could be due to the lower anhydrite content in T0-2 and similar ettringite content between S0-2 and T0-2. The conversion of anhydrite to calcite and dissolution of ettringite may have taken place and largely completed in the first 2 hours of carbonation, which then resulted in a relatively lower R value between SO_4^{2-} leaching and degree of carbonation (Figure 5-20).

Comparing between the different carbonation temperatures, T0-2 and T2-4 carbonated samples showed relatively higher calcite content for samples carbonated at 50°C than at 35°C (Table 7-2). However, the calcite content was similar for T4-20 and T20-50 carbonated samples. This is in agreement with the degree of carbonation discussed earlier, whereby the coarse size fractions were found to be not affected by the carbonation temperatures used.

After carbonation, the amount of malachite ($\text{Cu}_2(\text{OH})_2\text{CO}_3$) did not increase for T0-2 sample (Tables 7-1 and 7-2). Earlier in Section 5.3.5, it was suggested that the reduction in Cu leaching from T0-2 sample could result from the formation of insoluble carbonate mineral after carbonation. This is deduced from the higher R value between the degree of carbonation and Cu leaching (Figure 5-7c), as compared to the R value between DOC and Cu leaching (Figure 5-10b). Meima et al. (1999) suggested that carbonate mineral like malachite, could be controlling the solubility of Cu. Despite the lack of increase in malachite content for T0-2 carbonated sample, it is possible that the presence of malachite may contribute to the solubility control of Cu, in addition to the influence from DOC, as can be seen from the similar R values for S0-2 carbonated sample (Figure 5-7a and 5-10a). However, in terms of the different size fractions, the relatively high correlation between Cu and DOC leaching (Figure 6-4), could be due to the high magnetite content found in the coarse fractions, as will be further discussed below.

Another observation in the change in mineralogy after carbonation was the increase in wuestite (FeO) content for all the size fractions. The content of other Fe oxides (i.e. hematite, magnetite, goethite and marcasite) remained relatively similar after carbonation. Fe oxides played an important role in reducing the leachability of constituents, such as DOC and oxyanions, after carbonation (Cornelis et al., 2008; Arickx et al., 2010). Among the different size fractions, T4-20 has the highest reduction in DOC leaching (Figure 6-8). Similarly, the reduction in Cr leaching for T0-2 samples was an average of 62.2%, which was less significant compared to other size fractions (i.e. 83.0 to 94.9%) (Figure 6-5). The highest reduction for Mo leaching was T4-20 carbonated sample (Figure 6-6). It is observed that magnetite content was higher in coarse size fractions. The higher magnetite content in coarser TSIP samples could have contributed to more significant reduction in DOC, Cr and Mo leaching. Only Sb showed increment in leaching for all the size fractions after carbonation. Although researches have shown the adsorption capacity of Sb by Fe oxides (Cornelis et al., 2006; Leuz et al., 2006), Verbinnen et al. (2013) showed that the presence of soluble molybdate and chloride could result in the reduction of Sb adsorption on magnetite.

The presence of magnetite cannot fully explain the high variability of Mo and Sb leaching observed between S0-2 and T0-2 carbonated samples. Xu et al. (2006) reported that the adsorption of MoO_4^{2-} to goethite is more stable. It is possible that the higher Mo leaching for T0-2 sample carbonated at 42.5°C and 15% moisture content was due to the absence of goethite in T0-2 carbonated sample (Table 7-2). However, this finding should be further verified as the absence of goethite did not consistently result in higher Mo leaching at other carbonation conditions. The effect from competitive anions for adsorption sites, as in the case for Sb, could be a more possible explanation for the high variation in Mo and Sb leaching. Lastly, the increase in Sb leaching after carbonation, which could be due to the dissolution of romeites ($\text{Ca}_{1.13}\text{Sb}_2\text{O}_6(\text{OH})_{0.26} \cdot 0.74\text{H}_2\text{O}$), could not be verified as romeites was not detected during mineral identification.

Table 7-2. Comparison of mineralogical composition (in wt%) after accelerated carbonation at 35°C and 50°C, 15% moisture content for different size fractions of TSIP samples, using Rietveld method for quantitative XRD analysis.

Mineral	Chemical formula	T0-2		T2-4		T4-20		T20-50	
		35C15MC	50C15MC	35C15MC	50C15MC	35C15MC	50C15MC	35C15MC	50C15MC
Calcite	CaCO_3	32.98	34.60	21.33	23.37	20.08	20.94	11.56	10.74
Anhydrite	CaSO_4	18.21	18.02	7.95	9.00	3.03	3.72	0.68	0.56
Magnesium calcite	$\text{Ca}_{0.97}\text{Mg}_{0.03}\text{CO}_3$	1.05	2.00	0.26	N.D.	N.D.	N.D.	N.D.	N.D.
Portlandite	$\text{Ca}(\text{OH})_2$	1.12	N.D.	N.D.	0.02	N.D.	N.D.	N.D.	N.D.
Ettringite	$\text{Ca}_6\text{Al}_2(\text{SO}_4)_3(\text{OH})_{12} \cdot 26\text{H}_2\text{O}$	0.01	0.07	0.04	N.D.	0.38	0.17	N.D.	N.D.
Gehlenite	$\text{Ca}_2\text{Al}_2\text{SiO}_7$	0.71	0.48	0.63	N.D.	0.50	0.91	1.34	2.63
Diopside	$\text{CaMg}(\text{Si}_2\text{O}_6)$	0.74	0.98	3.43	6.28	10.74	13.06	16.34	16.82
Hydroxyl-apatite	$\text{Ca}_5(\text{PO}_4)_3(\text{OH})$	N.D.	N.D.	N.D.	0.12	N.D.	N.D.	N.D.	0.07
Calcium Zinc Aluminosilicate	$(\text{Ca}_{0.97}\text{Zn}_{0.03})_2(\text{Al}_{0.63}\text{Zn}_{0.37})(\text{Si}_{0.69}\text{Al}_{0.31})_2\text{O}_7$	3.80	5.58	3.87	7.04	8.30	5.08	5.10	6.16
Powellite	CaMoO_4	N.D.	N.D.	0.01	N.D.	N.D.	N.D.	N.D.	N.D.
-	CaO_4Ti_2	0.52	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	0.02
Anthophyllite	$\text{Mg}_7\text{Si}_8\text{O}_{22}(\text{OH})_2$	N.D.	0.69	3.28	1.68	2.98	5.09	3.29	0.89
Quartz	SiO_2	29.49	23.29	40.19	34.78	36.94	31.68	44.29	43.41

Mineral (Cont'd)	Chemical formula	T0-2		T2-4		T4-20		T20-50	
		35C15MC	50C15MC	35C15MC	50C15MC	35C15MC	50C15MC	35C15MC	50C15MC
Hematite	Fe ₂ O ₃	4.44	4.60	5.67	7.01	3.10	2.64	1.24	1.50
Magnetite	Fe ₃ O ₄	2.78	4.39	3.88	4.11	7.22	8.13	10.18	8.31
Goethite	FeOOH	N.D.	N.D.	N.D.	1.17	N.D.	N.D.	N.D.	0.55
Wuestite	FeO	0.15	0.41	1.27	0.86	2.19	2.61	1.19	2.31
Marcasite	FeS ₂	0.31	0.32	N.D.	N.D.	N.D.	N.D.	0.53	0.45
Gibbsite	Al(OH) ₃	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
Corundum	Al ₂ O ₃	1.74	1.64	5.50	2.57	2.71	5.38	3.88	5.56
Halite	NaCl	1.79	2.61	1.77	1.11	1.52	N.D.	N.D.	0.03
Sylvine	KCl	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
Malachite	Cu ₂ (OH) ₂ CO ₃	0.16	0.33	0.91	0.86	0.29	0.59	0.38	N.D.
GOF		4.25	4.26	4.95	4.35	4.21	4.11	5.06	4.65
R _{exp}		14.16	14.43	14.37	15.45	16.50	16.50	15.16	16.02
R _{wp}		60.20	61.43	71.15	67.14	69.47	67.74	76.76	74.43

N.D.: not detected

7.4 Conclusion

XRD analysis was carried out to determine the mineralogical composition of IBA and the Rietveld refinement method was used to quantify the weight percentage of the minerals identified. The GOF was found to be ~4, which is considered imperfect, as firstly, amorphous material in IBA was not considered in this study, and secondly, certain peaks were not identified due to the unavailability of ICDD files. However, this study was able to identify the major and common minerals found in IBA and applied them in the Rietveld calculation. This enables the quantified minerals to be compared among the different source of IBA and size fractions.

The mineralogical compositions of untreated S0-2 and T0-2 samples were compared. Based on the Rietveld calculation, diopside was undetectable in S0-2 sample while powellite, goethite, gibbsite and sylvine were undetectable in T0-2 sample. Anhydrite was observed to be present in higher quantity in untreated S0-2 than T0-2, which could be the reason for the different optimum carbonation temperatures. Among the untreated four size fractions of TSIP samples, calcite, anhydrite, portlandite and halite content decreased as the size increased. In contrast, quartz and corundum content increased as the size increased. Lastly, coarse size fractions were detected with higher content of Si- minerals and the absence of halite and sylvine.

After carbonation, calcite and wuestite increased in quantity while anhydrite, portlandite and ettringite decreased in quantity. From this study, it seems that the increase in calcite after carbonation was not the direct contributor to the reduction in leaching. Rather, the effect of carbonation resulted in the decrease in pH and the formation of secondary minerals (Fe oxides), which then contributed to the reduction in leaching through solubility control and adsorption. Moreover, due to the difference in mineral content in the different size fractions, the effect of carbonation resulted in varying percentage of reduction in leaching from the different size fractions.

CHAPTER 8: CONCLUSION AND RECOMMENDATION

8.1 Conclusion

The motivation behind this research is to increase the potential of utilising IBA by offering a treatment method that is sustainable and economically viable. This study explored the use of accelerated carbonation as a treatment method for IBA in Singapore as it has been overlooked up till now. The approach to this study was firstly, to characterise the IBA in Singapore and compare it with the IBA from other countries through literature review. The accelerated carbonation study was then carried out in two parts. In the first part, the influence of moisture content and temperature on accelerated carbonation was investigated using the 0-2 mm size fraction of IBA. The optimum operating conditions found in the first part was then applied to other size fractions (i.e. 2-4 mm, 4-20 mm and 20-50 mm) in the second part of the study. By sieving the IBA into different size fractions before accelerated carbonation, the different chemical compositions of the different size fractions can provide an insight into the carbonation mechanism of the accelerated carbonation process. In terms of utilisation, sieving is a simple and inexpensive method to separate IBA into the size fractions as required in different construction applications. Lastly, XRD was used to analyse the mineralogical composition of IBA.

The characterisation of IBA collected over a 6 months period has shown that the total trace element contents of IBA from both incineration plants in Singapore are similar to those in other countries reported in literature. Comparing between the two incineration plants, the total trace element content showed significant differences for elements like Cd, Mn, Pb and Sb, which could be associated with the dominant types of waste received by the plants. However, elements like Cd, Co, Hg, Pb and Se exhibited high variation over the investigated sampling period. Pb showed similar high variation in leaching test. Compared to landfill disposal criteria and effluent criteria in Singapore, Cu and Pb from both incineration plants did not meet the criteria for watercourse discharge while F⁻ from SWTEP did not meet the sewer criteria, if no treatment was carried out. This characterisation study has shown that Pb is a problem when considering the utilisation of Singapore's IBA due to its high

variation in both the total content and leachate concentration. Without treatment, the heavy metal leaching will restrict the application of IBA to confined areas, of which the infiltration of water to IBA has to be minimised and closely monitored. The accelerated carbonation study has shown that carbonation is effective in reducing the concentration of Pb from both incineration plants to $<5 \mu\text{g/L}$, regardless of the degree of carbonation. In contrast, accelerated carbonation has increased the leachability of Mo, Sb and SO_4^{2-} . The key results of the accelerated carbonation experiments are summarised as below:

Chapter 5

- The actual moisture content of IBA was found to change during carbonation, which affected the initial rate of carbonation. The rate of moisture loss and gain was dependent on the carbonation temperature.
- The optimum operating conditions for 0-2 mm size fraction (ground to $<425 \mu\text{m}$) at 20% CO_2 , was 35°C and 15% moisture content for SWTEP sample; and 50°C and 15% moisture content for TSIP sample. The carbonation duration was 2 hours.
- Under the optimum operating conditions, pH decreased from around 12.5 to 10 for both incineration plants after 2 hours of carbonation.
- For the 0-2 mm carbonated samples, Pb, Zn and Cu showed significant reduction in leaching after carbonation. Cr leaching initially increased but eventually decreased after 1 week of carbonation. Mo and Sb leaching increased after carbonation. Cl^- leaching was not significantly affected by carbonation, but SO_4^{2-} leaching increased significantly after carbonation.

Chapter 6

- The optimum operating conditions found in 0-2 mm size fraction was applied to the other size fractions. Both the 4-20 mm and 20-50 mm size fractions from both sources of IBA did not show significant difference in degree of carbonation when different carbonated temperatures were used.
- In terms of the different size fractions, most of the elements showed decrease in leaching as the size increased for untreated samples.

- The pH of the different size fractions reduced from around 12.5 to 9 after accelerated carbonation.
- For all the size fractions, Pb, Zn, Cu, Cr and DOC leaching decreased after carbonation. However, carbonation did not affect Cl^- leaching. Mo leaching increased for SWTEP but not TSIP sample, while Sb and SO_4^{2-} leaching increased significantly after carbonation.
- ANC results showed that 0-2 mm size fraction required more acid to reduce the pH as compared to other size fractions.

XRD was used to analyse the mineralogical composition of IBA, in conjunction with the various operating conditions for accelerated carbonation and leaching tests, to understand the physicochemical mechanism of accelerated carbonation and its influences on the leaching behaviour of IBA. The key findings are summarised as below:

Carbonation mechanism

In terms of 0-2 mm size fraction, the different optimum carbonation temperature for SWTEP and TSIP samples was attributed to the differences in mineralogical composition between the two incineration plants. Rietveld calculation found that anhydrite was higher in S0-2 sample while both S0-2 and T0-2 samples showed similar quantity for portlandite. The carbonation of anhydrite, which takes place at a lower log K (25°C) than portlandite (Bodéan et al., 2000) (Eq. 7-1 and 7-2), may have contributed to the lower carbonation temperature needed for S0-2 sample (i.e. 35°C), as compared to T0-2 sample (i.e. 50°C).

In terms of the different size fractions, anhydrite and portlandite showed decreasing intensity with increased size. Based on this observation, it is not sufficient to explain why the coarse size fractions showed lack of sensitivity towards the different carbonation temperatures used. However, the decreasing anhydrite and portlandite content was in agreement with the decreasing degree of carbonation as size increased. This decrease in the degree of carbonation also corresponded to the decrease in the total Ca content with increasing size. The mineralogical study has

shown that the coarse size fractions of 4-20 mm and 20-50 mm consisted mostly of quartz. Several minerals found in 0-2 mm were not present here, especially halite (NaCl) and sylvine (KCl). Therefore, this shows that the coarse size fractions have higher utilisation potential and it is possible that it can be used with less treatment.

Lastly, the decrease in buffering capacity (based on ANC) with increasing size was due to the lower portlandite content in coarse size fractions.

Overall, the XRD patterns showed the untreated IBA samples have high crystallinity, although IBA is commonly known to have high content of amorphous phase. This could be due to the inclusion of grate sifting, boiler and economiser ash to the IBA in the incineration plants.

Leaching mechanism

For Pb and Zn, after only 2 hours of carbonation, regardless of the degree of carbonation, Pb was below the detection limit in the leachate while Zn leaching was reduced by ~97% for S0-2 and T0-2 samples. The other size fractions also showed similar reduction after carbonation where Pb and Zn leaching were below the detection limit. After 2 hours of carbonation, the pH of all the size fractions reduced to 9-10. Based on the pH-static leaching test, it can be shown that this pH coincides with the minimum solubility of Pb and Zn. Therefore, the dominant factor of the leaching mechanism for Pb and Zn was pH.

For Cu, the contributing factors are degree of carbonation and DOC. For S0-2 sample, degree of carbonation and DOC seems to affect Cu leaching equally. However, for T0-2 sample, the contribution from degree of carbonation seems to be higher than that of DOC. The presence of malachite detected by XRD in T0-2 untreated sample could have contributed to the solubility control of Cu. pH did not play a significant role in reducing Cu leaching from carbonated 0-2 mm samples. Likewise, pH did not influence the decrease in DOC leaching after carbonation. In terms of the different size fractions, the correlation between the amount of Cu and DOC released was high. This difference in conclusion for 0-2 mm and the rest of

the size fractions could be due to the greater influence from the operating conditions on the degree of carbonation, which affected 0-2 mm more than other size fractions. Furthermore, the percentage reduction for DOC was highest for S4-20 and T4-20 samples. XRD detected the presence of higher magnetite content as size increased for TSIP sample. This could also contribute to the high correlation between the amount of Cu and DOC released for the different size fractions due to the adsorption of DOC to secondary minerals like Fe/Al (hydr)oxides formed after carbonation.

For Cr, the similarity in the measured pH profile of carbonated sample and pH-static leaching of untreated sample showed that pH was a dominant factor for 0-2 mm size fraction. The other size fractions of SWTEP and TSIP samples had more significant reduction in Cr leaching, compared to 0-2 mm size fraction. This could be attributed to the lower pH attained by the other size fractions after carbonation. In addition, the varying percentage reduction in Cr leaching in the different size fractions could be due to the higher magnetite content found in coarser TSIP samples as Fe oxides act as possible adsorption site for oxyanions, such as Cr.

For Mo and Sb, their leaching mechanism cannot be fully explained based on current study. Other factors, such as redox potential, could have affected their leaching but was not investigated in this study. As this study has shown, both degree of carbonation and pH did not show consistent influence on the leaching mechanism of Mo and Sb. The higher Mo leaching in T0-2 untreated sample could be due to the higher total Mo content in T0-2 (as compared to S0-2) and the absence of powellite in T0-2. For Sb, the increase in leaching after carbonation could be due to the dissolution of romeites, but this could not be verified as romeites was not detected during mineral identification. However, based on the pH-static leaching test, the pH after carbonation (i.e. around 9-10) coincides with an increase in Mo and Sb solubility. Lastly, in terms of the different size fractions, Mo leaching increased for SWTEP but not TSIP samples, while Sb leaching increased for both samples. A possible explanation for the high variability in Mo and Sb leaching after

carbonation could be due to the competing effect from other anions for adsorption sites.

For SO_4^{2-} , the increase in leaching was attributed to the conversion of anhydrite to calcite and dissolution of ettringite after carbonation. SO_4^{2-} leaching was found to be influenced by the degree of carbonation for S0-2 sample but not T0-2 sample. T0-2 sample showed that SO_4^{2-} leaching reached a plateau after 2 hours of carbonation. This could be due to the lower anhydrite content in T0-2 and similar ettringite content between S0-2 and T0-2. The conversion of anhydrite to calcite and dissolution of ettringite may have taken place and largely completed in the first 2 hours of carbonation, which then resulted in a relatively lower R value between SO_4^{2-} leaching and degree of carbonation.

This study on the accelerated carbonation has shown great potential as a treatment for IBA in reducing the leachability of Pb, Zn, Cu, Cr and DOC. This is important as Pb was observed to exhibit high variation in the total content and leaching of untreated IBA during the 6 months characterisation. However, the limitation of this treatment process was the increase in leaching of Mo, Sb and SO_4^{2-} due to the different leaching mechanisms, as discussed in this study. These constituents would have to be treated by other methods, such as washing.

In conclusion, the objective of understanding the physicochemical mechanism of accelerated carbonation and its influences on the leaching behaviour of IBA has been achieved in this research. This will provide an alternative treatment process to enhance the utilisation potential of IBA in Singapore.

8.2 Recommendation

This study has shown that accelerated carbonation has the potential to treat IBA within a short time frame. However, the research carried out here was focused on understanding the carbonation and leaching mechanism, hence the different size fractions were ground to $<425\ \mu\text{m}$. This is to minimise the effect of different surface area of each size fraction on accelerated carbonation. However, grinding

IBA into fine powder would not be practical in real application. Therefore, in continuation to this study, it is proposed that the investigation on the leaching behaviour of the different size fractions of untreated IBA be conducted without grinding or with minimal size reduction to the particle size required in a specific application. Size reduction of IBA increases the surface area in contact with the leachant, which may increase the leachability of some elements. As this study has shown, most of the elements showed decrease in leaching for the untreated IBA as the size increases. The carbonation duration for the coarser size fractions may also be further reduced, if the leaching of untreated IBA without size reduction is lower than that with grinding.

There are other leaching mechanisms of IBA, like sorption on secondary minerals formed after carbonation, which were cited from literature and discussed here, but not verified experimentally. These are important research areas that can be explored further.

Another possible future study is to carry out the accelerated carbonation in a continuous gas flow column system, instead of the current enclosed batch system. Factors such as the gas flow rate and packing density would have to be investigated, with reference to the knowledge gained from this study.

REFERENCE

- Arickx, S., T. Van Gerven and C. Vandecasteele (2006). "Accelerated carbonation for treatment of MSWI bottom ash." Journal of Hazardous Materials 137(1): 235-243.
- Arickx, S., T. Van Gerven, E. Boydens, P. L'hoëst, B. Blanpain and C. Vandecasteele (2008). "Speciation of Cu in MSWI bottom ash and its relation to Cu leaching." Applied Geochemistry 23(12): 3642-3650.
- Arickx, S., V. De Borger, T. Van Gerven and C. Vandecasteele (2010). "Effect of carbonation on the leaching of organic carbon and of copper from MSWI bottom ash." Waste Management 30(7): 1296-1302.
- Astrup, T. (2007). "Pretreatment and utilization of waste incineration bottom ashes: Danish experiences." Waste Management 27(10): 1452-1457.
- Baciocchi, R., G. Costa, E. Lategano, C. Marini, A. Poletti, R. Pomi, P. Postorino and S. Rocca (2010). "Accelerated carbonation of different size fractions of bottom ash from RDF incineration." Waste Management 30(7): 1310-1317.
- Bayuseno, A. P. and W. W. Schmahl (2010). "Understanding the chemical and mineralogical properties of the inorganic portion of MSWI bottom ash." Waste Management 30(8-9): 1509-1520.
- Bodéan, F., M. Azaroual and P. Piantone (2000). Forecasting the long-term behaviour of municipal solid waste incineration bottom ash: rapid combined tests. Waste Management Series. 1: 475-482.
- Boghetich, G., L. Liberti, M. Notarnicola, M. Palma and D. Petruzzelli (2005). "Chloride extraction for quality improvement of municipal solid waste incinerator ash for the concrete industry." Waste Management and Research 23(1): 57-61.

CEU (1999). Council directive 1999/31/EC of 26 April 1999 on the landfill of waste.

CEU (2003). Council decision 2003/33/EC of 19 December 2002 establishing criteria and procedures for the acceptance of waste at landfills pursuant to Article 16 of and Annex II to Directive 1999/31/EC.

Chandler, J., T.T. Eighmy, J. Hartlén, O. Hjelm, D.S. Kosson, S.E. Sawell, H.A. van der Sloot, J. Vehlow (1997) "Municipal Solid Waste Incinerator Residues", In: Studies in Environmental Science, Vol. 67, Elsevier: Amsterdam, The Netherlands.

Chimenos, J. M., M. Segarra, M. A. Fernández and F. Espiell (1999). "Characterization of the bottom ash in municipal solid waste incinerator." Journal of Hazardous Materials 64(3): 211-222.

Chimenos, J. M., A. I. Fernández, L. Miralles, M. Segarra and F. Espiell (2003). "Short-term natural weathering of MSWI bottom ash as a function of particle size." Waste Management 23(10): 887-895.

Comans, R. N. J. and J. A. Meima (1994). "Modelling Ca-solubility in MSWI bottom ASH leachates." Studies in Environmental Science 60(C): 103-110.

Cornelis, G., T. Van Gerven and C. Vandecasteele (2006). "Antimony leaching from uncarbonated and carbonated MSWI bottom ash." Journal of Hazardous Materials 137(3): 1284-1292.

Cornelis, G., C. A. Johnson, T. V. Gerven and C. Vandecasteele (2008). "Leaching mechanisms of oxyanionic metalloid and metal species in alkaline solid wastes: A review." Applied Geochemistry 23(5): 955-976.

Cornelis, G., T. Van Gerven and C. Vandecasteele (2012). "Antimony leaching from MSWI bottom ash: modelling of the effect of pH and carbonation." Waste Management 32(2): 278-286.

Costa, G., R. Baciocchi, A. Poletti, R. Pomi, C. D. Hills and P. J. Carey (2007). "Current status and perspectives of accelerated carbonation processes on municipal waste combustion residues." Environmental Monitoring and Assessment 135(1-3): 55-75.

Dijkstra, J. J., A. Van Zomeren, J. C. L. Meeussen and R. N. J. Comans (2006). "Effect of accelerated aging of MSWI bottom ash on the leaching mechanisms of copper and molybdenum." Environmental Science and Technology 40(14): 4481-4487.

Eighmy, T. T., J. D. Eusden, K. Marsella, J. Hogan, D. Domingo, J. E. Krzanowski and D. Stämpfli (1994). "Particle petrogenesis and speciation of elements in MSW incineration bottom ashes." Studies in Environmental Science 60(C): 111-136.

Fauth, D. J., Y. Soong and C. M. White (2002). "Carbon sequestration utilizing industrial solid residues." 224th ACS National Meeting, Orlando, FL.

Fernández Bertos, M., X. Li, S. J. R. Simons, C. D. Hills and P. J. Carey (2004a). "Investigation of accelerated carbonation for the stabilisation of MSW incinerator ashes and the sequestration of CO₂." Green Chemistry 6(8): 428-436.

Fernandez Bertos, M., S. J. Simons, C. D. Hills and P. J. Carey (2004b). "A review of accelerated carbonation technology in the treatment of cement-based materials and sequestration of CO₂." Journal of Hazardous Materials 112(3): 193-205.

Filipponi, P., A. Poletti, R. Pomi and P. Sirini (2003). "Physical and mechanical properties of cement-based products containing incineration bottom ash." Waste Management 23(2): 145-156.

Freyssinet, P., P. Piantone, M. Azaroual, Y. Itard, B. Clozel-Leloup, D. Guyonnet and J. C. Baubron (2002). "Chemical changes and leachate mass balance of municipal solid waste bottom ash submitted to weathering." Waste Management 22(2): 159-172.

Goh, C. C., K. Y. Show and H. K. Cheong (2003). "Municipal solid waste fly ash as a blended cement material." Journal of Materials in Civil Engineering 15(6): 513-523.

International Centre for Diffraction Data (ICDD) (2001). The Powder Diffraction File (PDF).

Ito, R., T. Fujita, J. Sadaki, Y. Matsumoto and J. -W. Ahn (2006). "Removal of chloride in bottom ash from the industrial and municipal solid waste incinerators." International Journal of the Society of Material Engineering for Resources 13(2): 70-74.

Izquierdo, M., A. López-Soler, E. V. Ramonich, M. Barra and X. Querol (2002). "Characterisation of bottom ash from municipal solid waste incineration in Catalonia." Journal of Chemical Technology and Biotechnology 77(5): 576-583.

Johnson, C. A., S. Brandenberger and P. Baccini (1995). "Acid neutralizing capacity of municipal waste incinerator bottom ash." Environmental Science & Technology 29(1): 142-147.

Kirby, C. S. and J. D. Rimstidt (1993). "Mineralogy and surface properties of municipal solid waste ash." Environmental Science and Technology 27(4): 652-660.

Kirby, C. S. and J. D. Rimstidt (1994). "Interaction of municipal solid waste ash with water." Environmental Science and Technology 28(3): 443-451.

Kotaś, J. and Z. Stasicka (2000). "Chromium occurrence in the environment and methods of its speciation." Environmental Pollution 107(3): 263-283.

Lackner, K. S., C. H. Wendt, D. P. Butt, B. L. Joyce and D. H. Sharp (1995). "Carbon dioxide disposal in carbonate minerals." Energy 20(11): 1153-1170.

Leuz, A. -K., H. Mönch, C. A. Johnson (2006). "Sorption of Sb(III) and Sb(V) to goethite: Influence on Sb(III) oxidation and mobilization." Environmental Science and Technology 40(23): 7277-7282.

Lim, M., G. C. Han, J. W. Ahn and K. S. You (2010). "Environmental remediation and conversion of carbon dioxide (CO₂) into useful green products by accelerated carbonation technology." International Journal of Environmental Research and Public Health 7(1): 203-228.

Mahieux, P. -Y., J. -E. Aubert, M. Cyr, M. Coutand and B. Husson (2010). "Quantitative mineralogical composition of complex mineral wastes – Contribution of the Rietveld method." Waste Management 30(3): 378-388.

Meima, J. A. and R. N. J. Comans (1997a). "Overview of geochemical processes controlling leaching characteristics of MSWI bottom ash." Studies in Environmental Science 71(C): 447-457.

Meima, J. A. and R. N. J. Comans (1997b). "Geochemical modeling of weathering reactions in municipal solid waste incinerator bottom ash." Environmental Science and Technology 31(5): 1269-1276.

Meima, J. A. and R. N. J. Comans (1999). "The leaching of trace elements from municipal solid waste incinerator bottom ash at different stages of weathering." Applied Geochemistry 14(2): 159-171.

Meima, J. A., A. Van Zomeren and R. N. J. Comans (1999). "Complexation of Cu with dissolved organic carbon in municipal solid waste incinerator bottom ash leachates." Environmental Science and Technology 33(9): 1424-1429.

Meima, J. A., R. D. Van Der Weijden, T. T. Eighmy and R. N. J. Comans (2002). "Carbonation processes in municipal solid waste incinerator bottom ash and their effect on the leaching of copper and molybdenum." Applied Geochemistry 17(12): 1503-1513.

Monteiro, R. C. C., C. F. Figueiredo, M. S. Alendouro, M. C. Ferro, E. J. R. Davim and M. H. V. Fernandes (2008). "Characterization of MSWI bottom ashes towards utilization as glass raw material." Waste Management 28(7): 1119-1125.

Muchova, L., E. Bakker and P. Rem (2008). "Precious Metals in Municipal Solid Waste Incineration Bottom Ash." Water, Air, & Soil Pollution: Focus 9(1-2): 107-116.

Musselman, C. N., T. T. Eighmy, D. L. Gress, M. P. Killeen, J. R. Presher and M. H. Sills (1994). "New Hampshire bottom ash paving demonstration US route 3, Laconia, New Hampshire." Proceedings of National Waste Processing Conference.

Olsson, S., J. W. J. Van Schaik, J. P. Gustafsson, D. B. Kleja and P. A. W. Van Hees (2007). "Copper(II) binding to dissolved organic matter fractions in municipal solid waste incinerator bottom ash leachate." Environmental Science and Technology 41(12): 4286-4291.

Paoletti, F., P. Sirini, H. Seifert and J. Vehlow (2001). "Fate of antimony in municipal solid waste incineration." Chemosphere 42(5-7): 533-543.

Pera, J., L. Coutaz, J. Ambroise and M. Chababbet (1997). "Use of incinerator bottom ash in concrete." Cement and Concrete Research 27(1): 1-5.

Piantone, P., F. Bodéan and L. Chatelet-Snidaro (2004). "Mineralogical study of secondary mineral phases from weathered MSWI bottom ash: implications for the modelling and trapping of heavy metals." Applied Geochemistry 19(12): 1891-1904.

Polettini, A. and R. Pomi (2004). "The leaching behavior of incinerator bottom ash as affected by accelerated ageing." Journal of Hazardous Materials 113(1-3): 209-215.

Prigiobbe, V., A. Polettini and R. Baciocchi (2009). "Gas–solid carbonation kinetics of Air Pollution Control residues for CO₂ storage." Chemical Engineering Journal 148(2-3): 270-278.

Prince, E. (1995). "Mathematical Aspects of Rietveld Refinement. " In: Young, R. A. (Ed.) The Rietveld Method. International Union of Crystallography, Oxford, New York: 43-54.

Rendek, E., G. Ducom and P. Germain (2006). "Carbon dioxide sequestration in municipal solid waste incinerator (MSWI) bottom ash." Journal of Hazardous Materials 128(1): 73-79.

Rendek, E., G. Ducom and P. Germain (2007). "Assessment of MSWI bottom ash organic carbon behavior: a biophysicochemical approach." Chemosphere 67(8): 1582-1587.

Rietveld, H. M. (1969). "A profile refinement method for nuclear and magnetic structures." Journal of Applied Crystallography 2: 65-71.

Santos, R. M., G. Mertens, M. Salman, O. Cizer and T. Van Gerven (2013). "Comparative study of ageing, heat treatment and accelerated carbonation for stabilization of municipal solid waste incineration bottom ash in view of reducing

regulated heavy metal/metalloid leaching." Journal of Environmental Management 128: 807-821.

Speiser, C., T. Baumann and R. Niessner (2000). "Morphological and chemical characterization of calcium-hydrate phases formed in alteration processes of deposited municipal solid waste incinerator bottom ash." Environmental Science and Technology 34(23): 5030-5037.

Speiser, C., T. Baumann and R. Niessner (2001). "Characterization of municipal solid waste incineration (MSWI) bottom ash by scanning electron microscopy and quantitative energy dispersive X-ray microanalysis (SEM/EDX)." Fresenius' Journal of Analytical Chemistry 370(6): 752-759.

Stegemann, J. A. and J. Schneider (1991). "Leaching potential of municipal waste incinerator bottom ash as a function of particle size distribution." In: Goumans, J. J. J. M., van der Sloot, H. A. and Aalbers, Th. G. (Eds.), Waste Materials in Construction, Studies in Environmental Science, Elsevier. Volume 48: 135-143.

Sun, J., M. F. Bertos, S. J. R. Simons (2008). "Kinetic study of accelerated carbonation of municipal solid waste incinerator air pollution control residues for sequestration of flue gas CO₂." Energy & Environmental Science 1(3): 370-377.

Tay, J. H. (1988). "Energy generation and resources recovery from refuse incineration." Journal of Energy Engineering 114(3): 107-117.

Tay, J. H. and H. K. Cheong (1991). "Use of ash derived from refuse incineration as a partial replacement of cement." Cement and Concrete Composites 13(3): 171-175.

Tay, J. H. and A. T. C. Goh (1991). "Engineering properties of incinerator residue." Journal of Environmental Engineering 117(2): 224-235.

The World Bank Annual Report (2012).

Todorovic, J. and H. Ecke (2006a). "Demobilisation of critical contaminants in four typical waste-to-energy ashes by carbonation." Waste Management 26(4): 430-441.

Todorovic, J. and H. Ecke (2006b). "Treatment of MSWI residues for utilization as secondary construction minerals: A review of methods." Minerals and Energy - Raw Materials Report 20(3-4): 45-59.

Todorovic, J., M. Svensson, I. Herrmann and H. Ecke (2006). "Artificial carbonation for controlling the mobility of critical elements in bottom ash." Journal of Material Cycles and Waste Management 8(2): 145-153.

Tyrer, M. (2013). "Municipal solid waste incinerator (MSWI) concrete." In: Pacheco-Torgal, F., Jalali, S., Labrincha, J., John, V. M. (Eds.), Eco-efficient concrete. Woodhead Publishing Limited, Cambridge, United Kingdom: 273-310.

Van der Sloot, H.A., Heasman, L., Quevauviller, Ph. (1997) "Harmonization of leaching/extraction tests", In: Studies in Environmental Science, Vol. 70, Elsevier: Amsterdam.

Van Gerven, T., E. Van Keer, S. Arickx, M. Jaspers, G. Wauters and C. Vandecasteele (2005). "Carbonation of MSWI-bottom ash to decrease heavy metal leaching, in view of recycling." Waste Management 25(3): 291-300.

Van Zomeren, A. and R. N. J. Comans (2004). "Contribution of natural organic matter to copper leaching from municipal solid waste incinerator bottom ash." Environmental Science and Technology 38(14): 3927-3932.

Verbinnen, B., C. Block, P. Lievens, A. Van Brecht and C. Vandecasteele (2013). "Simultaneous removal of molybdenum, antimony and selenium oxyanions from wastewater by adsorption on supported magnetite." Waste and Biomass Valorization 4(3): 635-645.

Wei, Y., T. Shimaoka, A. Saffarzadeh and F. Takahashi (2011). "Mineralogical characterization of municipal solid waste incineration bottom ash with an emphasis on heavy metal-bearing phases." Journal of Hazardous Materials 187(1-3): 534-543.

Will, G. (2006). Powder diffraction: the Rietveld method and the two-stage method to determine and refine crystal structures from powder diffraction data. Springer: Berlin, New York.

Xu, N., C. Christodoulatos and W. Braida (2006). "Adsorption of molybdate and tetrathiomolybdate onto pyrite and goethite: Effect of pH and competitive anions." Chemosphere 62(10): 1726-1735.

You, G. -S., J. -W. Ahn, G. -C. Han and H. -C. Cho (2006). "Neutralizing capacity of bottom ash from municipal solid waste incineration of different particle size." Korean Journal of Chemical Engineering 23(2): 237-240.

Zevenbergen, C., L. P. Van Reeuwijk, J. P. Bradley, P. Bloemen and R. N. J. Comans (1996). "Mechanism and conditions of clay formation during natural weathering of MSWI bottom ash." Clays and Clay Minerals 44(4): 546-552.