Real-time colorimetric hydration sensor for sport activities

Zhou, Yubin; Han, Htet; Naw, Hnin Pwint Phyuson; Lammy, Alice Venecia; Goh, Chee Hong; Boujday, Souhir; Steele, Terry W. J.

2015

Zhou, Y., Han, H., Naw, H. P. P., Lammy, A. V., Goh, C. H., Boujday, S., et al. (2016). Real-time colorimetric hydration sensor for sport activities. *Materials and Design*, 90, 1181-1185.

<https://hdl.handle.net/10356/80667>

<https://doi.org/10.1016/j.matdes.2015.06.078>

© 2015 Elsevier Ltd. This is the author created version of a work that has been peer reviewed and accepted for publication by *Materials and Design*, Elsevier Ltd. It incorporates referee's comments but changes resulting from the publishing process, such as copyediting, structural formatting, may not be reflected in this document. The published version is available at: [<http://dx.doi.org/10.1016/j.matdes.2015.06.078>].

Downloaded on 26 Apr 2023 10:21:30 SGT

REAL-TIME COLORIMETRIC **SENSOR** OF DEHYDRATION AND OVER-HYDRATION FOR SPORT ACTIVITIES

Yubin Zhou ^a, Htet Han ^a, Hnin Pwint Phyuson Naw ^a, Alice Venecia Lammy ^a, Chee
Hong Goh ^a, Souhir Boujday ^{b,c,*}, Terry W.J. Steele ^{a,*}

*a School of Materials Science & Engineering, College of Engineering, Nanyang
Technological University, 50 Nanyang Avenue, Singapore 639798, Singapore*

*b Sorbonne Universités, UPMC, Univ Paris 6, UMR CNRS 7197, Laboratoire de Réactivité
de Surface, F75005 Paris, France*

c CNRS, UMR 7197, Laboratoire de Réactivité de Surface, F75005 Paris, France

** Corresponding Author*

Souhir Boujday: souhir.boujday@upmc.fr, Terry W.J. Steele: wjsteele@ntu.edu.sg,

Tel.:65-65927594, fax: 65-67909081.

Abstract

Dehydration and over-hydration are a serious health concern in endurance sport activities, especially in tropical climates. Current methods for detection are inconvenient and not widely applied. Point-of-care hydration monitoring during a sport event is an ideal preventative therapy, as it allows personalize real-time feedback towards preventing hydration related injuries.

Gold nanoparticles allow colorimetric detection, whose color changes due to changes in colloidal stability. The red-shift in the plasmonic band induces a color change from red to purple upon aggregation that can be observed by the naked eye, which gives promising

applications in point-of-care preventative therapies. We developed a gold nanoparticle-based colorimetric sensor for rapid detection of dehydration and over-hydration by monitoring ‘proof-of-concept’ artificial sweat ion concentrations. The colorimetric sensor was designed to distinguish between dehydration and over-hydration through easily observed color changes. In addition, the sensor exhibited a fast response time within minutes. The designed sensor is a promising tool for point-of-care and real-time detection of dehydration and over-hydration.

Keywords: gold nanoparticles, colorimetric detection, sensor, sport activity, dehydration, over-hydration

1. Introduction

Endurance sport activities are often associated with fatigue, muscle cramps, and hydration imbalance. Among which dehydration is the most common due to the water loss in the form of sweat to keep the body cool during intensive sport activities. The human sweat contains not only water but also other mineral salts, lactic acid, glucose and urea [1]. Depending on the rate of rehydration of the individuals, hydration imbalances will be developed leading to two extreme conditions called dehydration and over-hydration [2]. Detection of hydration status requires complicated procedures to analyze body fluids such as sweat, blood, urine and saliva [3, 4] by analyzing body mass changes, urinary and hematological indices and salivary parameters [5]. Therefore, a non-invasive and easy-to-use technique is still in need to give real-time feedback during continuous strenuous exercise. Hydration status imbalance can be represented by the variation of electrolyte concentration in the sweat. Electrolytes in the sweat contain salts and dissolved ions such as sodium cations, which form the majority of the available ions other than potassium and calcium [1]. Hence, sweat sodium cations were

chosen to determine the hydration status with normal physiological sweat concentration at 40 mM, over-hydration at 26.5 mM and dehydration at 47.9 mM [6, 7].

Gold nanoparticles (AuNPs) have been widely studied and applied in many sensing application of inorganic ions [8] and biological analytes such as amino acids, peptides, proteins, and DNA fragments [9-13]. The optical properties of AuNPs enable their use for colorimetric transduction of molecular interactions simply by standard UV-Vis spectrometer or even by the naked eye [14-15]. Indeed, the small size of these particles compared to that of the visible wavelength gives rise to a strong extinction band in the visible wavelength regime upon collective electron oscillations [16]. This band is the localized surface plasmon resonance (LSPR) and its shape and position are closely dependent from local changes on particle surfaces and from their aggregation/dispersion state. It was reported that the addition of NaCl could induce the aggregation of the AuNPs, resulting in a color change because of the alteration in LSPR [17]. We use this property here to monitor the hydration state in sweat through the detection of standard values of salt concentration. The logic-gate based sensor was developed by tailoring the formulation of AuNPs. The designed model is able to give resolution in the concentration range of human body fluid. Figure 1 displays the working principal of the sensor. This design is applied to detect 26.5, 40 and 47.9 mM of NaCl in artificial sweat that correspond to over hydration, normal hydration and dehydration, respectively. These values are based on the data of average population, but the designed sensor can be customized for other ranges. The objective is displaying three distinguished colors for these three concentration levels within few minutes, which can be discerned by the naked eye. To the best of our knowledge, it is the first time applying AuNPs to sweat sensing for hydration imbalance detection. Therefore, this user friendly and responsive sensor is promising towards real time detection of ion concentrations in excreted body fluids.

Figure 1. Schematic illustration of the colorimetric sensor.

2. Experimental Work

All chemicals were purchased from Sigma-Aldrich Singapore. The procedure to synthesize AuNPs by reduction of ascorbic acid was modified from the literature [18-20]. In all the reactions, gold nanoparticle solutions were used at 0.35 g L^{-1} and the volume ratio of NaCl solution or artificial sweat to AuNPs solution was 5:1 unless otherwise stated. Briefly, the synthesis was started with 100 uL of 100 g L^{-1} chloroauric acid ($\text{HAuCl}_4 \cdot 3\text{H}_2\text{O}$), mixed with 25 mL of deionized water and 1.5 mL of 21.2 g L^{-1} sodium carbonate solution. The reaction was started by adding 2 mL of 7 g L^{-1} ascorbic acid under vigorous stirring at 1000 rpm on the magnetic stirrer for 15 minutes. The solution mixed was chilled with ice at about $0\text{-}2^\circ \text{C}$. The concentration of the obtained AuNPs solution is 0.35 g L^{-1} . Shimadzu UV-visible

spectrophotometer was used to measure the absorption spectra of the AuNPs solutions whereas Malvern Zeta Sizer, described previously [21], was used to measure the size and zeta potential of the AuNPs. NaCl solutions in concentrations of 40, 26.5 and 47.9 mM were used as indicators of normal physiological condition, over-hydration and dehydration. The final optimized formulation was applied to artificial sweat of pH 6.7 according to EN1811 standard [22].

3. Results & Discussion

3.1 Colorimetric sensing by using Ascorbic Capped AuNPs: Solutions with different concentrations of NaCl (0, 26.5, 40 and 47.9 mM) were added to the red ascorbic-capped Au nanoparticles. The observed color changes at different incubation times (0 to 30 min) are shown in Figure 2.

Figure 2. The different color of AuNPs solution in the presence of different concentrations of NaCl.

106

107 Figure 2 shows that in absence of NaCl, the AuNPs solutions with deionized water (negative
108 control) undergo no color change during the experiment. The AuNPs solution with NaCl 26.5
109 mM also did not display any detectable color change. Starting from 40 mM NaCl, AuNPs
110 solutions changed color from red to purple within 5 minutes. Color was stable during the
111 following 30 min indicating that the detection is achieved at this early stage. The color of
112 AuNPs solution with NaCl 47.9 mM transformed rapidly red to grey color solution at 5
113 minutes, with no color change thereafter. The results show that different colors, easily
114 identified by the naked eye could be obtained rapidly at NaCl concentration of 26.5, 40 and
115 47.9 mM which indicates the sensor can distinguish the hydration imbalance situations.

116

117 **3.2 UV-Vis measurement:** The color change of the AuNPs solutions was verified by
118 measuring the absorption spectra in the visible range by the UV-Vis spectrometer. Figure 3
119 shows the UV spectra of AuNPs in the presence of NaCl at a concentration of 26.5, 40 and
120 47.9 mM respectively as a function of time.

121 For 26.5 mM NaCl UV-Vis spectra weren't modified compared to the original AuNPs
122 solutions. Starting from 40 mM NaCl in the mixture, the intensity of the Plasmon band at 520
123 nm decreases while a broad band in the around 650 nm appears indicating the aggregation of
124 gold nanoparticles.

Figure 3. UV spectra of AuNPs in the presence of different concentration of NaCl as a function of time.

The ratio of absorbance at 650 to 520 nm (A_{650}/A_{520}) is a good indicator of the aggregation state of gold nanoparticle [23], this ratio in the presence of different concentrations of NaCl at different times is also analyzed in Figure 3. As the concentrations of NaCl increased from 26.5 to 40 and 47.9 mM, the A_{650}/A_{520} ratio increased indicating the decrease of dispersed particles and the increase of AuNPs aggregates. This aggregation induces the color change of the mixture. In addition, A_{650}/A_{520} ratio increases for NaCl concentration of 40 and 47.9 mM, indicating a higher aggregation state for high salt concentration, consistently with the observed color changes. Finally, the change in A_{650}/A_{520} ratio takes place only during the first 5 to 10 minutes suggesting that the equilibrium is rapidly reached and the color change is stable during at least 30 min.

3.3 Zeta Sizer Measurement: The sizes of AuNPs in the experiments were measured with Malvern Zeta Sizer. Figure 4 represents the change in size and zeta potential of the AuNPs solutions in the presence of NaCl solution as time proceeded. Upon the addition of the NaCl solution, the zeta potential of the AuNPs solution was unusually modified. The kinetic followed the previous observation by naked eye and UV-Vis, i.e. a rapid change and a stabilization after 10 min.

Figure 4. Size and Zeta Potential change of AuNPs as a function of time in the presence of different concentrations of NaCl: 26.5 mM (red) 40 mM (purple), 47.9 mM (grey).

The hydrodynamic radius of the AuNPs prior to NaCl addition was less than 30 nm. For the lowest NaCl concentration, 26.5 mM, this size wasn't modified during the measurement time, consistently with previously evidenced absence of aggregation. For higher salt concentrations, the measured radius increased without reaching a plateau. This discrepancy may simply result from the difficulty to measure accurately aggregates size. Nevertheless, the observed changes are in agreement with UV-Vis observation and evidence the dependence of colloids aggregation step on the tested range of salt concentration.

3.4 Detection of Artificial Sweat: The designed sensor was validated in artificial sweat samples. Artificial sweat was synthesized according to EN1811 standard. Figure 5 corresponds to the distinguished colors obtained by AuNPs solutions with the addition of EN1811 standard artificial sweat. The corresponding UV spectra are shown in the Supplementary Information (Figure S1) while the standard deviations (%) of the 26.5 mM, 40 mM and 47.9 mM samples are 1.8 %, 3.0 % and 1.0 %, respectively. Three distinct colors are obtained upon adding 26.5 mM, 40 mM and 47.9 mM of NaCl. We tested different concentrations of AuNPs and changed the ratio AuNP/NaCl. The optimal performances were obtained using 0.35 g L⁻¹ AuNP solution with 5:1 volume ratio of artificial sweat to AuNPs solution. The results from visual experiment, UV-spectrum and Zeta-potential show the functionality of this colorimetric sensor with the advantages of simplicity and accuracy. The advantage of using ascorbic acid as the capping agent is that it is less stable compared to citrate and other capping and thus optimization of tuning the size of AuNPs with NaCl solution and artificial sweat is more sensitive to NaCl concentrations. Non-invasive methods such as epidermal tattoo potentiometric sodium sensors [24] or the tattoo lactate sensors are current available biosensors. Other sweat sensors such as wearable sweat rate sensors [25] are again dependent of the electronic circuits [26]. Nevertheless, to the best of our knowledge, there is still no colorimetric sensor that monitors sweat sodium concentration for sports activities that applies color change method which is very convenient for the user. We are currently conducting experiments on selection of substrates and deposition methods. Adsorbent pads made from cellulose extraction thimbles, polycaprolactone, cellulose membrane, hydrophilic filter paper and blotting pad will be tried while deposition methods such freeze-drying and vacuum drying will be applied to develop our sensor into solid form.

Figure 5. The different colors of AuNPs with artificial sweat.

4. Conclusion

In this study, a colorimetric sensor for the detection of hydration level in buffer and artificial sweat was designed and developed. Detection of sodium cations at concentrations indicating over-hydration, normal hydration and dehydration state was achieved using ascorbic acid capped AuNPs. These particles aggregation/dispersion state occurred in the desired range of salt. Colorimetric changes from red to purple to grey with increasing salt concentrations were easily observable with UV-vis spectrometer and naked eyes. This sensor responds according the actual human body conditions during over hydration and dehydration typical of endurance events. Unlike the common assessment methods for sweat, this design can provide real time feedback. It reduces all the intricate methods of monitoring hydration condition by a visual indication of color change. This novel sensor has been shown to be promising for detection of hydration levels with many desirable properties, including simple detection display, high stability, and fast response time. Finally, this model of sensor may be developed to other kinds of detections for small changes of biological substances in excreted fluids.

Acknowledgement

Funding was greatly appreciated from the Ministry of Education Tier 1 Grant RG54/13: “Photochrome Aptamer Switch Assay: A Universal Bioassay Device”, Tan Chin Tuan Exchange Fellowship, Ministry of Education Tier 2 Grant: Tailored soft-tissue bioadhesives for site-specific therapy (MOE2012-T2-2-046), and the 2014 Ian Ferguson Innovation Challenge.

References

- [1] Harvey CJ, LeBouf RF, Stefaniak AB. Stefaniak. Formulation and stability of a novel artificial human sweat under conditions of storage and use. *Toxicol In Vitro* 2010;24:1790-6.
- [2] Sawka MN, et al. American College of Sports Medicine position stand. Exercise and fluid replacement. *Med Sci Sports Exerc* 2007;39:377-90.
- [3] Fiona E. Pelly GJS, Tanya M. King. Assessment of Hydration of Athletes. *Nutritional Assessment of Athletes*, Second Edition 2010:341-74.
- [4] Kerkick C. Fluid Needs of Athletes. *Nutritional Guidelines for Athletic Performance* 2012:175-94.
- [5] Armstrong LE. Assessing Hydration Status: The Elusive Gold Standard. *J Am Coll Nutr* 2007;26:575S-84S.
- [6] Taylor N, Machado-Moreira C. Regional variations in transepidermal water loss, eccrine sweat gland density, sweat secretion rates and electrolyte composition in resting and exercising humans. *Extrem Physiol Med* 2013;2:1-30.
- [7] Toker J. The Math of salt loss.
http://www.slowtwitch.com/Training/General_Physiology/The_Math_of_salt_loss_1093.html. 2009.
- [8] Lin Z, et al. Visual detection of copper(ii) based on the aggregation of gold nano-particles via click chemistry. *Anal Methods* 2012;4:612-5.
- [9] Ngo YH, et al. Gold nanoparticles paper as a SERS bio-diagnostic platform. *J Colloid Interf Sci* 2013;409:59-65.
- [10] Lin Y-W, Liu C-W, Chang H-T. DNA functionalized gold nanoparticles for bioanalysis. *Anal Methods* 2009;1:14-24.
- [11] Elghanian R, et al. Selective Colorimetric Detection of Polynucleotides Based on the Distance-Dependent Optical Properties of Gold Nanoparticles. *Science* 1997;277:1078-81.

- [12] Morel A-L, Volmant R-M, M^athivier C, Krafft J-M, Boujday S, Pradier C-M. Optimized immobilization of gold nanoparticles on planar surfaces through alkyldithiols and their use to build 3D biosensors. *Colloids and Surfaces B: Biointerfaces*. 2010;81:304-12.
- [13] Morel A-L, Boujday S, M^athivier C, Krafft J-M, Pradier C-M. Biosensors elaborated on gold nanoparticles, a PM-IRRAS characterisation of the IgG binding efficiency. *Talanta*. 2011;85:35-42.
- [14] Link S, El-Sayed MA. Size and Temperature Dependence of the Plasmon Absorption of Colloidal Gold Nanoparticles. *J Phys Chem B* 1999;103:4212-7.
- [15] Liu X, et al. Biofunctionalized Gold Nanoparticles for Colorimetric Sensing of Botulinum Neurotoxin A Light Chain. *Anal Chem* 2014;86:2345-52.
- [16] Sardar R, et al. Gold Nanoparticles: Past, Present, and Future†. *Langmuir* 2009;25:13840-51.
- [17] Wang G, Sun W. Optical Limiting of Gold Nanoparticle Aggregates Induced by Electrolytes. *The Journal of Physical Chemistry B*. 2006;110:20901-5.
- [18] Caillard L, et al. Gold Nanoparticles on Oxide-Free Silicon–Molecule Interface for Single Electron Transport. *Langmuir* 2013;29:5066-73.
- [19] Tabrizi A, Ayhan F, Ayhan H. Gold nanoparticle synthesis and characterisation. *Hacettepe J Biol & Chem* 2009;37:217-26.
- [20] Salcedo ARM, Sevilla III FB. Citrate-Capped Gold Nanoparticles as Colorimetric Reagent for Copper (II) Ions. *Philipp Sci Lett* 2013; 6: 90-96.
- [21] Steele TWJ, et al. Factors influencing polycation/siRNA colloidal stability toward aerosol lung delivery. *Eur J Pharm Biopharm* 2012;80:14-24.
- [22] Midander K, et al. Nickel release from nickel particles in artificial sweat. *Contact Dermatitis* 2007;56:325-30.
- [23] He L, et al. Colorimetric Sensing of Tetracyclines in Milk Based on the Assembly of Cationic Conjugated Polymer-Aggregated Gold Nanoparticles. *Food Anal Methods* 2013;6:1704-11.
- [24] Bandodkar AJ, et al. Epidermal tattoo potentiometric sodium sensors with wireless signal transduction for continuous non-invasive sweat monitoring. *Biosens Bioelectron* 2014;54:603-9.
- [25] Salvo P, et al. A Wearable Sensor for Measuring Sweat Rate. *IEEE Sens J* 2010;10:1557-8.
- [26] Pietro S. Sweat Rate Wearable Sensors. *Biological and Medical Sensor Technologies* 2012:243-262.

Figure captions:

Figure 1. Schematic illustration of the colorimetric sensor.

264 **Figure 2.** The different color of AuNPs solution in the presence of different concentrations of NaCl.

265 **Figure 3.** UV spectra of AuNPs in the presence of different concentration of NaCl as a function of
266 time.

267 **Figure 4.** Size and Zeta Potential change of AuNPs as a function of time in the presence of different
268 concentrations of NaCl: 26.5 mM (red) 40 mM (purple), 47.9 mM (grey).

269 **Figure 5.** The different colors of AuNPs with artificial sweat.

270

271

272

273

274 **Supplementary Figure S1 UV spectra of AuNPs in the presence of artificial sweat.**
275 Standard deviations (%) of the 26.5 mM, 40 mM and 47.9 mM samples are 1.8 %, 3.0 % and
276 1.0 %, respectively, n=3.

277