Molecular engineering toward coexistence of dielectric and optical switch behavior in hybrid perovskite phase transition material

Hu, Yuzhong; Zhang, Hongbo; Chong, Wee Kiang; Li, Yongxin; Ke, Yujie; Ganguly, Rakesh; Morris, Samuel Alexander; You, Lu; Yu, Ting; Sum, Tze Chien; Long, Yi; Fan, Hong Jin

2018

Hu, Y., Zhang, H., Chong, W. K., Li, Y., Ke, Y., Ganguly, R., ... Fan, H. J. (2018). Molecular engineering toward coexistence of dielectric and optical switch behavior in hybrid perovskite phase transition material. *The Journal of Physical Chemistry A*, 122(31), 6416-6423. doi:10.1021/acs.jpca.8b05693

<https://hdl.handle.net/10356/92447>

<https://doi.org/10.1021/acs.jpca.8b05693>

This document is the Accepted Manuscript version of a Published Work that appeared in final form in *The Journal of Physical Chemistry A*, copyright © American Chemical Society after peer review and technical editing by the publisher. To access the final edited and published work see <https://doi.org/10.1021/acs.jpca.8b05693>

Downloaded on 26 Apr 2023 16:42:19 SGT

This document is confidential and is proprietary to the American Chemical Society and its authors. Do not copy or disclose without written permission. If you have received this item in error, notify the sender and delete all copies.

Molecular Engineering Toward Coexistence of Dielectric and Optical Switch Behavior in Hybrid Perovskite Phase Transition Material

Journal:	<i>The Journal of Physical Chemistry</i>
Manuscript ID	jp-2018-05693f
Manuscript Type:	Article
Date Submitted by the Author:	14-Jun-2018
Complete List of Authors:	<p>Hu, Yuzhong; Nanyang Technological University, School of Physical and Mathematical Sciences</p> <p>Zhang, Hongbo; Nanyang Technological University, School of Physical and Mathematical Sciences</p> <p>Chong , Wee Kiang; Nanyang Technological University, School of Physical and Mathematical Sciences</p> <p>Li, Yongxin; Nanyang Technological University, School of Physical and Mathematical Sciences</p> <p>Ke, Yujie; Nanyang Technological University, School of Materials Science and Engineering</p> <p>Ganguly, Rakesh; Nanyang Technological University, Division of Chemistry and Biological Chemistry</p> <p>Morris, Samuel Alexander; Nanyang Technological University, Facility for Analysis, Characterisation, Testing and Simulation (FACT)</p> <p>You, Lu; Nanyang Technological University, School of Materials Science and Engineering</p> <p>Yu, Ting; Nanyang Technological University, Division of Physics and Applied Physics, School of Physical and Mathematical Sciences</p> <p>Sum, Tze Chien; Nanyang Technological University, Division of Physics & Applied Physics, School of Physical & Mathematical Sciences</p> <p>Long, Yi; Nanyang Technological University, School of Materials Science and Engineering</p> <p>Fan, Hong Jin; Nanyang Technological University, School of Physical and Mathematical Sciences</p>

SCHOLARONE™
Manuscripts

Molecular Engineering Toward Coexistence of Dielectric and Optical Switch Behavior in Hybrid Perovskite Phase Transition Material

Yuzhong Hu,[†] Hongbo Zhang,[†] Wee Kiang Chong,[†] Yongxin Li,[‡] Yujie Ke,[§] Rakesh Ganguly,[‡] Samuel Alexander Morris,^{||} Lu You,[§] Ting Yu,[†] Tze Chien Sum,[†] Yi Long,[§] and Hong Jin Fan^{*,†,‡}

[†] School of Physical and Mathematical Sciences, Nanyang Technological University, Singapore 637371
email: fanhj@ntu.edu.sg

[‡] Division of Chemistry and Biological Chemistry, School of Physical and Mathematical Sciences, Nanyang Technological University, 21 Nanyang Link, Singapore 637371

[§] School of Materials Science and Engineering, Nanyang Technological University Singapore 639798

^{||} Facility for Analysis, Characterisation, Testing and Simulation (FACT), Nanyang Technological University, 50 Nanyang Avenue, 639798, Singapore

Abstract: Organic-inorganic hybrid perovskites with considerable dielectric differences near the phase transition are potential candidates as phase transition materials (PTMs). However, compared with traditional PTMs, which require multiple switchable channels, the hybrid perovskites so far show only switching behavior in dielectric constants. We herein report a new crystal design strategy and successful synthesis of 2D perovskite $(\text{C}_6\text{H}_5\text{C}_2\text{H}_4\text{NH}_3)_2\text{MnCl}_4$. In this hybrid perovskite, the manganese chloride octahedron is a crystal field sensitive luminescent molecule system. And the distortion level of MnCl_6^{4-} also depends on temperature during the order-disorder phase transition. Hence, such a manganese octahedron-based perovskite can exhibit switching behaviors in both dielectric and optical properties. We observe a 14% decrease in optical absorption and 1.6 times increase in dielectric constant during the phase transition at 365 K. In addition, the characteristic photoluminescence decrease by 17% in intensity. Such a molecule-based crystal design paves a new way to explore multifunctional PTM based on organic-inorganic perovskite.

Keyword: 2D hybrid perovskite; phase transition material; dielectric switching; Jahn-Teller distortion; multifunctional perovskites

Main Text:

Control and switch multiple physics channels such as optics and electrics are interesting topic because their special coupling effects like optoelectronic, magneto-electric may consequently lead to novel multifunctional devices.¹⁻⁴ The coexisting physics properties at single phase make multifunctional material be capable of exploiting more than one task at the same time.⁵⁻⁷ This special feature triggers strong research impetus towards new design strategy and device for multifunctional materials in various molecule systems.^{2, 8-9} With the flourishing development of hybrid perovskite solar cell, considerable research efforts have also been devoted to their luminescence, ferroelectricity and crystal structure property.¹⁰⁻¹² The assembling organic, inorganic molecule network with each component carrying one functionality provides hybrid

perovskite intriguing promise as multifunctional material.¹³⁻¹⁴ For example, (Me₃NCH₂C)MnCl₃ reported by You et al exhibits large piezoelectric coefficient of 185 and strong photoluminescence (PL) at 640 nm.¹⁵ The piezoelectric polarization comes from long range ordered dipoles consisted of Me₃NCH₂C⁺ cations and MnCl₆⁴⁻ anions, and the photoluminescence stems from the electron transition in luminescence active manganese ion.

PTM is one of intensively investigated topics in multifunctional materials where various physics channels, such as dielectric constant (ϵ) and absorption coefficient, show switchable behavior between considerably low and high states near the phase transition temperature. Materials with multiple switchable behaviors have a high application potential in rewriteable data storage, signal sensing, data communication, and etc.¹⁶⁻¹⁸ Great efforts have been made to trigger dielectric switch behavior and design multifunctional PTMs in several material systems, such as organics, hybrid perovskites and metal organic framework.¹⁹⁻²¹ For example, Sun et al realized dielectric transition in an organic material by temperature-triggered molecule motion of trifluoromethanesulfonate anionic moiety in 4- N, N -Dimethylamino - 4 - N-methylstilbazolium Trifluoromethanesulfonate.²⁰ Shi et al reported two multifunctional phase transition materials based on hybrid perovskites, where both dielectric constant and second harmonic generation exhibit low and high states around the phase transition temperature.^{19,19} In these materials, the dielectric increases are attributed to the order-disorder transitions of organic cations, while the second harmonic generation switch behaviors are due to the transitions in the crystals centrosymmetry property. However, in hybrid perovskites, though much progress has been made to design and synthesize new PTMs, most of them only exhibit dielectric switching behavior.²⁰⁻²³ For their potential application in conventional PTM field such as optical disk, different memory states manifested by low and high optical absorption are desirable.

In this work, we report a new design strategy and property of a hybrid perovskite (C₆H₅C₂H₄NH₃)₂MnCl₄ as multifunctional PTM which exhibits coupled switch behaviors in dielectric, absorption and PL. Here we first trace the design strategy of realizing absorption

and PL switch behaviors in this material. In hybrid perovskite, optics properties such as PL are mainly determined by electron transition in inorganic layer, so the length of metal-halide chemical bond and structural distortion of inorganic lattice play key roles in the optical absorption and emission.²⁴⁻²⁶ Consequently, for the prospect of manipulating optical property, one of the methods is to change the distortion level of metal-halide octahedron.²⁷⁻²⁹ To this end, several methods have been reported, such as applying pressure,³⁰ employing different organic parts²⁹ and triggering phase transition.²⁷ Our strategy is to employ a metal-halide octahedron which both has crystal distortion sensitive optical property and goes through de-distortion molecule motion during phase transition. To design a molecule system with these two features, we consider transition metal centered octahedral system. From crystal field theory, a transition metal centered octahedron system is a non-linear one with degenerate energy states. This kind of system will spontaneously have Jahn-Teller distortion (JTD) to split its energy state and consequently remove its degeneracy.³¹ In particular, with increasing temperature, the phase transition of MnX_6^{4-} (X: halide) octahedron based perovskites generally undergo a de-JTD process due to thermal effect.³¹ Additionally, it is reported that MnCl_6^{4-} exhibits high sensitivity of its optical absorption and PL to the crystal field strength, which changes with the distortion level.³² Consequently, $(\text{C}_6\text{H}_5\text{C}_2\text{H}_4\text{NH}_3)_2\text{MnCl}_4$ is supposed to show both distortion sensitive optical properties and undergo de-JTD during phase transition. In addition, its large phenethylammonium (PEA) organic part leads to high stability and 2D structure feature, which is important for the miniaturization of memory material. Our measurements show that this crystal exhibits evident changes in optical absorption (13.7%) and PL intensity (17.5%) near the phase transition temperature. Another influence of de-JTD is the appearance of dielectric switch behavior at phase transition. With a decrease in distortion level, the symmetry of the inorganic layer becomes higher. This structure change induces equivalent energy states for the organic cation. At high temperatures, the PEA cations can overcome the energy barrier between equivalent states. As a result, order-disorder phase transition is triggered, accompanied by dielectric switch behavior.

The crystal structures of (PEA)₂MnCl₄ single crystal were studied using X-ray single-crystal diffraction analysis at 300 K (room temperature phase, RTP) and 380 K (high temperature phase, HTP). Table 1 lists the basic crystal structure information. At RTP (Fig. 1a), the crystal consists of MnCl₆⁴⁻ inorganic layers and PEA organic layers. The metal-halide octahedra share corners and form the 2D network while PEA cations occupy the space enclosed by inorganic layers and link MnCl₆⁴⁻ by hydrogen bonds between H in ammonias and Cl in metal halide octahedra. Different layers of perovskite are weakly bonded to each other by van der Waals interaction, making this material capable to be exfoliated to nanometer level thin film. Within the metal-halide layer, each manganese atom is surrounded by six chloride atoms, where four in-plane Cl atoms bridge Mn atoms in four nearby MnCl₆⁴⁻ octahedra. Because of JTD, the inorganic layers show distinct tilt both inside and between each metal-halide octahedron. The Cl-Mn-Cl angles around Mn range from 88.68° to 91.32° and the bridging angle (Mn-Cl-Mn) between octahedra is 168.56° (see Fig. 1c).

Table.1 Crystallography data of (PEA)₂MnCl₄ measured at two different temperatures.

	RTP	HTP
Empirical formula	(C ₆ H ₅ C ₂ H ₄ NH ₃) ₂ MnCl ₄	(C ₆ H ₅ C ₂ H ₄ NH ₃) ₂ MnCl ₄
Crystal system space group	Pbca	I $\bar{4}$
Measurement temperature (K)	300	380
a (Å)	7.159(3)	5.1435(3)
b (Å)	7.256(3)	5.1435(3)
c (Å)	39.280(15)	39.822(2)
β (°)	90	90
Lattice volume (Å ³)	2040.4(13)	1053.51(14)
Absorption correction	1.170 mm ⁻¹	1.133 mm ⁻¹
Z	4	2
F(000)	908	454
T _{min} / T _{max}	0.9330 / 0.7060	0.9350 / 0.7130
Goodness of fit (GOF)	1.074	1.124
R ₁ [I>2σ(I)]	0.0494	0.0425
wR ₂ [I>2σ(I)]	0.1229	0.1337

In the heating process, a phase transition towards higher disorder level of organic cation and de-JTD of metal-halide octahedron occurs.³¹ At HTP (Fig. 1b), the in-plane Cl-Mn-Cl angles change to 90° and out of plane angles range from 89.55 to 90.45°, which means the MnCl_6^{4-} systems have almost become standard octahedron. The Mn-Cl-Mn bridging angle changes to 179.10° (Fig. 1d), indicating that the distortion between adjacent metal-halide octahedra has diminished. Because of the inorganic framework transition and thermal effect, the phenethylammonium cations exhibit a distinct disorder phase with all atoms apparently existing in two possible positions.

Figure 1. Comparison of the crystal structure between RTP and HTP of $(\text{PEA})_2\text{MnCl}_4$. Perspective view at 300 (a) and 380 K (b). Top view of inorganic layer at 300 (c) and 380 K (d).

Differential scanning calorimetry (DSC) measurement is a powerful method for detecting reversible phase transition triggered by temperature (T_c). As shown in Fig. 2a, there is an exothermal peak at 365 K and 2 K thermal hysteresis (the dip in heating process and peak in

cooling process). The area under the phase transition curves yields values for entropy change (ΔS) of 1.22 J/mol $\cdot$ K. From Boltzmann equation, ΔS is given by $\Delta S = R \ln N$, where R is the gas constant and N is the number of sites in a disorder system. For a pure order-disorder phase transition, N is supposed to be 2 or larger integer.³³ The calculated N value for $(\text{PEA})_2\text{MnCl}_4$ is 1.15, which indicates the phase transition near $T_c = 365$ K is a more complex one rather than typical order-disorder type.^{19, 34} In addition, to investigate the thermostability, thermogravimetric analysis (TGA) was conducted on the bulk single crystal. The TGA curve reveals that $(\text{PEA})_2\text{MnCl}_4$ is stable up to around 473 K (Fig. 2b) and thus suggests this perovskite can meet the general working condition of optoelectronic device.

Figure 2. DSC curve obtained in a heating-cooling cycle (a) and TGA analysis (b) of the single crystal $(\text{PEA})_2\text{MnCl}_4$.

Raman spectroscopy is a powerful method for the investigation of phase transition in layered materials.³⁵⁻³⁷ In general, low-frequency Raman modes are often coupled to the order parameters of a phase transition.³⁸⁻³⁹ In the Raman spectra recorded from our single crystal, two low-frequency modes are observed and both show an obvious temperature dependence (see Fig. 3). At room temperature, these two modes are centered at 16 cm^{-1} and 39 cm^{-1} (refer to α and β , respectively). The previous Raman study of PEA type perovskites⁴⁰ reveals the α mode represents the shear mode of the organic layer with respect to metal-halide layer along the in-plane direction (see inset of Fig. 3) while the β mode corresponds to the rotation of NH_3^+ along c axis. The intensities of α and β modes continue to decrease to $T_c = 363$ K, around which

both of these two peaks disappear. This phenomenon suggests a translational symmetry breaking. For a pure order-disorder phase transition, the soft mode energy does not go to zero at T_c .⁴⁰ But in this material, both α and β modes disappear around 363 K. This also indicates that the phase transition in $(\text{PEA})_2\text{MnCl}_4$ is not a pure order-disorder type. Additionally, with temperature increasing close to T_c , both modes soften and broaden considerably. This behavior suggests the phase transition has a displacive nature, which is manifested by softening of collective excitation.⁴¹⁻⁴³ Hence, we may conclude that the phase transition at 363 K is an order-disorder type in conjunction with displacive nature appearing consistent to the DSC measurement.

Figure 3. Temperature dependent Raman spectra of the $(\text{PEA})_2\text{MnCl}_4$ crystal. The solid lines are fitted spectra. The inset shows the displacement direction of the α peak, where the red and black arrows indicate the inorganic and organic displacement direction, respectively.

It is found that several switchable properties coexist in our $(\text{PEA})_2\text{MnCl}_4$ crystal around the phase transition temperature. We first discuss the dielectric constant. Here, measurement of temperature dependent dielectric constant was performed on the bulk single crystal sample of $(\text{PEA})_2\text{MnCl}_4$ in the heating mode. The well-defined facets indicate good quality of the bulk crystal (see Fig. 4a). Pole figure was measured to confirm the direction of [100] and [010] of the HTP single crystal (Fig. 4b). As shown in Fig. 4c and 4d, step-like anomalies at around 366 K can be observed along the [100] and [010] directions whereas no anomaly was found in the

[001] direction. With the temperature approaching T_c , the dielectric constant increases by 1.64 and 1.66 times along the [100] and [010] direction, respectively.

Figure 4. Photograph (a) and dielectric switch measurement of (PEA)₂MnCl₄. (b) is pole figure of bulk crystal. (c) and (d) are temperature dependent dielectric constant (ϵ) along the two crystallographic directions of [100] and [010] at 1 MHz AC electric field, respectively.

The ϵ increase along the [100] and [010] directions and the anisotropy of dielectric constant can be explained by the structure transformation during phase transition. As illustrated in Fig. 5a, at RTP, the metal-halide octahedron system has a relatively lower symmetry. With hydrogen bond interaction between PEA cations and inorganic octahedron systems, the organic cations will be fixed at certain position where they have the lowest energy.⁴⁴ At HTP (Fig. 5b), JTD has been almost eliminated leading to expansion of the inorganic framework. As a result, the H–Cl hydrogen bonds are weakened due to the increased bonding length (from 2.40 to 2.69 Å at RTP and from 2.68 to 2.79 Å at HTP). Subsequently the degree of freedom of the cation increases and thus contributes to the switching behavior of the dielectric constant at HTP. More importantly, the de-JTD induces a mirror symmetry along the Mn–Cl–Mn bridges in each quasi-cuboid inorganic unit (see in Fig. 5b). Consequently, for the organic PEA cation, there are equivalent states with same energy in the diagonal plane of this quasi-cuboid system, which

induces two possible positions and results in the order-disorder transition of the PEA cation. Therefore, with this temperature induced change in crystal dynamic and higher degree of freedom, the organic cations are capable of switching between two equivalent states with small energy barrier along the diagonal plane under AC electric field. Consequently, there is a linear relationship between the increases in permittivity along the [100] and [010] directions at T_c , which also explains why the corresponding dielectric constants increase by similar times (1.64 and 1.66).

Figure 5. Crystal structure and length of hydrogen bonds (black and red dashed lines denote two different equivalent states. Length unit is Å) at RTP (a) and HTP (b). Left middle of (b) is the symmetry property of inorganic system.

As expected, the $(\text{PEA})_2\text{MnCl}_4$ crystal is also an optical material. The absorption and PL spectrum are illustrated in Fig. 6c. Six absorption peaks can be distinguished at around 272, 356, 417, 458, 503 and 605 nm. Among them, peak II to V are highly consistent with previous studies on the band structure of Mn^{2+} .⁴⁵ The weak absorption at 603 nm possibly originates from the direct electron transfer from ground state to the first excited triplet state in Mn^{2+} .⁴⁶⁻⁴⁷ Though the direct promotion of electron from ground state to triplet state is theoretically forbidden by absorption selection rule, this transition may take place because of distortion or impurity in crystal. Another peak at 272 nm stems from the transition between p orbitals of carbon and chlorine in phenethylammonium cation.⁴⁸ In addition, our $(\text{PEA})_2\text{MnCl}_4$ crystal is found strongly luminescent. Figure 6a is the photograph of the bulk crystal attached to a quartz. A strong orange color luminescence can be observed under 420 nm excitation (see Fig. 6b), and the corresponding PL spectrum is shown in Fig. 6c, where a broad emission peak is centered at 602 nm. The corresponding lifetime measurement of this 602 nm emission is shown

in Fig. 6d. The relatively large lifetime, 210 μs , lies in the general lifetime range of phosphorescence. Considering the relatively long PL lifetime, emission peak position and luminescence metal ion origin, we can assign this orange phosphorescence to the $(t_{2g})^4(e_g)^1 \rightarrow (t_{2g})^3(e_g)^2$ transition in the octahedrally coordinated manganese.^{3, 46-47}

Figure 6. Photograph of the bulk crystal (attached to a quartz substrate) (a) and luminescence under 420 nm excitation (b). Normalized absorption and photoluminescence spectrum (c) and PL lifetime (d).

In addition to the aforementioned dielectric switch behavior, the change in optical property associated with the phase transition is an interesting topic in PTM.^{16, 19} Especially, much attention has been paid to the short wavelength and ultraviolet region since a laser beam with shorter wavelength can be focused to smaller spot and achieve higher memory capacity.¹⁶ To investigate possible optical switch behavior of our $(\text{PEA})_2\text{MnCl}_4$ single crystal, we measured the absorption and PL spectrum around the phase transition temperature (365 K). As demonstrated in Fig. 7a, the absorption intensity shows 12.4% and 13.7 % change for the two peaks at 356 and 264 nm peak, respectively. The intensity differences before the onset of phase transition (between 353 and 363 K) and after T_c (between 367 and 373 K) of these two peaks are very small. So we can infer that this abrupt change in optical absorption across T_c results from the structure change rather than temperature difference. The absorption switching behavior at 265 nm may come from the disordered molecule motion of the PEA organic cation, while the change at 356 nm may be attributed to the change in the density of state triggered by

different distortion levels in the metal halide octahedron.^{30, 49-50} The photoluminescence peak obtained by 532 nm excitation also shows a 17.5% intensity decrease with a slight redshift of 2 nm near T_c (see Fig. 7b). This intensity decrease may be attributed to the amorphous-order phase transition of the metal halide octahedron.^{30, 32, 50} It may also be attracted to shift of excitation spectrum caused by removal of distortion in MnCl_6^{4-} system. The slight redshift comes from the changed axial crystal field, which is consistent to previous report.³²

Figure 7. Normalized absorption (a) and PL spectra excited by 532 nm laser (b) near the phase transition temperature (365 K). The inset in (a) and (b) show the intensity change of the absorption at 265 nm and emission at 608 nm as a function of temperature, respectively.

In conclusion, by a molecular design strategy, we have successfully achieved the synthesis a 2D hybrid perovskite single crystal and demonstrated it to be a multifunctional phase transition material. The crystal exhibits coupled switching response in both dielectric constant, optical absorption, as well as photoluminescence intensity near the phase transition point. The absorption and photoluminescence changes are induced by de-Jahn Teller phase transition in the Mn based octahedral system, which has a distortion sensitive absorption and PL spectrum. Dielectric switch behavior is induced by a coupled effect between order-disorder transition and inorganic layer symmetry change. This material design strategy may open a new avenue for the preparation of multifunctional phase transition materials based on organic-inorganic hybrid perovskites.

Experimental section

Synthesis of (PEA)₂MnCl₄ single crystal: All chemicals were purchased from Sigma-Aldrich and used as received. Single crystal of (PEA)₂MnCl₄ was synthesized by reaction of 4 mmol PEAHCl and 2 mmol MnCl₂ at room temperature. Brown crystals with a nearly squared face (Fig. 4a) were obtained by slow evaporation of 4.4 ml mixed methanol and deionized water with volume ratio of 10:1.

XRD: Pole figures of the obtained crystal was measured on bulk single crystal. The XRD data were recorded by a Bruker D8 Discover thin film X-ray diffractometer ($\lambda = 0.71073 \text{ \AA}$). Crystallography data with approximate dimensions of 0.060 x 0.220 x 0.320 mm were collected using a Bruker APEX II diffractometer. The crystals of (PEA)₂MnCl₄ were measured at 300 and 380 K. The structure was solved by Bruker SHELXTL Software Package and refined for all data by Full-matrix least-squares on F^2 . All nonhydrogen atoms were subjected to anisotropic refinement. The hydrogen atoms were generated geometrically and allowed to ride in their respective parent atoms; they were assigned appropriate isotropic thermal parameters and included in the structure factor calculations. The data can be obtained free of charge from the Cambridge Crystallography Data Center via www.ccdc.cam.ac.uk/data_request/cif

Differential scanning calorimetry (DSC) measurement: DSC was performed on a TA Q10 by heating and cooling single crystal sample with a rate of 3 K min⁻¹ in an aluminum pan under nitrogen at atmospheric pressure.

Thermogravimetric analysis: thermal stability was measured on bulk single crystal by a TGA/Q500 V6.7 Build 203 instrument with a rate of 10 K min⁻¹ under air.

Dielectric property: dielectric measurement was carried out on single crystal specimen by Agilent E 4980A with 1 V AC voltage and conductive tip on probe station. To measure in-plane dielectric property, interdigitated electrodes were deposited by evaporating 5 nm chromium and 50 nm gold on the bulk single crystal with mask.

Absorption and PL property: Absorption spectrum was recorded using an Agilent Technologies UV-Vis-NIR spectrometer with Cary 5000 model. Room temperature PL spectrum was measured by Shimadzu RF 5301-PC Spectrofluorophotometer. Temperature dependent PL spectrum was performed in vacuum on WITec Alpha300 Series confocal Raman system with 600 g/mm grating and 532 nm excitation laser. The temperature was controlled by a stage HFS600E from Linkam Scientific Instruments. Time-resolved PL measurements were conducted using 420 nm femtosecond excitation pulses (50 fs, 1 KHz). The backscattered PL emission was collected and dispersed using a 150 g mm⁻¹ spectrometer (Princeton Instruments), and temporally resolved using an Optronis streak camera system. The crystal lifetime ($210 \pm$

10 μ s) was determined by averaging lifetimes from 3 different crystal positions. All these measurements were conducted on bulk single crystal.

Raman spectrum: Raman spectra were recorded using a WITec Alpha300 Series confocal Raman system in vacuum with a 2400 lines mm^{-1} grating and a 50X objective under 532 nm laser excitation. The laser power was kept at 1 mW. All the Raman and PL temperature dependent measurements were conducted in a vacuum chamber and the temperature was controlled by a stage HFS600E from Linkam Scientific Instruments.

AUTHOR INFORMATION

Corresponding Authors.

*Email: fanhj@ntu.edu.sg

Notes

The authors declare no competing financial interest.

ACKNOWLEDGEMENTS

This work is supported by the Singapore MOE AcRF Tier 1 grants (RG115/15 and RG199/17) and the MOE Tier 2 grant (MOE2015-T2-2-015).

References

1. Wen, Z.; Li, C.; Wu, D.; Li, A.; Ming, N., Ferroelectric-field-effect-enhanced electroresistance in metal/ferroelectric/semiconductor tunnel junctions. *Nat. Mater.* **2013**, 12 (7), 617-621.
2. Hao, J.; Zhang, Y.; Wei, X., Electric-Induced Enhancement and Modulation of Upconversion Photoluminescence in Epitaxial $\text{BaTiO}_3\text{:Yb/Er}$ Thin Films. *Angew. Chem. Int. Ed.* **2011**, 123 (30), 7008-7012.
3. Ye, H. Y.; Zhou, Q.; Niu, X.; Liao, W. Q.; Fu, D. W.; Zhang, Y.; You, Y. M.; Wang, J.; Chen, Z. N.; Xiong, R. G., High-Temperature Ferroelectricity and Photoluminescence in a Hybrid Organic-Inorganic Compound: (3-Pyrrolinium) MnCl_3 . *J. Am. Chem. Soc.* **2015**, 137 (40), 13148-54.
4. Yao, Q.; Wang, F.; Xu, F.; Leung, C. M.; Wang, T.; Tang, Y.; Ye, X.; Xie, Y.; Sun, D.; Shi, W., Electric field-induced giant strain and photoluminescence-enhancement effect in rare-earth modified lead-free piezoelectric ceramics. *ACS Appl. Mater. Interfaces* **2015**, 7 (9), 5066-5075.
5. Itkis, M.; Chi, X.; Cordes, A.; Haddon, R., Magneto-opto-electronic bistability in a phenalenyl-based neutral radical. *Science* **2002**, 296 (5572), 1443-1445.
6. Kahn, O.; Martinez, C. J., Spin-transition polymers: from molecular materials toward memory devices. *Science* **1998**, 279 (5347), 44-48.
7. Gaultois, M. W.; Barton, P. T.; Birkel, C. S.; Misch, L. M.; Rodriguez, E. E.; Stucky, G. D.; Seshadri, R., Structural disorder, magnetism, and electrical and thermoelectric properties of pyrochlore $\text{Nd}_2\text{Ru}_2\text{O}_7$. *J. Phys.: Condens. Matter* **2013**, 25 (18), 186004.

8. Zhang, Y.; Liao, W. Q.; Fu, D. W.; Ye, H. Y.; Chen, Z. N.; Xiong, R. G., Highly Efficient Red-Light Emission in An Organic-Inorganic Hybrid Ferroelectric: (Pyrrolidinium)MnCl(3). *J. Am. Chem. Soc.* **2015**, *137* (15), 4928-31.
9. Melot, B. C.; Goldman, A.; Darago, L. E.; Furman, J. D.; Rodriguez, E. E.; Seshadri, R., Magnetic ordering and magnetodielectric phenomena in CoSeO₄. *J. Phys.: Condens. Matter* **2010**, *22* (50), 506003.
10. Shi, Z.; Guo, J.; Chen, Y.; Li, Q.; Pan, Y.; Zhang, H.; Xia, Y.; Huang, W., Lead-free Organic-Inorganic Hybrid Perovskites for Photovoltaic Applications: Recent Advances and Perspectives. *Adv. Mater.* **2017**, *29* (16), 1605005.
11. Hu, T.; Smith, M. D.; Dohner, E. R.; Sher, M.-J.; Wu, X.; Trinh, M. T.; Fisher, A.; Corbett, J.; Zhu, X.-Y.; Karunadasa, H. I., Mechanism for broadband white-light emission from two-dimensional (110) hybrid perovskites. *J. Phys. Chem. Lett.* **2016**, *7* (12), 2258-2263.
12. Liao, W. Q.; Zhang, Y.; Hu, C. L.; Mao, J. G.; Ye, H. Y.; Li, P. F.; Huang, S. D.; Xiong, R. G., A lead-halide perovskite molecular ferroelectric semiconductor. *Nat. Commun.* **2015**, *6*, 7338.
13. Zhang, Y.; Liao, W. Q.; Fu, D. W.; Ye, H. Y.; Liu, C. M.; Chen, Z. N.; Xiong, R. G., The First Organic-Inorganic Hybrid Luminescent Multiferroic: (Pyrrolidinium)MnBr₃. *Adv. Mater.* **2015**, *27* (26), 3942-6.
14. Bellitto, C.; Bauer, E. M.; Righini, G., Organic-inorganic hybrids: From magnetic perovskite metal (II) halides to multifunctional metal (II) phosphonates. *Coord. Chem. Rev.* **2015**, *289*, 123-136.
15. You, Y. M.; Liao, W. Q.; Zhao, D.; Ye, H. Y.; Zhang, Y.; Zhou, Q., An organic-inorganic perovskite ferroelectric with large piezoelectric response. *Science* **2017**, *357*, 306-309.
16. Wuttig, M.; Yamada, N., Phase-change materials for rewriteable data storage. *Nat. Mater.* **2007**, *6* (11), 824-832.
17. Salinga, M.; Wuttig, M., Phase-change memories on a diet. *Science* **2011**, *332* (6029), 543-544.
18. Sun, Z.; Luo, J.; Zhang, S.; Ji, C.; Zhou, L.; Li, S.; Deng, F.; Hong, M., Solid-State Reversible Quadratic Nonlinear Optical Molecular Switch with an Exceptionally Large Contrast. *Adv. Mater.* **2013**, *25* (30), 4159-4163.
19. Shi, P.-P.; Ye, Q.; Li, Q.; Wang, H.-T.; Fu, D.-W.; Zhang, Y.; Xiong, R.-G., Novel Phase-Transition Materials Coupled with Switchable Dielectric, Magnetic, and Optical Properties: [(CH₃)₄P][FeCl₄] and [(CH₃)₄P][FeBr₄]. *Chem. Mater.* **2014**, *26* (20), 6042-6049.
20. Sun, Z.; Luo, J.; Chen, T.; Li, L.; Xiong, R. G.; Tong, M. L.; Hong, M., Distinct Molecular Motions in a Switchable Chromophore Dielectric 4-N, N-Dimethylamino-4'-N'-methylstilbazolium Trifluoromethanesulfonate. *Adv. Funct. Mater.* **2012**, *22* (23), 4855-4861.
21. Zhang, W.; Ye, H.-Y.; Graf, R.; Spiess, H. W.; Yao, Y.-F.; Zhu, R.-Q.; Xiong, R.-G., Tunable and switchable dielectric constant in an amphidynamic crystal. *J. Am. Chem. Soc.* **2013**, *135* (14), 5230-5233.
22. Shi, X.; Luo, J.; Sun, Z.; Li, S.; Ji, C.; Li, L.; Han, L.; Zhang, S.; Yuan, D.; Hong, M., Switchable dielectric phase transition induced by ordering of twisting motion in 1, 4-diazabicyclo [2.2. 2] octane chlorodifluoroacetate. *Crystal Growth & Design* **2013**, *13* (5), 2081-2086.
23. Ji, C.; Sun, Z.; Zhang, S.-Q.; Chen, T.; Zhou, P.; Tang, Y.; Zhao, S.; Luo, J., Switchable dielectric behaviour associated with above room-temperature phase transition in N-isopropylbenzylammonium dichloroacetate (N-IPBADC). *J. Mater. Chem. C* **2014**, *2* (30), 6134-6139.
24. Chen, Q.; De Marco, N.; Yang, Y.; Song, T.-B.; Chen, C.-C.; Zhao, H.; Hong, Z.; Zhou, H.; Yang, Y., Under the spotlight: The organic-inorganic hybrid halide perovskite for optoelectronic applications. *Nano Today* **2015**, *10* (3), 355-396.
25. Wang, T.; Daiber, B.; Frost, J. M.; Mann, S. A.; Garnett, E. C.; Walsh, A.; Ehrler, B., Indirect to direct bandgap transition in methylammonium lead halide perovskite. *Energy Environ. Sci.* **2017**, *10* (2), 509-515.
26. Stoumpos, C. C.; Frazer, L.; Clark, D. J.; Kim, Y. S.; Rhim, S. H.; Freeman, A. J.; Ketterson, J. B.; Jang, J. I.; Kanatzidis, M. G., Hybrid germanium iodide perovskite semiconductors: active lone pairs, structural distortions,

- direct and indirect energy gaps, and strong nonlinear optical properties. *J. Am. Chem. Soc.* **2015**, *137* (21), 6804-6819.
27. Quarti, C.; Mosconi, E.; Ball, J. M.; D'Innocenzo, V.; Tao, C.; Pathak, S.; Snaith, H. J.; Petrozza, A.; De Angelis, F., Structural and optical properties of methylammonium lead iodide across the tetragonal to cubic phase transition: implications for perovskite solar cells. *Energy Environ. Sci.* **2016**, *9* (1), 155-163.
28. Jaffe, A.; Lin, Y.; Karunadasa, H. I., Halide Perovskites Under Pressure: Accessing New Properties Through Lattice Compression. *ACS Energy Letters* **2017**.
29. Cortecchia, D.; Neutzner, S.; Srimath Kandada, A. R.; Mosconi, E.; Meggiolaro, D.; De Angelis, F.; Soci, C.; Petrozza, A., Broadband Emission in Two-Dimensional Hybrid Perovskites: The Role of Structural Deformation. *J. Am. Chem. Soc.* **2017**, *139* (1), 39-42.
30. Wang, L.; Wang, K.; Zou, B., Pressure-induced structural and optical properties of organometal halide perovskite-based formamidinium lead bromide. *J. Phys. Chem. Lett.* **2016**, *7* (13), 2556-2562.
31. Depmeier, W.; Felsche, J.; Wildermuth, G., Phases and phase transitions of compounds $(\text{C}_n\text{H}_{2n+1}\text{NH}_3)2\text{MnCl}_4$ with $n = 1, 2, 3$. *J. Solid State Chem.* **1977**, *21* (1), 57-65.
32. Nataf, L.; Rodríguez, F.; Valiente, R.; González, J., Spectroscopic and luminescence properties of $(\text{CH}_3)_4\text{NMnCl}_3$: a sensitive Mn $2+$ -based pressure gauge. *High Pressure Research* **2009**, *29* (4), 653-659.
33. Jain, P.; Ramachandran, V.; Clark, R. J.; Zhou, H. D.; Toby, B. H.; Dalal, N. S.; Kroto, H. W.; Cheetham, A. K., Multiferroic behavior associated with an order–disorder hydrogen bonding transition in metal–organic frameworks (MOFs) with the perovskite ABX_3 architecture. *J. Am. Chem. Soc.* **2009**, *131* (38), 13625-13627.
34. Liu, Y.; Chen, Y.; Xu, M.-j.; Zhu, C.-L.; Liu, Z.-q., Synthesis, structure, and phase transition of a novel proton transfer in a supramolecular cation with 2-nitroanilinium based on 18-crown-6. *J. Mol. Struct.* **2017**, *1148*, 429-434.
35. Kang, Y.; Najmaei, S.; Liu, Z.; Bao, Y.; Wang, Y.; Zhu, X.; Halas, N. J.; Nordlander, P.; Ajayan, P. M.; Lou, J., Plasmonic hot electron induced structural phase transition in a MoS_2 monolayer. *Adv. Mater.* **2014**, *26* (37), 6467-6471.
36. Hagemann, H.; Bill, H., Raman spectroscopic study of structural phase transitions in the layer crystals $(\text{EtNH}_3)2\text{MCl}_4$ with $\text{M} = \text{Cd}$ and Mn . *Journal of Physics C: Solid State Physics* **1985**, *18* (35), 6441.
37. Zhang, X.; Qiao, X.-F.; Shi, W.; Wu, J.-B.; Jiang, D.-S.; Tan, P.-H., Phonon and Raman scattering of two-dimensional transition metal dichalcogenides from monolayer, multilayer to bulk material. *Chem. Soc. Rev.* **2015**, *44* (9), 2757-2785.
38. Scott, J., Soft-mode spectroscopy: Experimental studies of structural phase transitions. *Rev. Mod. Phys.* **1974**, *46* (1), 83.
39. Petzelt, J.; Dvorak, V., Changes of infrared and Raman spectra induced by structural phase transitions. I. General considerations. *Journal of Physics C: Solid State Physics* **1976**, *9* (8), 1571.
40. Caretta, A.; Miranti, R.; Havenith, R. W. A.; Rampi, E.; Donker, M. C.; Blake, G. R.; Montagnese, M.; Polyakov, A. O.; Broer, R.; Palstra, T. T. M.; van Loosdrecht, P. H. M., Low-frequency Raman study of the ferroelectric phase transition in a layered CuCl_4 -based organic-inorganic hybrid. *Phys. Rev. B* **2014**, *89* (2).
41. Cochran, W., Crystal stability and the theory of ferroelectricity. *Advances in Physics* **1960**, *9* (36), 387-423.
42. Schneider, T.; Srinivasan, G.; Enz, C., Phase transitions and soft modes. *Physical Review A* **1972**, *5* (3), 1528.
43. Lines, M. E.; Glass, A. M., *Principles and applications of ferroelectrics and related materials*. Oxford university press: 1977.
44. Mitzi, D. B., Templating and structural engineering in organic–inorganic perovskites. *J. Chem. Soc., Dalton Trans.* **2001**, (1), 1-12.
45. Lawson, K. E., Optical Studies of Electronic Transitions in Hexa- and Tetracoordinated Mn^{2+} Crystals. *J. Chem. Phys.* **1967**, *47* (9), 3627-3633.

- 1
2
3 46. Orgel, L., Band Widths in the Spectra of Manganous and Other Transition-Metal Complexes. *J. Chem. Phys.*
4 **1955**, 23 (10), 1824-1826.
5
6 47. Orgel, L., Phosphorescence of solids containing the manganous or Ferric ions. *J. Chem. Phys.* **1955**, 23 (10),
7 1958-1958.
8
9 48. Kassou, S.; El-Mrabet, R.; Kaiba, A.; Guionneau, P.; Belaraj, A., Combined experimental and density
10 functional theory studies of an organic–inorganic hybrid perovskite. *Phys. Chem. Chem. Phys.* **2016**, 18 (14), 9431-
11 9436.
12
13 49. Amat, A.; Mosconi, E.; Ronca, E.; Quarti, C.; Umari, P.; Nazeeruddin, M. K.; Grätzel, M.; De Angelis, F., Cation-
14 induced band-gap tuning in organohalide perovskites: interplay of spin–orbit coupling and octahedra tilting. *Nano*
15 *Lett.* **2014**, 14 (6), 3608-3616.
16
17 50. Wang, Y.; Lü, X.; Yang, W.; Wen, T.; Yang, L.; Ren, X.; Wang, L.; Lin, Z.; Zhao, Y., Pressure-induced phase
18 transformation, reversible amorphization, and anomalous visible light response in organolead bromide perovskite.
19 *J. Am. Chem. Soc.* **2015**, 137 (34), 11144-11149.
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60